

ISSN 2518-1491 (Online),
ISSN 2224-5286 (Print)

ҚАЗАҚСТАН РЕСПУБЛИКАСЫ
ҰЛТТЫҚ ҒЫЛЫМ АКАДЕМИЯСЫНЫҢ

Д.В.Сокольский атындағы «Жанармай,
катализ және электрохимия институты» АҚ

Х А Б А Р Л А Р Ы

ИЗВЕСТИЯ

НАЦИОНАЛЬНОЙ АКАДЕМИИ НАУК
РЕСПУБЛИКИ КАЗАХСТАН
АО «Институт топлива, катализа и
электрохимии им. Д.В. Сокольского»

NEWS

OF THE ACADEMY OF SCIENCES
OF THE REPUBLIC OF KAZAKHSTAN
JSC «D.V. Sokolsky institute of fuel, catalysis
and electrochemistry»

SERIES
CHEMISTRY AND TECHNOLOGY

4 (436)

JULY-AUGUST 2019

PUBLISHED SINCE JANUARY 1947

PUBLISHED 6 TIMES A YEAR

ALMATY, NAS RK

NAS RK is pleased to announce that News of NAS RK. Series of chemistry and technologies scientific journal has been accepted for indexing in the Emerging Sources Citation Index, a new edition of Web of Science. Content in this index is under consideration by Clarivate Analytics to be accepted in the Science Citation Index Expanded, the Social Sciences Citation Index, and the Arts & Humanities Citation Index. The quality and depth of content Web of Science offers to researchers, authors, publishers, and institutions sets it apart from other research databases. The inclusion of News of NAS RK. Series of chemistry and technologies in the Emerging Sources Citation Index demonstrates our dedication to providing the most relevant and influential content of chemical sciences to our community.

Қазақстан Республикасы Ұлттық ғылым академиясы "ҚР ҰҒА Хабарлары. Химия және технология сериясы" ғылыми журналының Web of Science-тің жаңаланған нұсқасы Emerging Sources Citation Index-те индекстелуге қабылданғанын хабарлайды. Бұл индекстелу барысында Clarivate Analytics компаниясы журналды одан әрі the Science Citation Index Expanded, the Social Sciences Citation Index және the Arts & Humanities Citation Index-ке қабылдау мәселесін қарастыруда. Web of Science зерттеушілер, авторлар, баспашылар мен мекемелерге контент тереңдігі мен сапасын ұсынады. ҚР ҰҒА Хабарлары. Химия және технология сериясы Emerging Sources Citation Index-ке енуі біздің қоғамдастық үшін ең өзекті және беделді химиялық ғылымдар бойынша контентке адалдығымызды білдіреді.

НАН РК сообщает, что научный журнал «Известия НАН РК. Серия химии и технологий» был принят для индексирования в Emerging Sources Citation Index, обновленной версии Web of Science. Содержание в этом индексировании находится в стадии рассмотрения компанией Clarivate Analytics для дальнейшего принятия журнала в the Science Citation Index Expanded, the Social Sciences Citation Index и the Arts & Humanities Citation Index. Web of Science предлагает качество и глубину контента для исследователей, авторов, издателей и учреждений. Включение Известия НАН РК в Emerging Sources Citation Index демонстрирует нашу приверженность к наиболее актуальному и влиятельному контенту по химическим наукам для нашего сообщества.

Б а с р е д а к т о р ы
х.ғ.д., проф., ҚР ҰҒА академигі **М.Ж. Жұрынов**

Р е д а к ц и я а л қ а с ы:

Ағабеков В.Е. проф., академик (Белорус)
Волков С.В. проф., академик (Украина)
Воротынцев М.А. проф., академик (Ресей)
Газалиев А.М. проф., академик (Қазақстан)
Ергожин Е.Е. проф., академик (Қазақстан)
Жармағамбетова А.К. проф. (Қазақстан), бас ред. орынбасары
Жоробекова Ш.Ж. проф., академик (Қырғыстан)
Иткулова Ш.С. проф. (Қазақстан)
Манташян А.А. проф., академик (Армения)
Пралиев К.Д. проф., академик (Қазақстан)
Баешов А.Б. проф., академик (Қазақстан)
Бүркітбаев М.М. проф., академик (Қазақстан)
Джусипбеков У.Ж. проф. корр.-мүшесі (Қазақстан)
Молдахметов М.З. проф., академик (Қазақстан)
Мансуров З.А. проф. (Қазақстан)
Наурызбаев М.К. проф. (Қазақстан)
Рудик В. проф., академик (Молдова)
Рахимов К.Д. проф. академик (Қазақстан)
Стрельцов Е. проф. (Белорус)
Тәшімов Л.Т. проф., академик (Қазақстан)
Тодераш И. проф., академик (Молдова)
Халиков Д.Х. проф., академик (Тәжікстан)
Фарзалиев В. проф., академик (Әзірбайжан)

«ҚР ҰҒА Хабарлары. Химия және технология сериясы».

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Меншіктенуші: «Қазақстан Республикасының Ұлттық ғылым академиясы» Республикалық қоғамдық бірлестігі (Алматы қ.)

Қазақстан республикасының Мәдениет пен ақпарат министрлігінің Ақпарат және мұрағат комитетінде 30.04.2010 ж. берілген №1089-Ж мерзімдік басылым тіркеуіне қойылу туралы куәлік

Мерзімділігі: жылына 6 рет.

Тиражы: 300 дана.

Редакцияның мекенжайы: 050010, Алматы қ., Шевченко көш., 28, 219 бөл., 220, тел.: 272-13-19, 272-13-18,
<http://chemistry-technology.kz/index.php/en/arithiv>

© Қазақстан Республикасының Ұлттық ғылым академиясы, 2019

Типографияның мекенжайы: «Аруна» ЖК, Алматы қ., Муратбаева көш., 75.

Главный редактор
д.х.н., проф., академик НАН РК **М. Ж. Журинов**

Редакционная коллегия:

Агабеков В.Е. проф., академик (Беларусь)
Волков С.В. проф., академик (Украина)
Воротынцев М.А. проф., академик (Россия)
Газалиев А.М. проф., академик (Казахстан)
Ергожин Е.Е. проф., академик (Казахстан)
Жармагамбетова А.К. проф. (Казахстан), зам. гл. ред.
Жоробекова Ш.Ж. проф., академик (Кыргызстан)
Иткулова Ш.С. проф. (Казахстан)
Манташян А.А. проф., академик (Армения)
Пралиев К.Д. проф., академик (Казахстан)
Баешов А.Б. проф., академик (Казахстан)
Буркитбаев М.М. проф., академик (Казахстан)
Джусипбеков У.Ж. проф. чл.-корр. (Казахстан)
Мулдахметов М.З. проф., академик (Казахстан)
Мансуров З.А. проф. (Казахстан)
Наурызбаев М.К. проф. (Казахстан)
Рудик В. проф., академик (Молдова)
Рахимов К.Д. проф. академик (Казахстан)
Стрельцов Е. проф. (Беларусь)
Ташимов Л.Т. проф., академик (Казахстан)
Тодераш И. проф., академик (Молдова)
Халиков Д.Х. проф., академик (Гаджикистан)
Фарзалиев В. проф., академик (Азербайджан)

«Известия НАН РК. Серия химии и технологии».

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Собственник: Республиканское общественное объединение «Национальная академия наук Республики Казахстан» (г. Алматы)

Свидетельство о постановке на учет периодического печатного издания в Комитете информации и архивов Министерства культуры и информации Республики Казахстан №10893-Ж, выданное 30.04.2010 г.

Периодичность: 6 раз в год

Тираж: 300 экземпляров

Адрес редакции: 050010, г. Алматы, ул. Шевченко, 28, ком. 219, 220, тел. 272-13-19, 272-13-18,
<http://chemistry-technology.kz/index.php/en/arhiv>

© Национальная академия наук Республики Казахстан, 2019

Адрес редакции: 050100, г. Алматы, ул. Кунаева, 142,
Институт органического катализа и электрохимии им. Д. В. Сокольского,
каб. 310, тел. 291-62-80, факс 291-57-22, e-mail:orgcat@nursat.kz

Адрес типографии: ИП «Аруна», г. Алматы, ул. Муратбаева, 75

E d i t o r i n c h i e f

doctor of chemistry, professor, academician of NAS RK **M.Zh. Zhurinov**

E d i t o r i a l b o a r d :

Agabekov V.Ye. prof., academician (Belarus)
Volkov S.V. prof., academician (Ukraine)
Vorotyntsev M.A. prof., academician (Russia)
Gazaliyev A.M. prof., academician (Kazakhstan)
Yergozhin Ye.Ye. prof., academician (Kazakhstan)
Zharmagambetova A.K. prof. (Kazakhstan), deputy editor in chief
Zhorobekova Sh.Zh. prof., academician (Kyrgyzstan)
Itkulova Sh.S. prof. (Kazakhstan)
Mantashyan A.A. prof., academician (Armenia)
Praliyev K.D. prof., academician (Kazakhstan)
Bayeshov A.B. prof., academician (Kazakhstan)
Burkitbayev M.M. prof., academician (Kazakhstan)
Dzhusipbekov U.Zh. prof., corr. member (Kazakhstan)
Muldakhmetov M.Z. prof., academician (Kazakhstan)
Mansurov Z.A. prof. (Kazakhstan)
Nauryzbayev M.K. prof. (Kazakhstan)
Rudik V. prof., academician (Moldova)
Rakhimov K.D. prof., academician (Kazakhstan)
Streltsov Ye. prof. (Belarus)
Tashimov L.T. prof., academician (Kazakhstan)
Toderash I. prof., academician (Moldova)
Khalikov D.Kh. prof., academician (Tadjikistan)
Farzaliyev V. prof., academician (Azerbaijan)

News of the National Academy of Sciences of the Republic of Kazakhstan. Series of chemistry and technology.
ISSN 2518-1491 (Online),
ISSN 2224-5286 (Print)

Owner: RPA "National Academy of Sciences of the Republic of Kazakhstan" (Almaty)

The certificate of registration of a periodic printed publication in the Committee of Information and Archives of the Ministry of Culture and Information of the Republic of Kazakhstan N 10893-Ж, issued 30.04.2010

Periodicity: 6 times a year

Circulation: 300 copies

Editorial address: 28, Shevchenko str., of. 219, 220, Almaty, 050010, tel. 272-13-19, 272-13-18,

<http://chemistry-technology.kz/index.php/en/arhiv>

© National Academy of Sciences of the Republic of Kazakhstan, 2019

Editorial address: Institute of Organic Catalysis and Electrochemistry named after D. V. Sokolsky
142, Kunayev str., of. 310, Almaty, 050100, tel. 291-62-80, fax 291-57-22,
e-mail: orgcat@nursat.kz

Address of printing house: ST "Aruna", 75, Muratbayev str, Almaty

NEWS

OF THE NATIONAL ACADEMY OF SCIENCES OF THE REPUBLIC OF KAZAKHSTAN

SERIES CHEMISTRY AND TECHNOLOGY

ISSN 2224-5286

<https://doi.org/10.32014/2019.2518-1491.46>

Volume 4, Number 436 (2019), 74 – 80

UDC 542.946.7; 543.272.75

**A.T. Massenova, M.K. Kalykberdiyev, A.S. Sass,
N.R. Kenzin, A.Z. Abilmagzhanov, A. Baiken**

JSC "Institute of Fuel, Catalysis and Electrochemistry after D.V. Sokolsky", Almaty, Kazakhstan

almasenova@mail.ru

CATALYTIC TECHNOLOGY FOR REDUCING THE CONTENT OF AROMATIC HYDROCARBONS IN MOTOR FUELS

Abstract. The aim of the work was to study the process of hydrodearomatization of diesel fractions for the production of environmentally friendly fuels with a low content of aromatic hydrocarbons. The hydrogenation of two diesel fractions 180-350°C and 230-360°C of PKOP LLP (PetroKazakhstanOilProducts, Shymkent) has been studied. Rh-Pt/Al₂O₃ catalysts were used in the work. The influence of the technological parameters of the process of hydrodearomatization (hydrogen pressure 2-6 MPa, temperature 100-220°C) on the reaction rate, conversion and aromatic hydrocarbon content at the "aniline point" was investigated. To increase stability and resistance to poisoning with sulfur-containing compounds of petroleum fractions, the carrier was modified with chromium oxide and synthetic zeolite ZSM-5, which led to an increase in the reaction rate and conversion of aromatic hydrocarbons. Optimal conditions have been selected (temperatures 200-220°C, hydrogen pressure 4-6 MPa, solvent - ethanol, propanol, isopropanol) for hydrogenation of diesel fractions 180-350°C and 230-360°C on Pt-Rh-catalysts supported on alumina and mixed carriers. The content of aromatic hydrocarbons was reduced by 10-20%. Some operational properties of diesel fuel (kinematic viscosity at 20°C, pour point and cloud point and density at 20°C) of the initial diesel fractions and after catalytic treatment were determined, the effect of temperature and pressure on the change in these characteristics was investigated.

Keywords: catalyst, hydrogenation, hydrodearomatization, aromatic hydrocarbons, diesel fraction.

Introduction

The constantly deteriorating of environmental situation in the world dictates the need for use of clean and quality fuel. Harmful compounds (carcinogens, in particular benzyrene) are formed upon incomplete combustion of benzene and aromatic hydrocarbons. Aromatic hydrocarbons promote coking in the engine combustion system, which increases the NO_x content in exhaust gases. For diesel fuels, the high content of polycyclic aromatic hydrocarbons reduces their cetane index; a lot of soot (black smoke) is contained in exhausts at combustion. The limiting value of aromatic hydrocarbons content according to the new EURO-5.6 specifications is less than 30%, benzene is less than 0.1%. One of the methods for improving the composition of fuels is their hydrodearomatization; olefins also hydrogenate at the same time, which reduce the stability of fuel as a result of their polymerization [1-6].

Development and introduction of the technology of hydrodearomatization of fuels and fuel fractions are relevant for the Republic, taking into account the high content of benzene (up to 5-7%) and aromatic hydrocarbons (up to 40-50%) in gasolines and diesel fuels, as the environmental situation in some regions raises concerns. The technological line for the proposed project is simple and the process can be carried out on the lines of oil hydrotreating at any refinery in Kazakhstan. The process technology is one-step and low-waste. Hydrodearomatization of fuels will help improve the performance properties of domestic gasolines, diesel fuels and will allow in a short time to cover the need for fuels with improved performance characteristics.

Many countries: Russia, United States, Great Britain, France, Germany, Japan, China, Poland, etc. are engaged in the problem of hydrodearomatizing of fuels [7-19]. Major trends in this field consist in

reducing the cost of catalyst (reduction of the noble metal content, selection of carriers and modifiers), increase stability and resistance to sulfur-containing compounds. In industry catalysts based on noble metals and sulfides are used, but in the latter, the process is carried out under more stringent conditions.

Recently Pt-Pd-catalysts have been intensively used for hydrotreatment of petroleum products, especially for reducing the content of benzene in gasolines and aromatics in diesel fuels, therefore, close attention of researchers has been riveted on them. The addition of Pd to Pt/Al₂O₃ leads to an increase in not only the activity, but also the stability in the hydrogenation of benzene. By varying the nature of the carrier and modifier the Pd catalysts with the addition of a second metal such as Cu, Ru or Pt a uniform distribution of metals in the pores, optimal acidity and stability against sulfur-containing compounds were achieved. Thus, in the literature of recent years on catalysis there has been considerable interest to the process of hydrogenation of aromatics, which is largely due to the practical use in the production of environmentally friendly fuels.

At present, Kazakhstan's refineries produce rather low-quality motor fuels, which are far from international standards. In addition to harmful emissions into the atmosphere, rapid deterioration of the details of equipment occurs due to the deposition of carbon during the combustion of such fuels. The service life of equipment is reduced by 30%.

In previous works [15-20] we investigated the catalytic hydrogenation of aromatic hydrocarbons and developed catalysts and technological regimes for the process of hydrodearomatization (removal of benzene and reduction of polyaromatic hydrocarbons) of gasoline fractions of ANPZ LLP (Atyrau Oil Refinery). Advantages of the these catalysts are a high conversion of benzene 99.5%, reduction of aromatic hydrocarbons content to 25%, high stability to poisoning with sulfur-containing compounds. The purpose of this work is the catalytic hydrogenation of polyaromatic hydrocarbons in diesel fractions of PKOP LLP (PetroKazakhstanOilProducts, Shymkent).

Experimental part

Bimetallic modified catalysts based on Group 8 metals (Pt and Rh) on aluminum oxide were prepared for hydrodearomatization of diesel fractions of PKOP LLP (Shymkent) - 180-350°C and 230-360°C with aromatics content of 30 and 39%, respectively.

At preparation of catalysts RhCl₃·3H₂O, H₂PtCl₆·6H₂O of "chemically pure" mark were used. Solutions of these compounds were applied by the adsorption method on the prepared carrier Al₂O₃. A mixture of aqueous solutions of two metals was applied at preparation of bimetallic catalysts. The catalyst samples were filtered off and dried at 100-110°C to constant weight. The reduction of supported catalysts was carried out in a quartz tube with electrical heating in a hydrogen stream at 200°C for 4 hours, then the catalysts were cooled in a hydrogen stream until room temperature.

The experiment was carried out on a kinetic installation - the autoclave of "Amar Equipment Ltd" in the isobaric-isothermal regime.

The "aniline point" method was used to determine the total content of aromatic hydrocarbons.

Results and discussion

Hydrodearomatization of diesel fractions of 180-350°C and 230-360°C was carried out on the prepared catalysts and the technological parameters (temperature and hydrogen pressure) were tested. The effect of temperature in the range of 100-200°C on the rate, duration of hydrogenation, and the content of aromatic hydrocarbons was studied.

Table 1 shows the data on the hydrogenation of the diesel fraction of oil 180-350°C. With increasing of temperature, the rate increases from 8.2 to 12.3 ml/min, the duration of the process decreases from 180 to 130 minutes. The aniline point increases from approximately <44 to <54. This indicates a decrease in the content of aromatic hydrocarbons by approximately 18% (the initial content of aromatic hydrocarbons is approximately 30%).

The effect of hydrogen pressure was studied in the range of 2.0-4.0 MPa. The change in reaction rate and duration at these pressure values is similar to the effect of temperature: the reaction rate increases from 8.2 to 10.1 ml/min, and the duration of the process decreases from 180 to 150 minutes (Table 1). The content of aromatic hydrocarbons is reduced by 15% as measured by the aniline point, which increases from <44 to <53.

Table 1 - Hydrogenation of the diesel oil fraction: 180-350°C on Pt-Rh/Al₂O₃ catalyst

Conditions	Rate, ml/min	Duration, min	Aniline point	
			before	after
100°C	8.2	180	<44	<51
120°C	9.0	169	<44	<52
140°C	9.8	156	<44	<53
160°C	10.2	149	<44	<54
180°C	11.0	139	<44	<54
200°C	12.3	130	<44	<55
2 MPa	8.2	180	<44	<51
3 MPa	9.1	165	<44	<52
4 MPa	10.1	150	<44	<53
ethanol	8.6	170	<44	<54
propanol	7.8	195	<44	<51
isopropanol	8.2	180	<44	<51

Ethanol, propanol, and isopropanol were used as solvents. According to the reaction rate and duration of the process, ethanol is the best solvent. These solvents by reaction rate are arranged in a row: ethanol > isopropanol > propanol.

And accordingly the speed values in this row are reduced from 8.6 to 7.8 ml/min, and the duration of the process is antipate increased from 170 to 195 minutes (Table 1). For all values of temperature, hydrogen pressure and solvent type, the rate of hydrogenation of the diesel fraction 180-350°C is greater than the fraction 230-360°C.

Pt-Rh/Al₂O₃ catalyst showed low activity for diesel fractions, which is associated with poisoning with sulfur-containing compounds (0.02%) contained in the fuel. Therefore, to increase its activity, the catalyst was modified in two ways: by introducing chromium oxide and zeolite ZSM-5. Chromium oxide increases resistance to poisoning by sulfur, and zeolite affects the formation of active surface phases, providing a sufficiently high concentration of strong proton donor and electron acceptor centers, thereby increasing the catalytic activity.

When hydrogenating diesel fuel with an aromatic content of 30-39% on catalysts modified by chromium oxide and zeolite, the reaction rate is higher than on an unmodified catalyst, the duration of the process is reduced. Conversion increases and is 10-13% (table 2). The content of aromatic hydrocarbons was determined by measuring aniline point. On modified catalysts, the aniline point after the reaction is <55, which indicates a decrease in the aromatic content. By all indications, a catalyst modified with zeolite is more active than unmodified and modified chromium oxide.

Table 2 - Hydrogenation of two diesel fractions on various catalysts

Catalyst	Type of fraction	Content of aromatics, %	Rate, ml/min	Conversion, %	Duration, min	Aniline point	
						before	after
Pt-Rh/ Al ₂ O ₃	Diesel fraction 180-350°C	30	0.01	9	> 360	<44	<54
	Diesel fraction 230-360°C	39	0.01	8	> 480	<42	<53
Pt-Rh/ Al ₂ O ₃ + Cr ₂ O ₃	Diesel fraction 180-350°C	30	0.05	10	280	<44	<55
	Diesel fraction 230-360°C	39	0.06	10	270	<42	<55
Pt-Rh/ Al ₂ O ₃ + ZSM-5	Diesel fraction 180-350°C	30	0.07	13	210	<44	<56
	Diesel fraction 230-360°C	39	0.08	12	200	<42	<56

For the same process the parameters of the regime (temperature and hydrogen pressure) were tested for some performance properties of diesel fuel, such as viscosity at 20°C, pour point and cloud point, and density at 20°C (Table 3). Table 3 shows the sample data for the Pt-Rh/Al₂O₃ catalyst.

In Table 3 the data of the initial diesel fuel before and after the catalytic treatment with the change of hydrogen pressure from 2 to 6 MPa and temperature from 180-220°C are presented. The characteristics presented are important operational parameters and are measured under laboratory conditions. The kinematic viscosity of the resulting product decreases from 3.15 to 2.86 mm²/s compared to the original fuel. Density is also reduced from 0.833 to 0.823 g/cm³. The cloud point decreases from -19 to -27°C, and the pour point from -22 to -29°C.

Table 3 - Effect of hydrogen pressure and temperature on the properties of diesel fuel

Conditions	Density at 20°C, g/cm ³	cloud point, °C	pour point, °C	Kinematic viscosity at 20°C, mm ² /s
Before treatment	0.833	-19	-22	3.15
2 MPa	0.830	-21	-25	3.00
4 MPa	0.829	-24	-27	2.98
6 MPa	0.823	-25	-28	2.86
180°C	0.830	-21	-25	3.00
200°C	0.828	-25	-27	2.72
220°C	0.825	-27	-29	2.70

Table 4 shows some of the performance properties (physico-chemical indicators) of diesel fuel in the process of hydrogenation on three catalysts: Pt-Rh/Al₂O₃, Pt-Rh/Al₂O₃+Cr₂O₃ и Pt-Rh/Al₂O₃+ZSM-5.

Table 4 – Physico-chemical indicators of diesel fuel in the process of hydrogenation

Conditions	Density at 20°C, g/cm ³	cloud point, °C	pour point, °C	Kinematic viscosity at 20°C, mm ² /s	Aniline point
Before treatment	0.833	-19	-22	3.15	<44
Pt-Rh/ Al ₂ O ₃	0.830	-21	-25	3.00	<54
Pt-Rh/Al ₂ O ₃ +Cr ₂ O ₃	0.829	-24	-27	2.98	<55
Pt-Rh/Al ₂ O ₃ +ZSM-5	0.823	-25	-28	2.86	<56

After treatment on developed catalysts, the fuel density decreases from 0.833 to 0.823. The cloud point and pour point are reduced, respectively, from -19 to -25 and from -22 to -28°C. Viscosity also decreases from 3.15 to 2.86 mm²/s. The content of aromatic hydrocarbons, measured by the aniline point method, decreases from <44 to <56. The best results were shown by the Pt-Rh/Al₂O₃ + ZSM-5 catalyst, which had the lowest cloud point -28°C, pour point -28°C, viscosity 2.86 mm²/s, as well as the content of aromatic hydrocarbons - aniline point <56.

Thus, the advantage of the prepared catalysts is in reduction the concentration of polycyclic aromatic hydrocarbons (PAHs) by 10–20% in diesel oil fractions. Diesel fuels obtained after hydrodearomatization have a lower cloud point and pour temperature, as well as kinematic viscosity. The catalysts have a high stability to poisoning with sulfur-containing compounds, which is especially important for diesel fuels in Kazakhstan.

The technology of hydrodearomatization of diesel fuels is applicable to the production of environmentally friendly fuels with a low content of aromatic hydrocarbons, has low energy consumption and high environmental friendliness. Reducing the amount of aromatic hydrocarbons in automotive fuels will reduce the amount of gaseous emissions and extend the service life of cars by 1/3, which will also bring an economic effect.

Conclusions

The process of hydrodearomatization of two diesel fractions of PKOP LLP (PetroKazakhstanOilProducts, Shymkent) of 180-350°C and 230-360°C on the prepared Rh-Pt/Al₂O₃ catalysts was investigated. The influence of the technological parameters of the process of hydrodearomatization (hydrogen pressure 2-6 MPa, temperature 100-220°C) on the reaction rate, conversion and aromatic hydrocarbon content at the “aniline point” was investigated.

To increase stability and resistance to poisoning with sulfur-containing compounds of petroleum fractions, the carrier was modified with chromium oxide and synthetic zeolite ZSM-5, which led to an increase in the reaction rate and conversion of aromatic hydrocarbons.

Optimum conditions have been selected (temperatures 200-220°C, hydrogen pressure 4-6 MPa, solvent - ethanol, propanol, isopropanol) for hydrogenation of diesel fractions: 180-350°C and 230-360°C on Pt-Rh-catalysts supported on alumina and mixed carriers. Some operational properties of diesel fuel (kinematic viscosity at 20°C, pour point and cloud point and density at 20°C) of the initial diesel fractions and after catalytic treatment were determined, the effect of temperature and pressure on the change in these characteristics was investigated.

In the presence of developed catalysts, the fuel density decreases from 0.833 to 0.823, cloud point and pour point decrease, respectively, from -19 to -25 and from -22 to -28°C, viscosity also decreases from 3.15 to 2.86 mm²/s. The content of aromatic hydrocarbons is reduced by 10-20%. The best results were shown by the Pt-Rh/Al₂O₃+ZSM-5 catalyst, which had the lowest cloud point of -28°C, solidification of -28°C, viscosity 2.86 mm²/s, as well as the content of aromatic hydrocarbons - aniline point <56.

Acknowledgments

This work was supported by grant No. BR05236739 of the Ministry of Education and Science of the Republic of Kazakhstan.

ӘӨЖ542.946.7; 543.272.75

**А.Т. Масенова, М.К. Калыкбердиев, А.С. Сасс,
Н.Р. Кензин, А.З. Абильмагжанов, А. Байкен**

«Д.В. Сокольский атындағы жаңармай, катализ және электрохимия институты» АҚ, Алматы, Қазақстан;

МОТОР ЖАНАРМАЙЛАРЫНДА АРОМАТТЫ КӨМІРСУТЕКТЕРДІҢ ҚҰРАМЫН АЗАЙТУДЫҢ КАТАЛИЗДІК ТЕХНОЛОГИЯСЫ

Аннотация. Жұмыстың мақсаты ароматты көмірсутектердің аз мөлшері бар экологиялық таза жанармайды өндіруге арналған дизель фракцияларын гидродеароматизациялау процесін зерттеу болып табылады. «ПКОП» ЖШС-нің (PetroKazakhstanOil Products, Шымкент) екі дизельдік фракциясының гидрогенизациясы 180-350°C және 230-360°C-та зерттелген. Жұмыста Rh-Pt/Al₂O₃ катализаторы қолданылды. Реакция жылдамдығына, гидрероматизация процесінің технологиялық параметрлері (қысым 2-6 МПа, температура 100-220°C), «анилин нүктесінде» конверсия және ароматты көмірсутектердің құрамының әсері зерттелді. Мұнай фракцияларының құрамында күкірті бар қосындылармен улануы тұрақтылығы мен жалпы тұрақтылығын арттыру үшін тасымалдағыш хром оксидімен және ZSM-5 синтетикалық цеолитімен модификацияланды, бұл ароматты көмірсутектердің реакциясы мен конверсиясының жылдамдығын арттыруға әкелді. Алюминий оксидіне және аралас тасымалдағыштарға отырғызылған Pt-Rh-катализаторларында дизельді фракцияларды гидрирлеу үшін оңтайлы жағдайлар (температурасы 200-220°C, сутегі қысымы 4-6 МПа, еріткіш - этанол, пропанол, изoproпанол) іріктелді. Ароматты көмірсутектердің құрамы 10-20% төмендейді. Дизель отынының кейбір пайдалану қасиеттері анықталды (20°C кезіндегі кинематикалық тұтқырлығы, қату және тұндыру температурасы және 20°C кезіндегі тығыздығы) және катализдік өндеуден кейін, температура мен қысымның осы сипаттамалардың өзгеруіне әсері зерттелді.

Түйін сөздер: катализатор, гидрирлеу, гидродеароматизация, ароматты көмірсутектер, дизельді фракция.

**А.Т. Масенова, М.К. Калыкбердиев, А.С. Сасс,
Н.Р. Кензин, А.З. Абилмагжанов, А. Байкен**

АО «Институт топлива, катализа и электрохимии им.Д.В.Сокольского», Алматы, Казахстан

КАТАЛИТИЧЕСКАЯ ТЕХНОЛОГИЯ СНИЖЕНИЯ СОДЕРЖАНИЯ АРОМАТИЧЕСКИХ УГЛЕВОДОРОДОВ В МОТОРНЫХ ТОПЛИВАХ

Аннотация. Целью работы являлось изучение процесса гидродеароматизации дизельных фракций для производства экологически чистых топлив низким содержанием ароматических углеводородов. Изучено гидрирование двух дизельных фракций ТОО ПКООП («ПетроКазахстанОйлПродактс», г. Шымкент) 180-350°C и 230-360°C. В работе использовался Rh-Pt/Al₂O₃ катализатор. Исследовалось влияние технологических параметров процесса гидродеароматизации (давление 2-6 МПа, температура 100-220°C) на скорость реакции, конверсию и содержание ароматических углеводородов по «анилиновой точке». Для повышения стабильности и устойчивости к отравлению серусодержащими соединениями нефтяных фракций носитель модифицировали оксидом хрома и синтетическим цеолитом ZSM-5, что привело к повышению скорости реакции и конверсии ароматических углеводородов. Осуществлен подбор оптимальных условий (температуры 200-220°C, давление водорода 4-6 МПа, растворитель - этанол, пропанол, изопропанол) для гидрирования дизельных фракций: 180-350°C и 230-360°C на катализаторах Pt-Rh, нанесенных на оксид алюминия и смешанные носители. Содержание ароматических углеводородов снижается на 10-20%. Определены некоторые эксплуатационные свойства дизельного топлива (кинематическая вязкость при 20°C, температуры застывания и помутнения и плотность при 20°C) исходных дизельных фракций и после каталитической обработки, исследовано влияние температуры и давления на изменение этих характеристик.

Ключевые слова: катализатор, гидрирование, гидродеароматизация, ароматические углеводороды, дизельная фракция.

Information about authors:

Massenova Alma Tulegenovna - Doctor of Chemical Sciences, associate professor, Head of the sector of Catalytic Synthesis after F. Bizhanov of JSC "Institute of Fuel, Catalysis and Electrochemistry after D.V. Sokolsky", Almaty, Kazakhstan. Tel:+7772681552, almasenova@mail.ru, ORCID 0000-0003-2251-0549

Kalykberdiyev Maksat Kuvatovich - Junior Researcher of sector of Catalytic Synthesis after F. Bizhanov of JSC "Institute of Fuel, Catalysis and Electrochemistry after D.V. Sokolsky", Almaty, Kazakhstan. Tel:+77071358090, mkalykberdiyev@mail.ru, ORCID 0000-0002-4309-441X

Sass Alexander Sergeevich - Candidate of Chemical Sciences, Senior Researcher of sector of Catalytic Synthesis after F. Bizhanov of JSC "Institute of Fuel, Catalysis and Electrochemistry after D.V. Sokolsky", Almaty, Kazakhstan. Tel:+77073906177, aleksandr-sass@mail.ru, ORCID 0000-0003-4049-6314

Kenzin Nail Rashidovich - Researcher of sector of Catalytic Synthesis after F. Bizhanov of JSC "Institute of Fuel, Catalysis and Electrochemistry after D.V. Sokolsky", Almaty, Kazakhstan. Tel:+77082764697, nailkenz@gmail.com, ORCID 0000-0001-8323-4619

Abilmagzhanov Arlan Zainutallaevich - Candidate of Chemical Sciences, Deputy General Director of JSC "Institute of Fuel, Catalysis and Electrochemistry after D.V. Sokolsky", Almaty, Kazakhstan. Tel:+77778028720, a.abilmagzhanov@ifce.kz, ORCID 0000-0001-8355-8031

[Baiken Amankeldi](mailto:amankeldibaiken@gmail.com) - Doctoral student of KBTU, Almaty, Kazakhstan. Tel:+77787272944, amankeldibaiken@gmail.com, ORCID 0000-0003-36884023

REFERENCES

- [1] Grebennikov M. (2008) Jekologicheskaja jama. Business Week, Rossija. N001, 4.1.(In Russian).
- [2] Karpov SA (2007) Neftepererabotka I neftehimija, 1:16-19. ISSN 0233-5727 (In Russian).
- [3] Ashrafov RA (2012) Sovremennaj anauka: Aktual'nyeproblemyteoriiipraktiki".Serija «Estestvennye i tehniczeskie nauki», 1:56-61. ISSN – 2223-2966 (In Russian).
- [4] Mirimanjan AA, Vihman AG, Mkrtychev AA, Maryshev VB, Boruckij PN, Mozhajko VN. (2006) Neftepererabotka i neftehimija, 8:11-14. ISSN 0233-5727 (In Russian).
- [5] Abu Bakar N.H.H., Bettahar M.M., Abu Bakar M., Monteverdi S., Ismail J., Alnot M. PtNi catalysts prepared via borohydride reduction for hydrogenation of benzene// J. Catal., 2009, V.265, № 1, P. 63-71. DOI:10.1016/j.jcat.2009.04.011 (In Eng.).
- [6] Corma A, Gonzales-Alfaro V, Orchilles AV (2001) J.Catal., 200:34-44. DOI: [10.1006/jcat.2001.3181](https://doi.org/10.1006/jcat.2001.3181) (In Eng.).
- [7] Michalska K, Kowalik P, Konkol M, Próchniak W, Stolecki K, Słowik G, Borowiecki T (2016) App.Cat. A: General, 523:54-60. <http://dx.doi.org/10.1016/j.apcata.2016.05.016> (in Eng).

- [8] Chen H, Yang H, Omotoso O, Ding L, Briker Y, Zheng Y, Ring Z(2009)Appl.Catal.A: General, 358:103-109. <https://doi.org/10.1016/j.apcata.2008.12.045> (In Eng.).
- [9] Wu Y, Li J, Chai Y, Guo H, Liu C (2015) J. Membrane Sci.469: 70-77. <https://doi.org/10.1016/j.memsci.2015.08.048>Get rights and content (in Eng).
- [10] Yue XM, Wei XY, Zhang ZQ, Liu FJ, Zong ZM, YangXO (2017) Fuel Proces.Technology 161:283-288. <https://doi.org/10.1016/j.fuproc.2017.03.006>Get rights and content (In Eng.).
- [11] Simon LJ, van Ommen JG, Jentys A, Lercher(2002) Catal.Today, 73:105-112. DOI: [10.1016/S0920-5861\(01\)00502-8](https://doi.org/10.1016/S0920-5861(01)00502-8) (In Eng.).
- [12] Vangelis C, Bouriazos A, Sotiriou S, Samorski M, Gutsche B, Papadogianakis G (2010) J. Catal., 274:21-28. DOI: [10.1016/j.jcat.2010.06.004](https://doi.org/10.1016/j.jcat.2010.06.004) (In Eng.).
- [13] Pushkarev VV, Kwangjin A, Alayoglu S, Beaumont SK, Somorjai GA (2012) J.Catal., 292:64-72. <https://doi.org/10.1016/j.jcat.2012.04.022> (In Eng.).
- [14] Yu Y, Gutiérrez OY, Haller GL, Colby R, Kabius B, van Veen JAR, Jentys^a A, Lercher JA (2013) J.Cat. 304:135-148. <https://doi.org/10.1016/j.jcat.2013.04.009>Get rights and content (in Eng).
- [15] Massenova AT, Frolova OA, Sassykova LR, BashevaZhT, BaytazinE, Ussenov A (2014) Int. J. Chem. Sci.12: 625-634. DOI.org/10.22271/chemical. (In Eng.).
- [16] Sassykova LR, Massenova AT, Basheva ZhT, Abilmagzhanov A.Z, Kalykberdyev MK, Rakhmetova KS, Frolova OA, Ussenov A (2014) News National academy of sci. Kazakhstan, Series chemistry and technology 4:50-53. ISSN-2224-5286 (In Russian).
- [17] Sassykova LR, Basheva ZhT, Kalykberdyev MK, Nurakhmetova M, Massenova AT, Zhumabai NA, Rakhmetova KS (2016) News National academy of sci. Kazakhstan, Series chemistry and technology 1:64-72. ISSN-2224-5286 (In Russian).
- [18] Sassykova LR, Basheva ZhT, Kalykberdyev MK, Nurakhmetova M, Massenova AT, Rakhmetova KS (2018) Bulgar.Chem.Comm., 50:82-88. ISSN 0324-1130 (in Eng).
- [19] Massenova AT, Kalykberdiyev MK, Sass AS, Kenzin NR, Kanatbayev ET, Tsygankov VP (2018) News National academy of sci.Kazakhstan, Series chemistry and technology, 5:146–153. <https://doi.org/10.32014/2018.2518-1491.19> (in Eng)
- [20] Massenova A, Kalykberdiyev M, Ussenov A, Sass A, Kenzin N, Kanatbayev T, Baiken A (2019) Oriental J.Chem., 35:351-357. DOI: <http://dx.doi.org/10.13005/ojc/350143> (in Eng).

Publication Ethics and Publication Malpractice in the journals of the National Academy of Sciences of the Republic of Kazakhstan

For information on Ethics in publishing and Ethical guidelines for journal publication see <http://www.elsevier.com/publishingethics> and <http://www.elsevier.com/journal-authors/ethics>.

Submission of an article to the National Academy of Sciences of the Republic of Kazakhstan implies that the described work has not been published previously (except in the form of an abstract or as part of a published lecture or academic thesis or as an electronic preprint, see <http://www.elsevier.com/postingpolicy>), that it is not under consideration for publication elsewhere, that its publication is approved by all authors and tacitly or explicitly by the responsible authorities where the work was carried out, and that, if accepted, it will not be published elsewhere in the same form, in English or in any other language, including electronically without the written consent of the copyright-holder. In particular, translations into English of papers already published in another language are not accepted.

No other forms of scientific misconduct are allowed, such as plagiarism, falsification, fraudulent data, incorrect interpretation of other works, incorrect citations, etc. The National Academy of Sciences of the Republic of Kazakhstan follows the Code of Conduct of the Committee on Publication Ethics (COPE), and follows the COPE Flowcharts for Resolving Cases of Suspected Misconduct (http://publicationethics.org/files/u2/New_Code.pdf). To verify originality, your article may be checked by the Cross Check originality detection service <http://www.elsevier.com/editors/plagdetect>.

The authors are obliged to participate in peer review process and be ready to provide corrections, clarifications, retractions and apologies when needed. All authors of a paper should have significantly contributed to the research.

The reviewers should provide objective judgments and should point out relevant published works which are not yet cited. Reviewed articles should be treated confidentially. The reviewers will be chosen in such a way that there is no conflict of interests with respect to the research, the authors and/or the research funders.

The editors have complete responsibility and authority to reject or accept a paper, and they will only accept a paper when reasonably certain. They will preserve anonymity of reviewers and promote publication of corrections, clarifications, retractions and apologies when needed. The acceptance of a paper automatically implies the copyright transfer to the National Academy of Sciences of the Republic of Kazakhstan.

The Editorial Board of the National Academy of Sciences of the Republic of Kazakhstan will monitor and safeguard publishing ethics.

Правила оформления статьи для публикации
в журнале смотреть на сайте:

www.nauka-nanrk.kz

<http://chemistry-technology.kz/index.php/en/arhiv>

ISSN 2518-1491 (Online), ISSN 2224-5286 (Print)

Редакторы: *М. С. Ахметова, Т. А. Апендиев, Аленов Д. С.*
Верстка на компьютере *А. М. Кульгинбаевой*

Подписано в печать 05.08.2019.
Формат 60x881/8. Бумага офсетная. Печать – ризограф.
5,25 п.л. Тираж 300. Заказ 4.