

ISSN 2518-1491 (Online),
ISSN 2224-5286 (Print)

ҚАЗАҚСТАН РЕСПУБЛИКАСЫ
ҰЛТТЫҚ ҒЫЛЫМ АКАДЕМИЯСЫНЫҢ

Д.В. Сокольский атындағы «Жанармай,
катализ және электрохимия институты» АҚ

Х А Б А Р Л А Р Ы

ИЗВЕСТИЯ

НАЦИОНАЛЬНОЙ АКАДЕМИИ НАУК
РЕСПУБЛИКИ КАЗАХСТАН
АО «Институт топлива, катализа и
электрохимии им. Д.В. Сокольского»

NEWS

OF THE ACADEMY OF SCIENCES
OF THE REPUBLIC OF KAZAKHSTAN
JSC «D.V. Sokolsky institute of fuel, catalysis
and electrochemistry»

SERIES
CHEMISTRY AND TECHNOLOGY

2 (446)

MARCH – APRIL 2021

PUBLISHED SINCE JANUARY 1947

PUBLISHED 6 TIMES A YEAR

ALMATY, NAS RK

NAS RK is pleased to announce that News of NAS RK. Series of chemistry and technologies scientific journal has been accepted for indexing in the Emerging Sources Citation Index, a new edition of Web of Science. Content in this index is under consideration by Clarivate Analytics to be accepted in the Science Citation Index Expanded, the Social Sciences Citation Index, and the Arts & Humanities Citation Index. The quality and depth of content Web of Science offers to researchers, authors, publishers, and institutions sets it apart from other research databases. The inclusion of News of NAS RK. Series of chemistry and technologies in the Emerging Sources Citation Index demonstrates our dedication to providing the most relevant and influential content of chemical sciences to our community.

Қазақстан Республикасы Ұлттық ғылым академиясы "ҚР ҰҒА Хабарлары. Химия және технология сериясы" ғылыми журналының Web of Science-тің жаңаланған нұсқасы Emerging Sources Citation Index-те индекстелуге қабылданғанын хабарлайды. Бұл индекстелу барысында Clarivate Analytics компаниясы журналды одан әрі the Science Citation Index Expanded, the Social Sciences Citation Index және the Arts & Humanities Citation Index-ке қабылдау мәселесін қарастыруда. Web of Science зерттеушілер, авторлар, баспашылар мен мекемелерге контент тереңдігі мен сапасын ұсынады. ҚР ҰҒА Хабарлары. Химия және технология сериясы Emerging Sources Citation Index-ке енуі біздің қоғамдастық үшін ең өзекті және беделді химиялық ғылымдар бойынша контентке адалдығымызды білдіреді.

НАН РК сообщает, что научный журнал «Известия НАН РК. Серия химии и технологий» был принят для индексирования в Emerging Sources Citation Index, обновленной версии Web of Science. Содержание в этом индексировании находится в стадии рассмотрения компанией Clarivate Analytics для дальнейшего принятия журнала в the Science Citation Index Expanded, the Social Sciences Citation Index и the Arts & Humanities Citation Index. Web of Science предлагает качество и глубину контента для исследователей, авторов, издателей и учреждений. Включение Известия НАН РК в Emerging Sources Citation Index демонстрирует нашу приверженность к наиболее актуальному и влиятельному контенту по химическим наукам для нашего сообщества.

Б а с р е д а к т о р ы
х.ғ.д., проф., ҚР ҰҒА академигі
М.Ж. Жұрынов

Р е д а к ц и я а л қ а с ы:

Ағабеков В.Е. проф., академик (Белорус)
Башов А.Б. проф., академик (Қазақстан)
Бүркітбаев М.М. проф., академик (Қазақстан)
Воротынцев М.А. проф., академик (Ресей)
Газалиев А.М. проф., академик (Қазақстан)
Жармағамбетова А.К. проф. (Қазақстан), бас ред. орынбасары
Жоробекова Ш.Ж. проф., академик (Қырғыстан)
Иткулова Ш.С. проф. (Қазақстан)
Манташян А.А. проф., академик (Армения)
Рахимов К.Д. проф., академик (Қазақстан)
Рудик В. проф., академик (Молдова)
Стрельцов Е. проф. (Белорус)
Тельтаев Б.Б. проф., академик (Қазақстан)
Тулеуов Б.И. проф., академик (Қазақстан)
Фазылов С.Д. проф., академик (Қазақстан)
Фарзалиев В. проф., академик (Әзірбайжан)
Халиков Д.Х. проф., академик (Тәжікстан)

«ҚР ҰҒА Хабарлары. Химия және технология сериясы».

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Меншіктенуші: «Қазақстан Республикасының Ұлттық ғылым академиясы» Республикалық қоғамдық бірлестігі (Алматы қ.).

Қазақстан Республикасының Ақпарат және қоғамдық даму министрлігінің Ақпарат комитетінде 29.07.2020 ж. берілген № KZ66VPY00025419 мерзімдік басылым тіркеуіне қойылу туралы куәлік.

Тақырыптық бағыты: *химия және жаңа материалдар технологиясы саласындағы басым ғылыми зерттеулерді жариялау.*

Мерзімділігі: жылына 6 рет.

Тиражы: 300 дана.

Редакцияның мекенжайы: 050010, Алматы қ., Шевченко көш., 28; 219, 220 бөл.; тел.: 272-13-19; 272-13-18,
<http://chemistry-technology.kz/index.php/en/arithiv>

© Қазақстан Республикасының Ұлттық ғылым академиясы, 2021

Редакцияның мекенжайы: 050100, Алматы қ., Қонаев к-сі, 142, «Д. В. Сокольский атындағы отын, катализ және электрохимия институты» АҚ, каб. 310, тел. 291-62-80, факс 291-57-22, e-mail:orgcat@nursat.kz

Типографияның мекенжайы: «Аруна» ЖК, Алматы қ., Муратбаева көш., 75.

Главный редактор
д.х.н., проф., академик НАН РК
М.Ж. Журинов

Редакционная коллегия:

Агабеков В.Е. проф., академик (Беларусь)
Баешов А.Б. проф., академик (Казахстан)
Буркитбаев М.М. проф., академик (Казахстан)
Воротынцев М.А. проф., академик (Россия)
Газалиев А.М. проф., академик (Казахстан)
Жармагамбетова А.К. проф. (Казахстан), зам. гл. ред.
Жоробекова Ш.Ж. проф., академик (Кыргызстан)
Иткулова Ш.С. проф. (Казахстан)
Манташян А.А. проф., академик (Армения)
Рахимов К.Д. проф., академик (Казахстан)
Рудик В. проф., академик (Молдова)
Стрельцов Е. проф. (Беларусь)
Тельтаев Б.Б. проф., академик (Казахстан)
Тулеуов Б.И. проф., академик (Казахстан)
Фазылов С.Д. проф., академик (Казахстан)
Фарзалиев В. проф., академик (Азербайджан)
Халиков Д.Х. проф., академик (Таджикистан)

«Известия НАН РК. Серия химии и технологий».

ISSN 2518-1491 (Online),
ISSN 2224-5286 (Print)

Собственник: Республиканское общественное объединение «Национальная академия наук Республики Казахстан» (г. Алматы).

Свидетельство о постановке на учет периодического печатного издания в Комитете информации Министерства информации и общественного развития Республики Казахстан № KZ66VPY00025419, выданное 29.07.2020 г.

Тематическая направленность: *публикация приоритетных научных исследований в области химии и технологий новых материалов.*

Периодичность: 6 раз в год.
Тираж: 300 экземпляров.

Адрес редакции: 050010, г. Алматы, ул. Шевченко, 28; ком. 219, 220; тел. 272-13-19; 272-13-18,
<http://chemistry-technology.kz/index.php/en/arhiv>

© Национальная академия наук Республики Казахстан, 2021

Адрес редакции: 050100, г. Алматы, ул. Кунаева, 142, АО «Институт топлива, катализа и электрохимии им. Д.В. Сокольского», каб. 310, тел. 291-62-80, факс 291-57-22, e-mail: orgcat@nursat.kz

Адрес типографии: ИП «Аруна», г. Алматы, ул. Муратбаева, 75.

E d i t o r i n c h i e f

doctor of chemistry, professor, academician of NAS RK

M.Zh. Zhurinov

E d i t o r i a l b o a r d:

Agabekov V.Ye. prof., academician (Belarus)
Bayeshov A.B. prof., academician (Kazakhstan)
Burkitbayev M.M. prof., academician (Kazakhstan)
Vorotyntsev M.A. prof., academician (Russia)
Gazaliyev A.M. prof., academician (Kazakhstan)
Zharmagambetova A.K. prof. (Kazakhstan), deputy editor in chief
Zhorobekova Sh.Zh. prof., academician (Kyrgyzstan)
Itkulova Sh.S. prof. (Kazakhstan)
Mantashyan A.A. prof., academician (Armenia)
Rakhimov K.D. prof., academician (Kazakhstan)
Rudik V. prof., academician (Moldova)
Streltsov Ye. prof. (Belarus)
Teltaev B.B. prof., akademik (Kazakhstan)
Tuleuov B.I. prof., akademik (Kazakhstan)
Fazylov S.D. prof., akademik (Kazakhstan)
Farzaliyev V. prof., academician (Azerbaijan)
Khalikov D.Kh. prof., academician (Tadjikistan)

News of the National Academy of Sciences of the Republic of Kazakhstan. Series of chemistry and technology.

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Owner: RPA "National Academy of Sciences of the Republic of Kazakhstan" (Almaty).

The certificate of registration of a periodical printed publication in the Committee of information of the Ministry of Information and Social Development of the Republic of Kazakhstan No. **KZ66VPY00025419**, issued 29.07.2020.

Thematic scope: *publication of priority research in the field of chemistry and technology of new materials*

Periodicity: 6 times a year.

Circulation: 300 copies.

Editorial address: 28, Shevchenko str., of. 219, 220, Almaty, 050010, tel. 272-13-19; 272-13-18,
<http://chemistry-technology.kz/index.php/en/arhiv>

© National Academy of Sciences of the Republic of Kazakhstan, 2021

Editorial address: JSC «D.V. Sokolsky institute of fuel, catalysis and electrochemistry», 142, Kunayev str., of. 310, Almaty, 050100, tel. 291-62-80, fax 291-57-22, e-mail: orgcat@nursat.kz

Address of printing house: ST "Aruna", 75, Muratbayev str., Almaty.

NEWS

OF THE NATIONAL ACADEMY OF SCIENCES OF THE REPUBLIC OF KAZAKHSTAN

SERIES CHEMISTRY AND TECHNOLOGY

ISSN 2224-5286

Volume 2, Number 446 (2021), 65 – 71

<https://doi.org/10.32014/2021.2518-1491.28>

UDC 546.05+661.183.2

N. O. Appazov^{1,2}, B. M. Diyarova³, B. M. Bazarbayev¹,
T. Assylbekkyzy¹, S. A. Kanzhar¹, B. Zh. Dzhiembaev

¹Korkyt Ata Kyzylorda University, Kyzylorda, Kazakhstan;

²I. Zhakhaev Kazakh Scientific Research Institute of Rice Growing, Kyzylorda, Kazakhstan;

³Kazakh National Women's Teacher Training University, Almaty, Kazakhstan.

E-mail: nurasar.82@mail.ru, banu_92_06@mail.ru, baurat.bb@gmail.com, tansholpan0504@mail.ru,
sakenkanzhar@gmail.com, bulat.dzhienbaev@gmail.com

RICE STRAW AND HUSK OIL SLUDGE FOR PROCESSING THROUGH THE USE OF LIGNOSULFONATE AS A BINDER WITH ACTIVATED CHARCOAL

Abstract. This article examines the effect of lignosulfonate binding of rice waste to oil waste to obtain activated carbon. Lignosulfonate was added to the mixture to produce briquetted activated carbon by processing rice residue (husk and straw) and oil sludge together. The mixture was carbonized and activated in a BR-12 NFT series high-temperature vacuum tube furnace with a length of 300 mm and a diameter of 60 mm and a heating section length of 200 mm in a quartz glass tube. Briquettes obtained by adding rice waste (husks and straw), oil sludge and lignosulfonate were placed in the kiln. Carbonation was carried out at a temperature of 500°C, activation was carried out at a temperature of 850°C in a ratio of 2: 1 with water vapor. The effect of the relationship of the addition of lignosulfonate binder to rice residue and oil sludge on the product properties was studied. The optimal ratio of co-treatment of the mixture was found in the ratio of rice residue: oil sludge: lignosulfonate = 9: 1: 2 (by weight). The adsorption activity of the obtained product on iodine, the total volume of pores on water, the mass fraction of moisture, the adsorption activity on methylene blue and the bulk density were studied. Activated carbon obtained from both rice straw and rice husk has high sorption properties. According to the results of experimental studies, activated carbon obtained by adding lignosulfonate to rice straw and oil sludge in a ratio of 9: 1: 2 corresponds to the brands BAC-A, WAC, BAC-Au.

Key words: activated carbon, rice husk, rice straw, oil sludge, lignosulfonate, carbonization, activation, briquettes.

Introduction. Currently, the problem of pollution due to active industrial activities, which are harmful to the environment, mainly water, is a matter of concern from year to year. Several processes are used to reduce the level of pollution of water resources and treatment of contaminated water, including the process of adsorption of activated carbon [1].

Adsorption is considered to be more favorable due to its high efficiency, low cost, simple operation and availability of adsorbents [2-4]. Activated carbon is often used as a sorption filter. Activated carbon is one of the most commonly used adsorbents for the removal of dyes from aqueous solutions. Many effective methods of adsorbent production are known, but in some cases are economically inefficient due to the high cost of use, preparation and recovery of raw materials [5]. Therefore, the use of waste and inexpensive products for the production of activated carbon is considered as one of the ways to save adsorbent [6].

One such inexpensive product is agricultural waste, as rice straw and rice husk. During the harvesting and industrial processing of rice, a large amount of waste is collected in the form of bran (up to 20% by weight) and straw (up to 50% by weight). At the end of the campaign, rice husks and straw are burned in the open air, which causes air pollution. Incineration of agricultural waste is a major problem not only for our country but also for the world and is one of the causes of global climate change. Today, the main

problem of scientists is the utilization of straw and bran. The joint solution of environmental and technological problems - the utilization of rice husks and straw, as well as the production of solid products in demand is relevant today. The proposed technologies for the treatment of rice residues are based on the processes of thermal decomposition of soot without release into the atmosphere.

Currently, a number of countries have developed areas for the use of rice waste, the main of which are: production of heat and electricity [7], production of silicon dioxide, activated carbon and sorbents [8], production of liquid chemicals [9-11] and integrated treatment of solid waste [12-16].

In particular, activated carbon is a sorbent belonging to the class of high molecular weight porous carbon materials, capable of efficient and selective absorption of molecules of various chemical substances from vapor-gas and liquid media [17].

Activated carbon is used in ventilation gases, water and other liquid treatment systems, as well as in the protection of the respiratory system [18, 19].

One of the components that determine the properties of activated carbon is the binder. It is designed to simultaneously combine the particles of coal powders into a plastic mass in order to effectively form the primary (raw) granules of carbon sorbent by extrusion and bind these particles into a strong granule with a porous structure developed as a result of heat treatment. In addition, the parameters of their production process are determined by the characteristics and composition of the connecting components.

Most often, granulated activated carbon is produced using wood resin binder [20], coal tar [21] or their mixtures [22-23]. In addition, potassium carbonate was used as a binder for coal tar, while coke residue in coal tar was 15% [24-28].

To obtain activated carbon, the furnace soot was mixed with lignosulfonate, the mixture was granulated, the pellets were dried and activated in a steam-gas medium. Mixing of furnace soot and lignosulfonate was carried out in the form of dry matter in a ratio of 1: 0.6-1.8, and activation was carried out at a temperature of 680-780°C for 60-180 minutes [29]. Petroleum was used as a binder to obtain activated carbon from hard coal. Coal and oil slag are ground together, 4-5% KOH solution is added and activated carbon up to 40-50% by weight is obtained, which allows to remove N, N-dimethylformamide from industrial wastes [30-32]. In addition, technical lignosulfonate dried in air until dry was used as a binder when using peat as a carbon material [33-35].

Although lignosulfonate is widely used in the literature, its use as a binder in the production of activated carbon is still poorly understood. Therefore, the purpose of this research to obtain a stable of high-quality activated carbon components on the basis of this development.

Lignosulfonate - technological processing of vegetable raw material for wood pulp and paper industry products. Lignosulfonate in various fields, because it has a high surface activity can be used as anionic surfactants. Lignosulfonate concrete solutions, dyes, and as a binder component in the production of vanilla is widely used in the production of food [36].

In our previous studies, activated carbon was extracted from rice straw and husks, as well as from rice husks and oil sludge [37, 38], and binders were used to improve its sorption properties and improve our study. As noted above as a binder lignosulfonate used because it is available and has a high surface activity.

Materials and methods. Carbonization with rice residue (husk and straw) by adding lignosulfonate to the oil sludge was carried out in a nitrogen atmosphere at 500 ° C and activation at 850°C with water vapor in a BR-12 NFT series high-temperature vacuum tube furnace. Activated carbon adsorption of iodine from water activity, total pore volume and density of the products from the area were determined by standard methods.

To determine the adsorption activity on iodine, a solution of iodine in potassium iodide at a concentration of 0.1 mol/dm³ was added to a certain part of activated carbon and shaken in a mixer for 15 minutes at an intensity of 100-125 oscillations. Then, after waiting until the solution precipitates, it accumulates the required volume for titration and titrates with 0.1 mol/dm³ of sodium thiosulfate solution until the blue color disappears, using starch as an indicator [39].

To determine the total pore volume in water, pores in the range of 0.5-10⁴ nm are determined by heating in boiling water for 15 minutes, pumping out at a pressure of 8 kPa, separating excess water and weighing it on a balance. Determination of the bulk density of activated carbon was carried out by measuring the mass of normalized compaction of a certain amount of activated carbon [40-41].

Results and discussion. The bricked mixture was placed in a tubular furnace by adding lignosulfonate to rice residue and oil sludge (husk and straw). Hermetically sealed, the tube was filled with nitrogen gas supplied from the cylinder, the carbonization process was increased from 10°C to 500°C per minute and held at this temperature for 100 minutes, and activation was carried out at 850°C in a 2: 1 ratio of carbonate and water vapor. The effect of lignosulfonate ratio on the yield and physical and chemical properties of activated carbon was studied (table 1).

Table 1 - Properties of activated carbon obtained by the use of lignosulfonate as a binder in the processing of rice straw and with oil sludge

Indicator	The results of experimental research			
	Rice straw: lignosulfonate	Rice straw: Oil sludge: Lignosulfonate		
Ratio	10:1	9:1:1.1	9:1:1.25	9:1:2
Carbonation temperature, °C	500			
Carbonate consumption, mass %	61.57	53.76	74.5	84.30
Activation temperature, °C	850			
Water: carbonate ratio	2:1			
Consumption of activated carbon, dr. %	35.92	33.99	29.86	24.72
Adsorption activity on iodine,%	39.37	55.88	62.33	64.77
Total volume of pores on water, cm ³ /g	0.929	0.930	0.946	0.950
Mass fraction of moisture,%	1.49	1.56	1.68	2.39
Heap density, g/dm ³	233.94	239.59	246.01	251.86
Adsorption activity on methylene blue, mg/g	432.20	412.35	431.10	411.12

According to the results shown in table 1, rice straw: oil sludge: as the content of lignosulfonate in activated carbon obtained from lignosulfonate increases, its adsorption activity for iodine increases from 39.37% to 64.77%, the total porosity of water increases from 0.929 cm³/g 0.950 cm³/g, the mass fraction of moisture increased from 1.49% to 2.39%, the bulk density increased from 233.94 g/dm³ to 251.86 g/dm³. When processing rice straw with oil sludge, the ratio of 9: 1: 2 was chosen as the optimal ratio for the production of activated carbon with the addition of a binder lignosulfonate. In figure 1 shown the optimal ratio of activated carbon.



Figure 1 – Rice straw: oil sludge: activated carbon which was taken in the ratio of lignosulfonate 9: 1: 2

Table 2 - Properties of activated carbon obtained by the use of lignosulfonate as a binder in the processing of rice husk and with oil sludge

Indicator	The results of experimental research			
	Rice husk: lignosulfonate	Rice husk: Oil sludge: Lignosulfonate		
Ratio	10:1	9:1:1.1	9:1:1.25	9:1:2
Carbonation temperature, °C	500			
Carbonate consumption, mass%	68.14	81.75	71.11	79.07
Activation temperature, °C	850			
Water: carbonate ratio	2:1			
Consumption of activated carbon, dr. %	34.83	28.07	35.29	32.73
Adsorption activity on iodine,%	31.75	48.26	54.61	61.17
Total volume of pores on water, cm ³ /g	0.551	0.563	0.571	0.584
Mass fraction of moisture, %	1.19	1.29	1.81	1.88
Heap density, g/dm ³	351.27	362.95	367.17	392.18
Adsorption activity on methylene blue, mg/g	344.50	355.50	362.70	352.70

On table 2, rice husk: oil sludge: it can be seen that as the amount of lignosulfonate in activated carbon obtained from lignosulfonate increases, the adsorption activity for iodine increases from 31.75% to 61.17%, the total porosity of water increases from 0.551 cm³/g to 0.584 cm³/g, the mass fraction of moisture increases from 1.19% to 1.88%, the bulk density increases from 351.27 g/dm³ to 392.18 g/dm³. When processing rice hulls with oil sludge, the ratio of 9: 1: 2 was chosen as the optimal ratio for the production of activated carbon by adding a binder lignosulfonate. In figure, 2 shown the activated carbon obtained in an optimal ratio.



Figure 2 – Rice husk oil sludge: activated carbon obtained in the ratio of lignosulfonate 9: 1: 2.

Comparing rice bran to rice soap, the total number of pores in water in rice soap is 1.6 times greater than that in rice bran. The density of the heap in rice hulls is 1.5 times that of rice hulls. There is no significant difference in the mass fraction of moisture and the values of the adsorption activity for methylene blue. When processing rice straw and husks with oil sludge, the ratio of 9: 1: 2 was chosen as the optimal ratio for the production of activated carbon with the addition of lignosulfonate as a binder.

Conclusions. In conclusion, the optimal conditions were determined in the ratio of rice husk: oil sludge: lignosulfonate = 9: 1: 2 and rice straw: oil sludge: lignosulfonate = 9: 1: 2. The adsorption activity of activated carbon on iodine was 61.74% in rice husk, 64.77% in rice straw, the total volume of water pores was 0.584 cm³/g in rice husk, 0.950 cm³/g in rice straw and the bulk density was 392.18 g/dm³ in rice husk in rice straw showed 251.86 g/dm³. According to the results of experimental studies, activated carbon obtained by adding lignosulfonate to oil sludge with rice residue in a ratio of 9: 1: 2 corresponds to the brands BAC-A, WAC, BAC-Au. The use of the proposed method of production of activated carbon compared to the known method provides high adsorption activity, and it is recommended to use rice waste and oil waste and lignosulfonate as raw materials. The results of the study allow for the rational use of environmentally important and natural resources.

Funding. The work was carried out with the support of the Ministry of Education and Science of the Republic of Kazakhstan and the Committee of Science due to grant funding AP05134356.

**Н.О. Аппазов^{1,2}, Б.М. Диярова³, Б.М. Базарбаев¹,
Т. Асылбекқызы¹, С.А. Қанжар¹, Б.Ж. Джиембаев³**

¹ Қорқыт Ата атындағы Қызылорда университеті, Қызылорда қаласы, Қазақстан;

² Ы. Жақаев атындағы Қазақ күріш шаруашылығы ғылыми-зерттеу институты, Қызылорда қаласы, Қазақстан;

³ Қазақ ұлттық қыздар педагогикалық университеті, Алматы қаласы, Қазақстан

КҮРІШ САБАНЫ МЕН ҚАУЫЗЫН МҰНАЙ ШЛАМЫМЕН БІРГЕ ӨНДЕУ КЕЗІНДЕ ЛИГНОСУЛЬФОНАТТЫ ПАЙДАЛАНУ ОТЫРЫП БЕЛСЕНДІРІЛГЕН КӨМІР АЛУ

Аннотация. Бұл мақалада белсендірілген көмір алу үшін күріш қалдығымен мұнай қалдығына байланыстырушы лигносульфонат әсері зерттелді. Күріш қалдығы (қауызы және сабаны) мен мұнай шламын бірге өңдеу арқылы брикеттелген белсендірілген көмір алу үшін қоспаға лигносульфонат қосылды. Қоспаны карбонизациялау және белсендіру кварцты шыныдан жасалған түтікте ұзындығы 300 мм және диаметрі 60 мм, қыздыру бөлімінің ұзындығы 200 мм болатын BR-12 NFT сериялы жоғары температурада вакуумдық түтікте пеште жүргізілді. Карбонизация 500°C температурада, белсендіру 850°C температурада 2:1 қатынаста су буымен жүргізілді. Күріш қалдығы мен мұнай шламына лигносульфонат байланыстырғышын қосу қатынас-

тарының өнім қасиеттеріне әсері зерттелді. Қоспаны бірге өңдеудің оңтайлы қатынасы күріш қалдығы: мұнай шламы: лигносульфонат = 9:1:2 (салмақтары бойынша) қатынастары табылды. Алынған өнімнің йод бойынша адсорбциялық белсенділігі, су бойынша жалпы кеуектер көлемі, ылғалдың массалық үлесі, метилен көгі бойынша адсорбциялық белсенділігі және үйінділік тығыздығы тәрізді көрсеткіштер зерттелді. Жүргізілген зерттеулер нәтижесі бойынша белсендірілген көмірдің құрамындағы лигносульфонат мөлшері артқан сайын оның сорбциялық қасиетінің артатыны байқалды. Күріш сабанынан да, күріш қаузынан да алынған белсендірілген көмір жоғары сорбциялық қасиеттерге ие. Тәжірибелік зерттеулер нәтижесі бойынша 9:1:2 қатынастағы күріш қалдығы мен мұнай шламы және лигносульфонатты қосу арқылы алынған белсендірілген көмір БАУ-А, ДАК, БАУ-Ац маркаларына сәйкес келеді.

Түйін сөздер: белсендірілген көмір, күріш қаузы, күріш сабаны, мұнай шламы, лигносульфонат, карбонизация, белсендіру, брикеттер.

Н.О. Аппазов^{1,2}, Б.М. Диярова³, Б.М. Базарбаев¹,
Т. Асылбекқызы¹, С.А. Канжар¹, Б.Ж. Джембаев¹

¹Кызылординский университет имени Коркыт Ата, Кызылорда, Казахстан;

²Казахский научно-исследовательский институт рисоводства им. И. Жахаева, Кызылорда, Казахстан;

³Казахский национальный женский педагогический университет, Алматы, Казахстан

ПОЛУЧЕНИЕ АКТИВИРОВАННОГО УГЛЯ С ИСПОЛЬЗОВАНИЕМ ЛИГНОСУЛЬФОНАТА В КАЧЕСТВЕ СВЯЗУЮЩЕГО ПРИ СОВМЕСТНОЙ ПЕРЕРАБОТКЕ РИСОВОЙ СОЛОМЫ И ШЕЛУХИ С НЕФТЕШЛАМОМ

Аннотация. В данной статье изучено влияние лигносульфоната как связующего вещества для получения брикетированного активированного угля путем совместной переработки отходов риса (шелухи и соломы) и нефтешлама. Карбонизацию и активацию смеси проводили в высокотемпературной вакуумной трубчатой печи серии BR-12 NFT длиной 200 мм, в нагревательной стеклянной трубке из кварца размером 300 мм и диаметром 60 мм. В печь помещали отход риса (шелуху или солому) в виде брикетированного с добавлением лигносульфоната и нефтешлама. Карбонизацию проводили при температуре 500°C, активацию – водяным паром при температуре 850°C в соотношении 2:1. Исследовано влияние соотношений лигносульфонатного связующего, отхода риса и нефтешлама на свойства активированного угля. Оптимальным соотношением совместной переработки смеси является отход риса: нефтешлам: лигносульфонат 9:1:2 (по массе). Исследования проводились по следующим показателям: адсорбционная активность по йоду, общий объем пор по воде, массовая доля влаги, адсорбционная активность по метиленовому голубому и насыпная плотность. По результатам проведенных исследований было отмечено, что по мере увеличения содержания лигносульфоната в активированном угле повышаются его сорбционные свойства. Активированный уголь, полученный как на основе рисовой соломы, так и на основе рисовой шелухи, обладает высокими сорбционными свойствами. По результатам экспериментальных исследований установлено, что активированный уголь, полученный из отходов риса, нефтешлама и лигносульфоната, в соотношениях 9:1:2 соответствует маркам БАУ-А, ДАК, БАУ – Ац.

Ключевые слова: активированный уголь, рисовая шелуха, рисовая солома, нефтешлам, лигносульфонат, карбонизация, активация, брикеты.

Information about authors:

Appazov Nurbol Orynbasaruly, Candidate of Chemical sciences, Professor, Deputy Chairman of the board for scientific work of the I. Zhakhaev Kazakh Scientific Research Institute of Rice Growing and Chief scientist of the laboratory of engineering profile of the Korkyt Ata Kyzylorda University, Aiteke bi street, 29A, 120014, Kyzylorda, Republic of Kazakhstan; e-mail: nurasar.82@mail.ru; <https://orcid.org/0000-0001-8765-3386>;

Diyarova Banu Maralbekkyzy (corresponding author), doctoral student in chemistry of the Kazakh National Women's Teacher Training University, Aiteke bi street, 99, 050000, Almaty, Republic of Kazakhstan; e-mail: banu_92_06@mail.ru; <https://orcid.org/0000-0002-1086-369X>;

Bazarbayev Baurat Malikuly, engineer of the laboratory of engineering profile of the Korkyt Ata Kyzylorda University, Aiteke bi street, 29A, 120014, Kyzylorda, Republic of Kazakhstan; e-mail: baurat.bb@mail.ru; <http://orcid.org/0000-0003-1574-8145>;

Assylbekkyzy Tangsholpan, master's student in chemical technology of inorganic substances of the Korkyt Ata Kyzylorda University, Aiteke bi street, 29A, 120014, Kyzylorda, Republic of Kazakhstan; e-mail: tansholpan0504@mail.ru; <https://orcid.org/0000-0001-5337-2164>;

Kanzhar Saken Alimuly, student in chemical technology of organic substances of the Korkyt Ata Kyzylorda University, Aiteke bi street, 29A, 120014, Kyzylorda, Republic of Kazakhstan; e-mail: sakenkanzhar@gmail.com; <https://orcid.org/0000-0003-4553-3049>;

Dzhiembaev Bulat Dzhazkenovich, Doctor of Chemical Sciences, Professor of the Department of Chemistry, Institute of Natural Sciences, Kazakh National Women's Teacher Training University, Aiteke bi street 99, 050000, Almaty, Republic of Kazakhstan; e-mail: bulat.dzhiembaev@gmail.com; <https://orcid.org/0000-0001-7868-7285>

REFERENCES

- [1] Ouhammou M., Lahnine L., Mghazli S., Hidar N., Bouchdoug M., Jaouad A., Mandi L., & Mahrouz M. (2019). Valorisation of cellulosic waste basic cactus to prepare activated carbon. *Journal of the Saudi Society of Agricultural Sciences*, 18, 133–140. DOI 10.1016/j.jssas.2017.03.003
- [2] Sasmal D., Maity J., Kolya H., & Tripathy T. (2017). Study of Congo red dye removal from its aqueous solution using sulfated acrylamide and N, N–dimethyl acrylamide grafted amylopectin. *Journal. Water Process Engineering*, 18, 7–19. DOI: 10.1016/j.jwpe.2017.05.007
- [3] Thue P.S., Sophia A.C., Lima E.C., Wamba A.G.N., de Alencar W.S., & dos Reis G. S. Synthesis and characterization of a novel organic–inorganic hybrid clay adsorbent for the removal of acid red 1 and acid green 25 from aqueous solutions. *Journal of Cleaner Production*, 171, 30–44. DOI: 10.1016/j.jclepro.2017.09.278
- [4] Abbasi M. (2017). Synthesis and characterization of magnetic nanocomposite of chitosan/ SiO₂/carbon nanotubes and its application for dyes removal. *Journal of Cleaner Production*, 145, 105–113. DOI: 10.1016/j.jclepro.2017.01.046
- [5] Ferreira G.M.D., Hespanhol M.C., de Paula Rezende J., dos Santos Pires A.C., Gurgel, L.V.A., & da Silva, L.H.M. (2017). Adsorption of red azo dyes on multi-walled carbon nanotubes and activated carbon: a thermodynamic study. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 529, 531–540. DOI: 10.1016/j.colsurfa.2017.06.021
- [6] Tran H.N. You S.J., & Chao H.P. (2017) Fast and efficient adsorption of methylene green 5 on activated carbon prepared from new chemical activation method. *Journal Environmental Management*, 188, 322–336. DOI 10.1016/j.jenvman.2016.12.003
- [7] Misson M., Haron R., Kamaroddin M.F.A., & Amin N.A.S. (2009). Pretreatment of empty palm fruit bunch for production of chemicals via catalytic pyrolysis. *Bioresource Technology*, 100 (11), 2867–2873. DOI: 10.1016/j.jenvman.2016.12.003
- [8] Foo K.Y., & Hameed B.H. (2011). Utilization of rice husks as a feedstock for preparation of activated carbon by microwave induced KOH and K₂CO₃ activation. *Bioresource Technology*, 102, 9814–9817. DOI: 10.1016/j.biortech.2011.07.102
- [9] Sazonov YU. N., Gribov A.V. (2010). Termokhimiya lignina [Thermochemistry of lignin]. *Zhurnal prikladnoy khimii - Journal of Applied Chemistry*, Vol. 83, 2, 175–194 [in Russian].
- [10] Suerbaev H. A., Chepajkin E. G., Dzhiembaev B. Z., Appazov N. O., & Abyzbekova G. M. (2007). Catalytic hydroxycarbonylation of isobutylene with carbon monoxide and polyhydric alcohols in the presence of the Pd (acac) (2)-PPh₃-TsOH system. *Petroleum Chemistry*, 47(5), 345-347. <https://doi.org/10.1134/s0965544107050064>.
- [11] Chang H., Yan H., Chong R. (2001). Effects of pre carbonization on porosity development of activated carbons from rice straw. *Carbon*, 39 (4), 559–567.
- [12] Arutyunyan T. V., Korystova A. F., Kublik L. N., Levitman M. K., Shaposhnikova V. V., Appazov N. O., Narmanova, R. A., Ibadullayeva, S. Z., & Korystov, Y. N. (2014). Camel Thorn Extract Reduces Activity of Angiotensin-Converting Enzyme in Rat Aorta Increased during Aging and Treatment with NO-Synthase Inhibitor. *Bulletin of Experimental Biology and Medicine*, 158(2), 222-224. <https://doi.org/10.1007/s10517-014-2727-2>.
- [13] Yespanova I.D., Zhusupova L.A., Tapalova A.S., Appazov N.O. (2018) Microwave activation of addition of 1-hexene and butanoic acid reaction // News of the National Academy of Sciences of the Republic of Kazakhstan-Series Chemistry and Technology. 1: 63-69. ISSN 2518-1491 (Online), ISSN 2224-5286 (Print).
- [14] Marsh H., Rodriguez Reinoso F. (2006). Activated Carbon. Amsterdam, Elsevier Science & Technology Books.
- [15] Shalbolova U., Narmanova R., Elpanova M. (2012) Methodical peculiarities of tariff setting at oil transportation via main pipelines // Actual problems of economics. 138: 540-555. ISSN: 1993-6788.
- [16] Sergiyenko V.I., Zemnukhova L.A., Yegorov A.V., Ye. D., Shkorina N.S. (2004). Vasilyuk Vozobnovlyayemye istochniki khimicheskogo syr'ya: kompleksnaya pererabotka otkhodov proizvodstva risa i grechikhi [Renewable sources of chemical raw materials: complex processing of rice and buckwheat production waste]. *Rossiyskiy khimicheskiy zhurnal – Russian Chemical Journal*, Vol. 48, 3, 116–124 [In Russian].
- [17] Mukhin V.M. (2014) Ekologicheskiye aspekty primeneniya aktivnykh ugley [Environmental aspects of using activated coals]. *Ekologiya i promyshlennost' Rossii – Ecology and industry of Russia*, Vol. 12, 52-56 [In Russian].
- [18] Zav'yalov, A.N., Gusher L.K., & Kasilova L.V. (1990). Patent No. 2053958 RF. Publ. [In Russian].
- [19] Lyubchik S., Shapovalova O., Lygina O., Oliveira M. C., Appazov N. O., Lyubchik A., Charmier A. J., Lyubchik S., Pombeiro, A. J. L. (2019). Integrated Green Chemical Approach to the Medicinal Plant *Carpobrotus edulis* Processing [Article]. *Scientific Reports*, 9, 12, Article 18171. <https://doi.org/10.1038/s41598-019-53817-8>.
- [20] Suerbaev K.A., Chepaikin E.G., Appazov N.O., Dzhiembaev B.Z. (2012) Hydroalkoxycarbonylation of isobutylene with polyhydric alcohols in the presence of catalytic systems based on palladium compounds and tertiary phosphines // *Petroleum Chemistry*. 52(3): 189-193. ISSN: 1555-6239 (Online), ISSN: 0965-5441. doi: 10.1134/S0965544112030127.

- [21] Andreykov Ye. I. (2017). Novyye produkty i protsessy na baze kamennougol'noy smoly [New products and processes based on coal tar]. *Ugle khimiya i ekologiya Kuzbassa - 2017: Sbornik tezisov dokladov - Coal chemistry and ecology of Kuzbassa - 2017: a collection of abstracts*, 17.
- [22] Suerbaev K. A., Kudaibergenov N. Z., Appazov N. O., & Zhaksylykova G. Z. (2016). Synthesis of L-menthyl isovalerate by esterification of isovaleric acid with L-menthol under microwave irradiation. *Russian Journal of Organic Chemistry*, 52(4), 585-586. <https://doi.org/10.1134/s1070428016040205>.
- [23] Mukhin V.M., Klushin V.N. (2012). Production and application of carbon adsorbents. [Production and application of carbon adsorbents]. M: Russian University of Chemical Technology. DI. Mendeleev [In Russian].
- [24] Bisenov K.A., Narmanova R.A., Appazov N.O. (2020). Physical and chemical studies of the oil sludge hydrocarbon composition and the prospects for their use in the technology of expanded clay production // *News of NAS RK. Series of chemistry and technology*. 5(443): 28-37. <https://doi.org/10.32014/2020.2518-1491.77>
- [25] Narmanova R.A., Bishimbayev V.K., Tapalova A.S., Appazov N.O. (2020). Polymer additive effect on the structural and mechanical properties of the organic part of oil bituminous rock. // *News of NAS RK. Series of chemistry and technology*. 5(443): 141-150. <https://doi.org/10.32014/2020.2518-1491.91>
- [26] Glushankov, S.L., Farberova, Ye. A., Zorina, Ye. I., & Tin'gayeva Ye. A. Usovershenstvovaniye tekhnologii polucheniya granulirovannogo aktivnogo uglya melkogo zemeniya AG-5 [Improvement of the technology for producing finely grained granular activated carbon AG-5]. *Zhurnal prikladnoy khimii – Journal of Applied Chemistry*, Vol. 83, 6, 714-720 [In Russian].
- [27] Zimin N.A., Leyf V.E., Tamam'yan A.N., Vnuchkova V.A., Khazanov A.A., Aleshina N.S., Taratun M.N., Arzhakov A.Ye., & Kondrat'yeva V.V. (2001). Patent 2174949 RF. Publ. [In Russian].
- [28] Abdibattayeva M., Bisenov K., Rysmagambetova A., Itzhanova K., Sgem. (2016, Jun 30-Jul 06). Integrated oil waste processing with using solar energy. *International Multidisciplinary Scientific Geo Conference-SGEM* [Energy and clean technologies conference proceedings, sgem 2016, vol i]. 16th International Multidisciplinary Scientific Geoconference (SGEM 2016), Albena, Bulgaria.
- [29] Lagunov V.M., Shepelev A.N., Yermolayev V.A., Abdeyeva G.V., Bricheva I.L. (1991). Patent 2033387 RF. Publ. [In Russian].
- [30] Mukhin, V. M., Zubova, I. D., Zubova, I.N., Chumakov, V. P., & Yakovleva, Ye. N. (2007). Patent 2344075 RF. Publ. [in Russian].
- [31] Suerbaev K. A., Chepaikin E. G., Zhaksylykova G. Z., Kanybetov K. S., Turkbenov T. K., Abyzbekova G. M. (2008). Hydroxycarbonylation of isobutylene in the presence of the palladium acetylacetonate-triphenylphosphine-p-toluenesulfonic acid catalyst system. *Petroleum Chemistry*, 48(3), 206-209. <https://doi.org/10.1134/s0965544108030067>
- [32] Appazov N.O., Seitzhanov S.S., Zhunissov A.T., Narmanova, R.A. (2017) Synthesis of Cyclohexyl Isovalerate by Carbonylation of Isobutylene with Carbon Monoxide and Cyclohexanol in the Presence of Pd(PPh3)(4)-PPh3-TsOH and Its Antimicrobial Activity // *Russian Journal of Organic Chemistry*. 53(10): 1596-1597. ISSN: 1608-3393 (Online), ISSN: 1070-4280. doi: 10.1134/S1070428017100189.
- [33] Timofeyev A. Ye., Misnikov O.S. Timofeyev A.Ye. (2009). Metody modifikatsii formovannykh sorbtionnykh materialov na osnove torfa [Methods of modification of molded sorption materials based on peat]. *Gornyy informatsionno-analiticheskiy byulleten' – Mining information and analytical bulletin*, Vol.5, 112-120 [In Russian].
- [34] Гаврилов С.В. Адсорбционные свойства торфа и продуктов его переработки / С.В. Гаврилов, З.А. Канарская // *Вестник Казанского технологического университета – 2015. – Т. 18, №2. – С. 422-427.*
- [35] Buzanova G.N., Gayenko V.N. (2000). Patent 2171779 RF. Publ. [In Russian].
- [36] Islamov S.R., Stepanov S.G., & Nagibin, G.Ye. (2008) Patent 2376342 RF. Publ. [in Russian].
- [37] Appazov N.O., Turmanov R.A., Lyubchik S.B., Lyubchik A.I., Lyubchik S.I., Lygina O.S., Baynazarova S.R., Bazarbayev B.M. (2019). Patent №3892 Kaz. Publ. [in Russian].
- [38] Appazov N.O., Turmanov R.A., Baynazarova S.R., Diyarova B.M., Shuragazyeva A.T., Dzhiyembayev B.ZH., Lygina, O.S., Lyubchik, A.I., & Kurmanbayev, R.KH. (2019) Patent №3821 Kaz. Publ. [in Russian].
- [39] GOST 6217. Crushed active charcoal. Technical conditions [Ugol' aktivnyj drevesnyj droblenyj. Tehnicheskie uslovija]. Moscow, Russia, 2003. [In Russian].
- [40] GOST 17219. Active coals. Method for determining the total pore volume by water [Ugli aktivnyye. Metod opredeleniya summarnogo ob'ema por po vode]. Moscow, Russia, 1988. [In Russian].
- [41] GOST 16190. Sorbents. Bulk density determination method [Sorbenty. Metod opredeleniya nasypnoy plotnosti]. Moscow, Russia, 1970. [In Russian].

Publication Ethics and Publication Malpractice in the journals of the National Academy of Sciences of the Republic of Kazakhstan

For information on Ethics in publishing and Ethical guidelines for journal publication see <http://www.elsevier.com/publishingethics> and <http://www.elsevier.com/journal-authors/ethics>.

Submission of an article to the National Academy of Sciences of the Republic of Kazakhstan implies that the described work has not been published previously (except in the form of an abstract or as part of a published lecture or academic thesis or as an electronic preprint, see <http://www.elsevier.com/postingpolicy>), that it is not under consideration for publication elsewhere, that its publication is approved by all authors and tacitly or explicitly by the responsible authorities where the work was carried out, and that, if accepted, it will not be published elsewhere in the same form, in English or in any other language, including electronically without the written consent of the copyright-holder. In particular, translations into English of papers already published in another language are not accepted.

No other forms of scientific misconduct are allowed, such as plagiarism, falsification, fraudulent data, incorrect interpretation of other works, incorrect citations, etc. The National Academy of Sciences of the Republic of Kazakhstan follows the Code of Conduct of the Committee on Publication Ethics (COPE), and follows the COPE Flowcharts for Resolving Cases of Suspected Misconduct (http://publicationethics.org/files/u2/New_Code.pdf). To verify originality, your article may be checked by the Cross Check originality detection service <http://www.elsevier.com/editors/plagdetect>.

The authors are obliged to participate in peer review process and be ready to provide corrections, clarifications, retractions and apologies when needed. All authors of a paper should have significantly contributed to the research.

The reviewers should provide objective judgments and should point out relevant published works which are not yet cited. Reviewed articles should be treated confidentially. The reviewers will be chosen in such a way that there is no conflict of interests with respect to the research, the authors and/or the research funders.

The editors have complete responsibility and authority to reject or accept a paper, and they will only accept a paper when reasonably certain. They will preserve anonymity of reviewers and promote publication of corrections, clarifications, retractions and apologies when needed. The acceptance of a paper automatically implies the copyright transfer to the National Academy of Sciences of the Republic of Kazakhstan.

The Editorial Board of the National Academy of Sciences of the Republic of Kazakhstan will monitor and safeguard publishing ethics.

Правила оформления статьи для публикации
в журнале смотреть на сайте:

www.nauka-nanrk.kz

<http://chemistry-technology.kz/index.php/en/arhiv>

ISSN 2518-1491 (Online), ISSN 2224-5286 (Print)

Редакторы: *М. С. Ахметова, Д. С. Аленов, Р.Ж. Мрзабаева*
Верстка на компьютере *Д. А. Абдрахимовой*

Подписано в печать 12.04. 2021.
Формат 60x881/8. Бумага офсетная. Печать – ризограф.
10,2 п.л. Тираж 300. Заказ 2.