

ISSN 2518-1491 (Online),
ISSN 2224-5286 (Print)



«ҚАЗАҚСТАН РЕСПУБЛИКАСЫ
ҰЛТТЫҚ ҒЫЛЫМ АКАДЕМИЯСЫ» РҚБ
«ХАЛЫҚ» ЖҚ

Х А Б А Р Л А Р Ы

ИЗВЕСТИЯ

NEWS

РОО «НАЦИОНАЛЬНОЙ
АКАДЕМИИ НАУК РЕСПУБЛИКИ
КАЗАХСТАН»
ЧФ «Халық»

OF THE ACADEMY OF SCIENCES
OF THE REPUBLIC OF
KAZAKHSTAN
«Halyk» Private Foundation

**SERIES
CHEMISTRY AND
TECHNOLOGY
2 (459)**

APRIL – JUNE 2024

PUBLISHED SINCE JANUARY 1947

PUBLISHED 4 TIMES A YEAR

ALMATY, NAS RK



ЧФ «ХАЛЫҚ»

В 2016 году для развития и улучшения качества жизни казахстанцев был создан частный Благотворительный фонд «Халык». За годы своей деятельности на реализацию благотворительных проектов в областях образования и науки, социальной защиты, культуры, здравоохранения и спорта, Фонд выделил более 45 миллиардов тенге.

Особое внимание Благотворительный фонд «Халык» уделяет образовательным программам, считая это направление одним из ключевых в своей деятельности. Оказывая поддержку отечественному образованию, Фонд вносит свой посильный вклад в развитие качественного образования в Казахстане. Тем самым способствуя росту числа людей, способных менять жизнь в стране к лучшему – профессионалов в различных сферах, потенциальных лидеров и «великих умов». Одной из значимых инициатив фонда «Халык» в образовательной сфере стал проект *Ozgeris powered by Halyk Fund* – первый в стране бизнес-инкубатор для учащихся 9-11 классов, который помогает развивать необходимые в современном мире предпринимательские навыки. Так, на содействие малому бизнесу школьников было выделено более 200 грантов. Для поддержки талантливых и мотивированных детей Фонд неоднократно выделял гранты на обучение в Международной школе «Мирас» и в Astana IT University, а также помог казахстанским школьникам принять участие в престижном конкурсе «USTEM Robotics» в США. Авторские работы в рамках проекта «Тәлімгер», которому Фонд оказал поддержку, легли в основу учебной программы, учебников и учебно-методических книг по предмету «Основы предпринимательства и бизнеса», преподаваемого в 10-11 классах казахстанских школ и колледжей.

Помимо помощи школьникам, учащимся колледжей и студентам Фонд считает важным внести свой вклад в повышение квалификации педагогов, совершенствование их знаний и навыков, поскольку именно они являются проводниками знаний будущих поколений казахстанцев. При поддержке Фонда «Халык» в южной столице был организован ежегодный городской конкурс педагогов «Almaty Digital Ustaz».

Важной инициативой стал реализуемый проект по обучению основам финансовой грамотности преподавателей из восьми областей Казахстана, что должно оказать существенное влияние на воспитание финансовой грамотности и предпринимательского мышления у нового поколения граждан страны.

Необходимую помощь Фонд «Халык» оказывает и тем, кто особенно остро в ней нуждается. В рамках социальной защиты населения активно проводится

работа по поддержке детей, оставшихся без родителей, детей и взрослых из социально уязвимых слоев населения, людей с ограниченными возможностями, а также обеспечению нуждающихся социальным жильем, строительству социально важных объектов, таких как детские сады, детские площадки и физкультурно-оздоровительные комплексы.

В копилку добрых дел Фонда «Халык» можно добавить оказание помощи детскому спорту, куда относится поддержка в развитии детского футбола и карате в нашей стране. Жизненно важную помощь Благотворительный фонд «Халык» оказал нашим соотечественникам во время недавней пандемии COVID-19. Тогда, в разгар тяжелой борьбы с коронавирусной инфекцией Фонд выделил свыше 11 миллиардов тенге на приобретение необходимого медицинского оборудования и дорогостоящих медицинских препаратов, автомобилей скорой медицинской помощи и средств защиты, адресную материальную помощь социально уязвимым слоям населения и денежные выплаты медицинским работникам.

В 2023 году наряду с другими проектами, нацеленными на повышение благосостояния казахстанских граждан Фонд решил уделить особое внимание науке, поскольку она является частью общественной культуры, а уровень ее развития определяет уровень развития государства.

Поддержка Фондом выпуска журналов Национальной Академии наук Республики Казахстан, которые входят в международные фонды Scopus и WoS и в которых публикуются статьи отечественных ученых, докторантов и магистрантов, а также научных сотрудников высших учебных заведений и научно-исследовательских институтов нашей страны является не менее значимым вкладом Фонда в развитие казахстанского общества.

**С уважением,
Благотворительный Фонд «Халык»!**

Бас редактор:

ЖҰРЫНОВ Мұрат Жұрынұлы, химия ғылымдарының докторы, профессор, ҚР ҰҒА академигі, Қазақстан Республикасы Ұлттық ғылым академиясының президенті, АҚ «Д.В. Сокольский атындағы отын, катализ және электрохимия институтының» бас директоры (Алматы, Қазақстан) Н = 4

Редакция алқасы:

ӘДЕКЕНОВ Серғазы Мынжасарұлы (бас редактордың орынбасары), химия ғылымдарының докторы, профессор, ҚР ҰҒА академигі, «Фитохимия» Халықаралық ғылыми-өндірістік холдингінің директоры (Қарағанды, Қазақстан) Н = 11

АГАБЕКОВ Владимир Енокович (бас редактордың орынбасары), химия ғылымдарының докторы, профессор, Беларусь ҰҒА академигі, Жаңа материалдар химиясы институтының құрметті директоры (Минск, Беларусь) Н = 13

СТРНАД Мирослав, профессор, Чехия ғылым академиясының Эксперименттік ботаника институтының зертхана меңгерушісі (Оломоуц, Чехия) Н = 66

БҮРКІТБАЕВ Мұхамбетқали, химия ғылымдарының докторы, профессор, ҚР ҰҒА академигі, әл-Фараби атындағы ҚазҰУ-дың бірінші проректоры (Алматы, Қазақстан) Н = 11

ХОХМАНН Джудит, Сегед университетінің Фармацевтика факультетінің Фармакогнозия кафедрасының меңгерушісі, Жаратылыстану ғылымдарының пәнаралық орталығының директоры (Сегед, Венгрия) Н = 38

РОСС Самир, PhD докторы, Миссисипи университетінің Өсімдік өнімдерін ғылыми зерттеу ұлттық орталығы, Фармация мектебінің профессоры (Оксфорд, АҚШ) Н = 35

ХУТОРЯНСКИЙ Виталий, философия докторы (PhD, фармацевт), Рединг университетінің профессоры (Рединг, Англия) Н = 40

ТЕЛТАЕВ Бағдат Бұрханбайұлы, техника ғылымдарының докторы, профессор, ҚР ҰҒА корреспондент-мүшесі, Қазақстан Республикасы Индустрия және инфрақұрылымдық даму министрлігі (Алматы, Қазақстан) Н = 13

ФАРУК Асана Дар, Хамдар аль-Маджида Шығыс медицина колледжінің профессоры, Хамдард университетінің Шығыс медицина факультеті (Карачи, Пәкістан) Н = 21

ФАЗЫЛОВ Серік Драхметұлы, химия ғылымдарының докторы, профессор, ҚР ҰҒА академигі, Органикалық синтез және көмір химиясы институты директорының ғылыми жұмыстар жөніндегі орынбасары (Қарағанды, Қазақстан) Н = 6

ЖОРОБЕКОВА Шарипа Жоробекқызы, химия ғылымдарының докторы, профессор, Қырғызстан ҰҒА академигі, ҚР ҰҒА Химия және химиялық технология институты (Бішкек, Қырғызстан) Н = 4

ХАЛИКОВ Джурабай Халикович, химия ғылымдарының докторы, профессор, Тәжікстан ҒА академигі, В.И. Никитин атындағы Химия институты (Душанбе, Тәжікстан) Н = 6

ФАРЗАЛИЕВ Вагиф Меджидоглы, химия ғылымдарының докторы, профессор, ҰҒА академигі (Баку, Әзірбайжан) Н = 13

ГАРЕЛИК Хемда, философия докторы (PhD, химия), Халықаралық таза және қолданбалы химия одағының Химия және қоршаған орта бөлімінің президенті (Лондон, Англия) Н = 15

«ҚР ҰҒА Хабарлары. Химия және технология сериясы»

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Меншіктенуші: «Қазақстан Республикасының Ұлттық ғылым академиясы» РҚБ (Алматы қ.). Қазақстан Республикасының Ақпарат және қоғамдық даму министрлігінің Ақпарат комитетінде 29.07.2020 ж. берілген № **KZ66VPY00025419** мерзімдік басылым тіркеуіне қойылу туралы куәлік.

Тақырыптық бағыты: *органикалық химия, бейорганикалық химия, катализ, электрохимия және коррозия, фармацевтикалық химия және технологиялар.*

Мерзімділігі: жылына 4 рет.

Тиражы: 300 дана.

Редакцияның мекен-жайы: 050010, Алматы қ., Шевченко көш., 28, 219 бөл., тел.: 272-13-19

<http://chemistry-technology.kz/index.php/en/archiv>

© Қазақстан Республикасының Ұлттық ғылым академиясы РҚБ, 2024

Редакцияның мекенжайы: 050100, Алматы қ., Қонаев к-сі, 142, «Д.В. Сокольский атындағы отын, катализ және электрохимия институты» АҚ, каб. 310, тел. 291-62-80, факс 291-57-22, e-mail: orgcat@nursat.kz

Главный редактор:

ЖУРИНОВ Мурат Журинович, доктор химических наук, профессор, академик НАН РК, президент Национальной академии наук Республики Казахстан, генеральный директор АО «Институт топлива, катализа и электрохимии им. Д.В. Сокольского» (Алматы, Казахстан) Н = 4

Редакционная коллегия:

АДЕКЕНОВ Сергазы Мынжасарович (заместитель главного редактора), доктор химических наук, профессор, академик НАН РК, директор Международного научно-производственного холдинга «Фитохимия» (Караганда, Казахстан) Н = 11

АГАБЕКОВ В ладимир Енокович (заместитель главного редактора), доктор химических наук, профессор, академик НАН Беларуси, почетный директор Института химии новых материалов (Минск, Беларусь) Н = 13

СТРНАД Мирослав, профессор, заведующий лабораторией института Экспериментальной ботаники Чешской академии наук (Оломоуц, Чехия) Н = 66

БУРКИТБАЕВ Мухамбеткали, доктор химических наук, профессор, академик НАН РК, Первый проректор КазНУ имени аль-Фараби (Алматы, Казахстан) Н = 11

ХОХМАНН Джудит, заведующий кафедрой Фармакогнозии Фармацевтического факультета Университета Сегеда, директор Междисциплинарного центра естественных наук (Сегед, Венгрия) Н = 38

РОСС Самир, доктор PhD, профессор Школы Фармации национального центра научных исследований растительных продуктов Университета Миссисипи (Оксфорд, США) Н = 35

ХУТОРЯНСКИЙ Виталий, доктор философии (Ph.D, фармацевт), профессор Университета Рединга (Рединг, Англия) Н = 40

ТЕЛЬГАЕВ Багдат Бурханбайулы, доктор технических наук, профессор, член-корреспондент НАН РК, Министерство Индустрии и инфраструктурного развития Республики Казахстан (Алматы, Казахстан) Н = 13

ФАРУК Асана Дар, профессор колледжа Восточной медицины Хамдарда аль-Маджида, факультет Восточной медицины университета Хамдарда (Карачи, Пакистан) Н = 21

ФАЗЫЛОВ Серик Драхметович, доктор химических наук, профессор, академик НАН РК, заместитель директора по научной работе Института органического синтеза и углехимии (Караганда, Казахстан) Н = 6

ЖОРОБЕКОВА Шарипа Жоробековна, доктор химических наук, профессор, академик НАН Кыргызстана, Институт химии и химической технологии НАН КР (Бишкек, Кыргызстан) Н = 4

ХАЛИКОВ Джурабай Халикович, доктор химических наук, профессор, академик АН Таджикистана, Институт химии имени В.И. Никитина АН РТ (Душанбе, Таджикистан) Н = 6

ФАРЗАЛИЕВ Вагиф Меджид оглы, доктор химических наук, профессор, академик НАНА (Баку, Азербайджан) Н = 13

ГАРЕЛИК Хемда, доктор философии (Ph.D, химия), президент Отдела химии и окружающей среды Международного союза чистой и прикладной химии (Лондон, Англия) Н = 15

«Известия НАН РК. Серия химии и технологий».

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Собственник: Республиканское общественное объединение «Национальная академия наук Республики Казахстан» (г. Алматы).

Свидетельство о постановке на учет периодического печатного издания в Комитете информации Министерства информации и общественного развития Республики Казахстан № KZ66VPY00025419, выданное 29.07.2020 г.

Тематическая направленность: *органическая химия, неорганическая химия, катализ, электрохимия и коррозия, фармацевтическая химия и технологии.*

Периодичность: 4 раз в год.

Тираж: 300 экземпляров.

Адрес редакции: 050010, г. Алматы, ул. Шевченко, 28, оф. 219, тел.: 272-13-19

<http://chemistry-technology.kz/index.php/en/archiv>

© РОО Национальная академия наук Республики Казахстан, 2024

Адрес редакции: 050100, г. Алматы, ул. Кунаева, 142, АО «Институт топлива, катализа и электрохимии им. Д.В. Сокольского», каб. 310, тел. 291-62-80, факс 291-57-22, e-mail: orgcat@nursat.kz

Editor in chief:

ZHURINOV Murat Zhurinovich, doctor of chemistry, professor, academician of NAS RK, president of NAS RK, general director of JSC "Institute of fuel, catalysis and electrochemistry named after D.V. Sokolsky (Almaty, Kazakhstan) H = 4

Editorial board:

ADEKENOV Sergazy Mynzhasarovich (deputy editor-in-chief) doctor of chemical sciences, professor, academician of NAS RK, director of the international Scientific and production holding «Phytochemistry» (Karaganda, Kazakhstan) H = 11

AGABEKOV Vladimir Enokovich (deputy editor-in-chief), doctor of chemistry, professor, academician of NAS of Belarus, honorary director of the Institute of Chemistry of new materials (Minsk, Belarus) H = 13

STRNAD Miroslav, head of the laboratory of the institute of Experimental Botany of the Czech academy of sciences, professor (Olomouc, Czech Republic) H = 66

BURKITBAYEV Mukhambetkali, doctor of chemistry, professor, academician of NAS RK, first vice-rector of al-Farabi KazNU (Almaty, Kazakhstan) H = 11

HOHMANN Judith, head of the department of pharmacognosy, faculty of Pharmacy, university of Szeged, director of the interdisciplinary center for Life sciences (Szeged, Hungary) H = 38

ROSS Samir, Ph.D., professor, school of Pharmacy, national center for scientific research of Herbal Products, University of Mississippi (Oxford, USA) H = 35

KHUTORYANSKY Vitaly, Ph.D., pharmacist, professor at the University of Reading (Reading, England) H = 40

TELTAYEV Bagdat Burkhanbayuly, doctor of technical sciences, professor, corresponding member of NAS RK, ministry of Industry and infrastructure development of the Republic of Kazakhstan (Almaty, Kazakhstan) H = 13

PHARUK Asana Dar, professor at Hamdard al-Majid college of Oriental medicine. faculty of Oriental medicine, Hamdard university (Karachi, Pakistan) H = 21

FAZYLOV Serik Drakhmetovich, doctor of chemistry, professor, academician of NAS RK, deputy director for institute of Organic synthesis and coal chemistry (Karaganda, Kazakhstan) H = 6

ZHOROBEKOVA Sharipa Zhorobekovna, doctor of chemistry, professor, academician of NAS of Kyrgyzstan, Institute of Chemistry and chemical technology of NAS KR (Bishkek, Kyrgyzstan) H = 4

KHALIKOV Jurabay Khalikovich, doctor of chemistry, professor, academician of the academy of sciences of Tajikistan, institute of Chemistry named after V.I. Nikitin AS RT (Tajikistan) H = 6

FARZALIEV Vagif Medzhid ogly, doctor of chemistry, professor, academician of NAS of Azerbaijan (Azerbaijan) H = 13

GARELIK Hemda, PhD in chemistry, president of the department of Chemistry and Environment of the International Union of Pure and Applied Chemistry (London, England) H = 15

News of the National Academy of Sciences of the Republic of Kazakhstan. Series of chemistry and technology.

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Owner: RPA «National Academy of Sciences of the Republic of Kazakhstan» (Almaty).

The certificate of registration of a periodical printed publication in the Committee of information of the Ministry of Information and Social Development of the Republic of Kazakhstan No. **KZ66VPY00025419**, issued 29.07.2020.

Thematic scope: *organic chemistry, inorganic chemistry, catalysis, electrochemistry and corrosion, pharmaceutical chemistry and technology.*

Periodicity: 4 times a year.

Circulation: 300 copies.

Editorial address: 28, Shevchenko str., of. 219, Almaty, 050010, tel. 272-13-19

<http://chemistry-technology.kz/index.php/en/arhiv>

© National Academy of Sciences of the Republic of Kazakhstan, 2024

Editorial address: JSC «D.V. Sokolsky institute of fuel, catalysis and electrochemistry», 142, Kunayev str., of. 310, Almaty, 050100, tel. 291-62-80, fax 291-57-22, e-mail: orgcat@nursat.kz

NEWS OF THE NATIONAL ACADEMY OF SCIENCES OF THE REPUBLIC OF KAZAKHSTAN
SERIES CHEMISTRY AND TECHNOLOGY
ISSN 2224–5286
Volume 2. Number 459 (2024), 191–208
<https://doi.org/10.32014/2024.2518-1491.232>

© R. Shulen¹, D. Makhayeva^{1*}, D. Kazybayeva¹, G. Irmukhametova¹,
G. Mun^{1,2}, 2024

¹al-Farabi Kazakh National University, Almaty, Kazakhstan;

²The National Engineering Academy of the Republic of Kazakhstan, Almaty,
Kazakhstan.

E-mail: danelya.1993@gmail.com

CREATING BIODEGRADABLE DOSAGE FORMS BASED ON PENTAERYTHRITOL TETRAACRYLATE AND TETRAKIS(3-MERCAPTOPROPIONATE) PENTAERYTHRITOL

R. Shulen — Master of Engineering Science, junior researcher, al-Farabi Kazakh National University, Almaty, Kazakhstan

E-mail: shulen_ruslan@mail.ru, <https://orcid.org/0000-0001-6822-3057>;

D. Makhayeva — PhD, senior researcher, al-Farabi Kazakh National University, Almaty, Kazakhstan

E-mail: danelya.1993@gmail.com, <https://orcid.org/0000-0003-1250-9587>;

D. Kazybayeva — PhD, senior researcher, al-Farabi Kazakh National University, Almaty, Kazakhstan

E-mail: diara_92@mail.ru, <https://orcid.org/0000-0001-6822-3057>;

G. Irmukhametova — Candidate of Chemical Sciences, Associate Professor, al-Farabi Kazakh National University, Almaty, Kazakhstan

E-mail: galiya.irm@gmail.com, <https://orcid.org/0000-0002-1264-7974>;

G. Mun — Doctor of Chemical Sciences, Professor, al-Farabi Kazakh National University, academician of NEA RK, Almaty, Kazakhstan

E-mail: mungrig@yandex.ru, <https://orcid.org/0000-0002-4984-7937>.

Abstract. Of particular interest to scientists is creating ways to ensure continuous delivery of necessary components for treating specific diseases. Some diseases require a consistent supply of essential elements for treatment. Often, conventional forms of medication, such as tablets or capsules, might not get adequately absorbed by the body and end up being eliminated without much effect. To address this, the use of polymer-based dosage forms that degrade in the body, releasing medicinal substances gradually, extends their impact. Employing polymer carriers offers the advantage of targeting precise areas within the body, enhancing the efficient utilisation of the drug substance. Pentaerythritol tetraacrylate and pentaerythritol tetrakis (3-mercapto propionate) (PETA-PEMP) based gels form through thiol-ene click polymerisation mechanisms. The functional groups present in these gels enable the development of materials that can degrade within diverse biological and physiological settings alongside improved mucoadhesive characteristics. These attributes promise future applications in targeted delivery systems for various medical substances. This study marks the initial creation of cross-linked polymer gels using varying compositions of PETA and PEMP. The major physicochemical properties of gels were determined

through sol-gel analysis, IR and Raman spectroscopy, and optical and scanning electron microscopy. Results revealed that gels containing an excess of PETA initially showcased a porous structure, while higher proportions of PEMP monomers led to developing a denser network structure. The degradation behaviour of these gels in different environments was also investigated. Specifically, gels placed in enzyme solutions exhibited immediate degradation, whereas degradation in hydrogen peroxide solutions underwent a swelling stage before breaking down.

Keywords: biodegradable polymers, drug delivery systems, gels, thiol-ene polymerisation, biodegradation

Acknowledgements. *The work was financially supported by the Ministry of Science and Higher Education of the Republic of Kazakhstan, program-targeted financing out of competitive procedures for 2023–2025. Project No. (BR21882289), entitled «Development and Implementation of Technological Aspects of the Production and Industrial Application of Functional Carbon-silicon Fillers».*

© Р. Шулен¹, Д. Махаева^{1*}, Д. Казыбаева¹, Г. Ирмухаметова¹, Г.А. Мун^{1,2},
2024

¹ әл-Фараби атындағы Қазақ ұлттық университеті, Алматы, Қазақстан;

² The National Engineering Academy of the Republic of Kazakhstan, Almaty, Kazakhstan.

E-mail: danelya.1993@gmail.com

ТЕТРААКРИЛАТ ПЕНТАЭРИТРИТОЛ ЖӘНЕ ТЕТРАКИС(3-МЕРКАПТОПРОПИОНАТ) ПЕНТАЭРИТРИТОЛНЕГІЗІНДЕ БИОДЕГРАДАЦИЯЛАНАТЫН ДӘРІЛІК ФОРМАЛАРДЫ АЛУ

Шулен Р. — техника ғылымдарының магистрі, кіші ғылыми қызметкер, әл-Фараби атындағы Қазақ ұлттық университеті, Алматы, Қазақстан

E-mail: shulen_ruslan@mail.ru, <https://orcid.org/0000-0001-6822-3057>;

Махаева Д.Н. — PhD, аға ғылыми қызметкер, әл-Фараби атындағы Қазақ ұлттық университеті, Алматы, Қазақстан

E-mail: danelya.1993@gmail.com, <https://orcid.org/0000-0003-1250-9587>;

Казыбаева Д.С. — PhD, аға ғылыми қызметкер, әл-Фараби атындағы Қазақ ұлттық университеті, Алматы, Қазақстан

E-mail: diara_92@mail.ru, <https://orcid.org/0000-0001-6822-3057>;

Ирмухаметова Г.С. — х. ғ. к., қауымдастырылған профессор, әл-Фараби атындағы Қазақ ұлттық университеті, Алматы, Қазақстан

E-mail: galiya.irm@gmail.com, <https://orcid.org/0000-0002-1264-7974>;

Мун Г.А. — х. ғ. д., профессор, Қазақ ұлттық университеті.әл-Фараби, ҚР ҰИА академигі, Алматы, Қазақстан

E-mail: mungrig@yandex.ru, <https://orcid.org/0000-0002-4984-7937>.

Аннотация. Белгілі бір ауруларды емдеуге қажетті компоненттерді үздіксіз жеткізуді қамтамасыз ету жолдарын құру зерттеушілерді ерекше қызықтырады. Кейбір аурулар емдеу үшін қажетті элементтердің тұрақты

жеткізілуін талап етеді. Көбінесе таблеткалар немесе капсулалар сияқты дәстүрлі дәрі-дәрмектер денеге дұрыс сіңбейді және көп әсер етпестен жойылады. Ағзада ыдырауы мүмкін, дәрілік заттарды шығаратын полимерлі дәрілік формаларды қолдану олардың ағзаға ұзақ әсер етуіне ықпал етеді. Полимерлі тасымалдаушыларды қолданудың артықшылығы дәрілік субстанцияны тиімді пайдалануды жеңілдететін дененің белгілі бір аймақтарына бағытталған. Пентаэритритол тетраакрилат (ПЭТА) және пентаэритритол тетраакис (3-меркаптопропионат) (ПЭМП) мономерлеріне негізделген гельдердің түзілуі тиолды-басу (тиолен-клик) полимерлеу механизмдеріне негізделген. ПЭТА-ПЭМП негізіндегі гельдерде функционалдық топтардың болуына байланысты әртүрлі биологиялық және физиологиялық ортада ыдырай алатын жақсартылған шырышты жабысқақ қасиеттері бар материалдарды алуға болады. Бұл қасиеттер кейінірек медицинада кеңінен қолданылатын әртүрлі заттардың мақсатты жеткізу жүйелерінде қолданылуы мүмкін. Бұл зерттеуде әртүрлі ПЭТА-ПЭМП негізіндегі композицияларды қолдану арқылы айқаспалы полимерлі гельдер дайындалды. Гельдердің негізгі физика-химиялық қасиеттері золь-гельді талдау, ИҚ және РАМАН спектроскопиясы, сонымен қатар оптикалық және сканерлеуші электронды микроскопия арқылы анықталды. Нәтижелер құрамында артық ПЭТА бар гельдердің кеуекті құрылымы бар екенін көрсетті, ал ПЭМП құрамының жоғарылауы тығыз торлы құрылымның дамуына әкеледі. Бұл гельдердің әртүрлі орталарда ыдырауы да зерттелді. Атап айтқанда, фермент ерітінділеріне салынған гельдер бірден ыдырауды көрсетті, ал сутегі асқын тотығы ерітінділеріндегі ыдырау одан алдын ісіну сатысынан өтті.

Түйін сөздер: биологиялық ыдырайтын полимерлер, дәрілік заттарды жеткізу жүйелері, тиол-эн полимерленуі, биодеградация

© Р. Шулен¹, Д. Махаева^{1*}, Д. Казыбаева¹, Г. Ирмухаметова¹, Г.А. Мун^{1,2},
2024

¹Казахский национальный университет им. аль-Фараби, Алматы, Казахстан;

²Национальная инженерная академия наук РК, Алматы, Казахстан.
E-mail: danelya.1993@gmail.com

ПОЛУЧЕНИЕ БИОДЕГРАДИРУЕМЫХ ЛЕКАРСТВЕННЫХ ФОРМ НА ОСНОВЕ ТЕТРААКРИЛАТА ПЕНТАЭРИТРИТОЛА И ТЕТРАКИС(3- МЕРКАПТОПРОПИОНАТА) ПЕНТАЭРИТРИТОЛА

Шулен Р. — магистр технических наук, младший научный сотрудник, Казахский национальный университет им.аль-Фараби, Алматы, Казахстан

E-mail: shulen_ruslan@mail.ru, <https://orcid.org/0000-0001-6822-3057>;

Махаева Д.Н. — PhD, старший научный сотрудник, Казахский национальный университет им.аль-

Фараби, Алматы, Казахстан

E-mail: danelya.1993@gmail.com, <https://orcid.org/0000-0003-1250-9587>;

Казыбаева Д.С. — PhD, старший научный сотрудник, Казахский национальный университет им.аль-Фараби, Алматы, Казахстан

E-mail: diara_92@mail.ru, <https://orcid.org/0000-0001-6822-3057>;

Ирмухаметова Г.С. — к.х.н., ассоциированный профессор, Казахский национальный университет им.аль-Фараби, Алматы, Казахстан

E-mail galiya.irm@gmail.com, <https://orcid.org/0000-0002-1264-7974>;

Мун Г.А. — д.х.н., профессор, Казахский национальный университет им.аль-Фараби, академик НИА РК, Алматы, Казахстан

E-mail: mungrig@yandex.ru, <https://orcid.org/0000-0002-4984-7937>.

Аннотация. Особый интерес исследователей представляет создание способов обеспечения непрерывной доставки необходимых компонентов для лечения конкретных заболеваний. Некоторые заболевания требуют постоянного снабжения необходимыми элементами для лечения. Часто обычные формы лекарств, такие как таблетки или капсулы не усваиваются организмом должным образом и в итоге выводятся без особого эффекта. Применение полимерных лекарственных форм, способных деградировать в организме, высвобождая лекарственные вещества, способствует их пролонгированному действию на организм. Преимуществом использования полимерных носителей является нацеливание на конкретные участки организма, что способствует эффективному использованию лекарственного вещества. Образование гелей на основе мономеров пентаэритритол тетраакрилат (ПЭТА) и пентаэритритол тетраакис (3-меркаптопропионат) (ПЭМП) основано на механизмах тиол-клик полимеризации. Благодаря присутствию функциональных групп в гелях на основе ПЭТА-ПЭМП можно получать материалы с улучшенными мукоадгезивными свойствами, способные разлагаться в различных биологических и физиологических средах. Данные свойства в дальнейшем могут быть использованы в системах направленной доставки различных веществ, имеющих широкое распространение в медицине. В данном исследовании были получены шитые полимерные гели с использованием различных композиций на основе ПЭТА-ПЭМП. Основные физико-химические свойства гелей определяли методами золь-гель анализа, ИК- и РАМАН спектроскопии, а также оптической и сканирующей электронной микроскопиями. Результаты показали, что гели, содержащие избыток ПЭТА, имеют пористую структуру, в то время как увеличение содержания ПЭМП приводит к развитию более плотной сетчатой структуры. Также была исследована деградация этих гелей в различных средах. В частности, гели, помещенные в растворы ферментов, демонстрировали немедленную деградацию, тогда как деградация в растворах перекиси водорода проходила через стадию набухания перед разрушением.

Ключевые слова: биodeградируемые полимеры, системы доставки лекарственных веществ, тиол-ен полимеризация, биodeградация

Introduction

Biodegradable materials are utilised in various industries, including packaging, agriculture, and medicine. These materials are categorised into two types: synthetic and natural biodegradable polymers. Synthetic polymers are made from petroleum-based raw materials, which are non-renewable. In contrast, natural polymers are derived from renewable biological resources. Generally, natural polymers are viewed as having fewer benefits

than synthetic polymers (Mukherjee et al., 2023: 112068).

Biodegradation is how enzymes or other living organisms break down materials. First of all, polymers undergo fragmentation via abiotic processes involving microbial breakdown. Subsequently, microorganisms assimilate these polymer fragments, leading to their mineralisation. The biodegradability of a polymer depends not only on its inherent nature but also on its chemical composition and environmental conditions. Various mechanisms and techniques exist to assess the biodegradation of polymers. Additionally, the mechanical properties of biodegradable materials are influenced by factors such as chemical composition, manufacturing methods, storage conditions, processing, ageing, and usage patterns (Samir et al., 2022: 7).

The authors (Zhang et al., 2021: 116) reviewed biodegradable polymers utilised in biomaterials. For a polymer to be effective as a biomaterial, it must exhibit three essential properties: biocompatibility, bioabsorbability, and mechanical strength. Natural polymers, such as proteins or polysaccharides, which degrade enzymatically, have been prevalent in biomedical applications for thousands of years. In contrast, synthetic biodegradable polymers have been used for about fifty years. These polymers are employed in various applications, including surgical implants for vascular or orthopedic procedures and simple membranes. Biodegradable polyesters are particularly notable for their durability and controlled degradation rates, making them extensively used as porous structures in tissue engineering, especially for constructing scaffolds. Additionally, biodegradable polymers serve as implantable matrices for controlled drug release within the body and as absorbable suture materials (Panchal et al., 2020: 4370).

Natural polymers typically degrade within biological systems through a process involving hydrolysis followed by oxidation. Therefore, when designing synthetic biodegradable materials, a primary focus is on incorporating hydrolysable linkages such as amide, ester, urea, and urethane groups. Enzymes that cleave peptides often target specific sites adjacent to these groups. Hydrophobic surfaces are less conducive to enzymatic reactions, primarily in aqueous environments. Interestingly, the fastest degradation occurs in polymers containing hydrophobic and hydrophilic segments (Kim et al., 2023: 9916).

Other considerations involve the accessibility of polymer chains to enzymes. Synthetic polymers with short repeat units and regular structures tend to pack tightly, making hydrolysable groups less accessible to enzymes. Experiments with partially crystalline materials show that amorphous regions decompose first, with decomposition rates influenced by the size, shape, and number of crystallites present. Although cross-linking reduces crystallinity, it does not improve degradation rates because the cross-links themselves restrict enzyme access. Conversely, polymers with long repeating chain stretches have a less regular structure and are more susceptible to degradation. Therefore, aliphatic chains are more prone to biodegradation than aromatic chains (Chereddy et al., 2016: 223).

The decomposition of polymers, whether *in vitro* or *in vivo*, is affected by numerous factors. These include the preparation method, the presence of low molecular weight compounds such as monomers, oligomers, or catalysts, and the polymer's size, shape, and morphology. Polymer physical and chemical properties influence the degradation process (Hermengildo et al., 2022: 111197). Studies indicate that polymers with lower molecular weight, greater hydrophilicity, and higher amorphousness degrade more rapidly. Similarly, copolymers with higher glycolide content show shorter degradation times.

Copolymers can experience either surface erosion or volumetric erosion, depend-

ing on the conditions, with volumetric erosion typically being the main degradation pathway. The biodegradation process of polymers involves the random cleavage of ester bonds within the polymer backbone, occurring uniformly across the entire material. A proposed three-phase mechanism outlines the degradation stages. Initially, there is a substantial decrease in the polymer's molecular weight without significant mass loss, which leads to the formation of soluble monomer products. These soluble monomers originate from soluble oligomeric fragments, marking the beginning of the degradation process. Ultimately, this sequence culminates in the complete breakdown and degradation of the polymer into simpler, potentially biocompatible components. (Mirjafari, 2018: 2945).

Over the past decade, thiol-ene click polymerisation has been extensively studied (Li et al., 2019: 485; Gregoritz et al., 2015: 439). This reaction offers several advantages: it occurs under mild conditions, yields high product quantities, and produces harmless by-products (Liu et al., 2017: 6182; Ki et al., 2014: 9668). Recently, thiol polymers have gained attention in biomedical applications, particularly as gels, due to their ability to tailor physical properties like biodegradability, drug release kinetics, swelling behaviour, and other crucial characteristics. (Machado et al., 2017: 201).

In thiol-ene click polymerisation, one of the reactants typically contains thiol groups, while the other contains multiple bonds (Štorha et al., 2013: 12275). The main objective of this work is to create biodegradable drug forms using PETA and PEMP through thiol-ene polymerisation and then assess their physicochemical properties and biodegradability. This method enables the rapid and straightforward production of new composite materials with enhanced properties. Due to the functional groups present in PETA-PEMP-based gels, it is possible to develop materials that decompose in various biological and physiological environments with improved mucoadhesive properties. These properties can be utilised in targeted delivery systems for various substances widely used in medicine.

Materials and methods

Materials

Pentaerythritol tetraacrylate, pentaerythritol tetrakis 3-mercaptopropionate (95 %), porcine liver esterase, N, N-Dimethylformamide (DMF) obtained from Sigma Aldrich (USA), acetone, Phosphate buffer (fixanal, pH 6.86), salts for phosphate buffer solution (NaCl, KCl, Na₂HPO₄ и KH₂PO₄) ReactiveKhimSnab (Russian Federation), hydrogen peroxide (3 % solution) from «DosFarm» (Republic of Kazakhstan). All reagents were of analytical grade and were used without additional purification.

Synthesis of PETA-PEMP gels in the presence of DMF solvent

Gels with varying compositions ([PETA-PEMP] ratios of 3:1, 2:1, 1:1, 1:2, and 1:3 wt.%) were synthesised in sealed glass vessels. PETA and PEMP monomers were mixed in a DMF solvent with constant magnetic stirring for the first hour. Depending on the composition, a cross-linked structure formed within 1–2 hours. The resulting gels were then washed in DMF for 1 hour, in acetone for 3 hours (with 3 changes of acetone), and in water for 24 hours (with about 10 water changes). The washed polymers were dried in a vacuum oven at room temperature.

Physicochemical research methods

The kinetics and extent of swelling were investigated using the gravimetric method. After measuring the mass of the washed and dried gel, each sample was immersed in a solution, and its mass was recorded using an analytical balance. Measurements were initially taken every 15 minutes and later every 30 minutes until the sample's mass stabilised.

This analysis used distilled water, isotonic solutions, and buffer solutions. The *degree of swelling* (α) of the gels was calculated using formula (1).

$$\alpha = \frac{m_x - m_0}{m_0},$$

where m_x is the mass of the swollen gel at a certain point in time, g; m_0 is the initial mass of the gel, g.

The gels underwent sequential treatments for the sol-gel analysis: they were immersed in a DMF solution for 1 hour, followed by 3 hours in acetone, and then soaked in water for 24 hours. Subsequently, the washed gels were dried in a vacuum oven. The yield of the gel fraction (G %) was determined using formula (2).

$$G\% = \frac{m_{\text{dried}}}{m_{\text{synth}}} * 100 \%,$$

where m_{dried} – the mass of washed and dried gel, g; m_{synth} – the mass of the synthesised and dried sample, g. The yield of the *sol fraction* (S%) was calculated using the formula (3):

$$S \% = 100 \% - G \%,$$

where G % is the percentage of the gel fraction, %.

The physical and mechanical characteristics of the synthesised samples were analysed as follows:

The mass of the synthesised and washed dried gels was determined using Sartorius BP 121S analytical balances from Germany, which provide accuracy up to 0.0001 g. The samples were dried in a Binder VD 115 vacuum drying oven (Germany).

To confirm the chemical composition, IR spectroscopy was performed using a Vertex 70V Bruker IR Fourier spectrometer (USA), which covers wavelengths from 4000 to 500 cm^{-1} . Raman spectroscopy was conducted using a Solver Spectrum setup (Russia) on selected samples with a diameter of 0.5 mm.

Scanning electron microscopy (SEM) was employed with a Quanta 200i 3D system (USA) for structural analysis. Samples were freeze-dried before analysis.

Optical analysis of the gels was carried out using a Leica DM 6000M microscope from Sweden.

These methods were utilised to assess the synthesised samples' physical properties and determine mechanical behaviours using a TAXT Texture Analyzer device (UK) in a compression mode.

Study of the degradation ability of synthesised gels based on PETA-PEMP

The degradation ability of the synthesised 3:1 PETA-PEMP gels was investigated using three different environments: a buffer solution at pH 7.4, an enzyme solution, and hydrogen peroxide solutions. For hydrogen peroxide degradation studies, solutions of varying concentrations (0.1 %, 0.5 %, 1 %, 2 %, and 3 %) were employed. All experiments were conducted in sealed plastic beakers at a constant temperature of 37 ° C in a water bath, with intermittent stirring. The assessment of degradability properties involved multiple parallel experiments. The degree of degradation (DD) was evaluated using the gravimetric method until the sample mass stabilised and then calculated using formula (4).

$$DD = (m_0 - m_x)/m_0,$$

where m_x is the mass of the gel at a certain point in time, g; m_0 is the initial mass of the gel, g.

Results and discussion

Synthesis of gels based on PETA-PEMP

In this study, gels based on PETA-PEMP were synthesised using thiol-ene click polymerisation. Different ratios of components in the initial monomer mixture were used: 3:1, 2:1, 1:1, 1:2, and 1:3 weight per cent, in the presence of a DMF solvent (50 % solvent and 50 % monomers). Figure 1 illustrates the reaction scheme for forming a cross-linked PETA-PEMP structure. The interaction between monomers and the formation of covalent bonds occurs through functional groups, specifically the double bonds in PETA and the thiol groups in PEMP. When PETA is in the monomer mixture, gels with numerous double bonds are produced, whereas an excess of PEMP results in gels rich in thiol groups. The formation of these structures was confirmed through IR and Raman spectroscopy, the details of which are discussed later.




Figure 1 - Synthesis reaction scheme of gels based on PETA-PEMP.

Characteristics of gels based on PETA-PEMP

To investigate the yield of products based on the initial ratios of PETA-PEMP monomers, sol-gel analysis was conducted on the synthesised samples. Figure 2 and Table 1 depict the outcomes of this analysis.




Figure 2 - Dependence of the sol and gel fraction yield of PETA-PEMP gel on the composition of the initial monomer mixture.

According to Table 1, the highest yield of the gel fraction occurs with the 1:1 composition, where the initial PETA and PEMP monomers are present in equal proportions. In contrast, lower yields are observed at ratios of 3:1 and 1:3 because one of the components is present in excess or deficiency. When there is an excess of PETA or PEMP, all available molecules of the other component become fully bound, leaving unreacted monomers that are subsequently washed out during the washing process. Interestingly, the yield of the gel fraction at the PETA-PEMP ratio of 1:3 is higher than that at 3:1. This difference is attributed to the denser structure of gels formed with excess PEMP.

Table 1
Results of sol-gel analysis of the obtained PETA-PEMP gels

Composition of initial monomer mixture, wt. %	№	[3:1]	[2:1]	[1:1]	[1:2]	[1:3]
Gel fraction, %	1	48,65	68,94	79,30	77,09	69,71
	2	47,32	69,71	79,58	77,04	69,91
	3	48,90	70,23	79,27	77,63	69,25
	Average	48,29	69,63	79,38	77,25	69,62
Sol fraction, %	1	51,35	31,06	20,70	22,91	30,29
	2	52,68	30,29	20,42	22,96	30,09
	3	51,10	29,77	20,73	22,37	30,75
	Average	51,71	30,37	20,62	22,75	30,38

This study examined gels synthesised from PETA-PEMP using various physico-chemical methods. The swelling characteristics of these gels were evaluated in three different solutions: distilled water, isotonic solution, and a buffer solution with pH 6.86. Figure 2 (A, B, C) illustrates graphs depicting the degree of swelling over time. The gels exhibited the highest rate of swelling in the isotonic solution. The data collected determined the equi-

librium degree of swelling in these gels across different compositions (Figure 3). In an isotonic solution, the swelling capacity of the gels remained relatively consistent regardless of the composition. Conversely, in the buffer solution at pH 6.86, gels with equal proportions of PETA and PEMP in the initial monomer mixture showed the lowest degree of swelling, indicating a denser cross-linked network as supported by the gel fraction analysis. As the PEMP content increased, the swelling ability of the gels also increased, potentially influenced by the presence of -SH groups within the network. No distinct trends were observed in the influence of composition on the equilibrium degree of swelling in gels immersed in distilled water.




Figure 3 - Dependence of the swelling rate of gels based on PETA-PEMP on the composition in distilled water (A), isotonic (B), and buffer (C) solutions.




Figure 4 - Dependence of the equilibrium degree of swelling on the composition of gels based on PETA-PEMP in distilled water (1), in isotonic (2) and buffer (3) solutions.

Figure 5 displays the IR spectra of synthesised gels composed of PETA and PEMP in ratios of 3:1, 1:1, and 1:3 wt.%. A prominent peak in the 1745–1725 cm^{-1} range in all three spectra indicates the presence of C=O functional groups. A broader peak with lower intensity in the 1180–1140 cm^{-1} region suggests the presence of (-C-O-C-) groups within the gel composition. The absorption band observed in the 690–640 cm^{-1} region indicates the presence of (-C-S) functional groups in the polymer structure. Additionally, the peak at 1635 cm^{-1} signifies the presence of (-C=C) groups, while a small peak in the 1475–1450 cm^{-1} region indicates the presence of (=CH₂) groups.

It's important to note that detecting -SH groups typically require Raman spectroscopy due to their weak signal in IR spectra. This study employed Raman spectroscopy to provide a more detailed analysis of the polymer structure. The resulting Raman spectra are presented in Figure 6.




Figure 5 - IR spectra of PETA-PEMP gels of ratios [3:1] (1), [1:1] (2), and [1:3] (3).

Figure 6 illustrates the outcomes of Raman spectroscopy conducted on PETA-PEMP gels. The analysis revealed distinctive bands corresponding to specific chemical bonds within the polymer structure. The bands observed between 700–650 cm^{-1} are attributed to vibrations of the C-S bond, indicating its presence in the polymer network. At 2590–2550 cm^{-1} , a band was identified that confirms the existence of SH groups, crucial for understanding the gel's composition and cross-linking density.

Furthermore, the band observed at 525 cm^{-1} signifies the presence of S-S bonds, suggesting an excess of PEMP in the gel composition, particularly evident in the 1:3 wt.% ratio. Bands around 1680 cm^{-1} were associated with vibrations of the $-\text{CH}=\text{CH}_2$ bond, confirming the presence of multiple bonds characteristic of gels with an excess of PETA (3:1 wt.%).

These findings from Raman spectroscopy provide detailed insights into the chemical structure and composition variations across different ratios of PETA-PEMP gels synthesised in this study.




Figure 6 - Raman spectra of gels based on PETA-PEMP of ratios [3:1], [1:1], and [1:3].

Figure 7 (A, B, C) presents optical microscopy images used to study the structure and morphology of gels composed of PETA-PEMP. Samples with a diameter of 3 mm were chosen and pre-dried in a vacuum drying cabinet prior to analysis. The images indicate that gels with excess PETA exhibit a uniform structure. However, as the concentration of PETA increases in the initial monomer mixture, there is an observable emergence of crystalline supramolecular structures within the gels.




Figure 7 - Microphotographs of gels based on PETA-PEMP of ratios 3:1 (A), 1:1 (B), and 1:3 (C).

SEM was employed to conduct a detailed study of the gels' structure and morphology. The results, displayed in Figure 8 (A, B, C), reveal notable differences based on the composition of PETA-PEMP. Gels with an excess of PETA exhibit a more porous structure, as observed in the images. This porous nature correlates with the gels' swelling properties, where higher concentrations of PETA lead to increased degrees of swelling.

Conversely, as the concentration of PEMP monomers increases, a denser network structure becomes evident in the gels. This densification is reflected in the SEM images, indicating a tighter arrangement of polymer chains and reduced porosity compared to gels with excess PETA.




Figure 8 - SEM micrographs of gels based on PETA-PEMP of ratios 3:1 (A), 1:1 (B), and 1:3 (C).

The mechanical strength of the synthesised gels based on PETA-PEMP was evaluated through compression testing. Figure 9 illustrates that these gels exhibit significant strength and elasticity. The results evidently show the impact of varying ratios of initial monomers on the gels' strength. Gels with a higher proportion of PEMP show a slight reduction in elasticity but an increase in overall strength. This effect is likely due to the increased number of cross-links formed, which restricts the flexibility and movement of the polymer chains within the network.

On the other hand, gels with an excess of PETA in the initial mixture demonstrate higher elasticity. This elasticity can be attributed to the presence of a greater number of multiple bonds in their structure, which allows for more flexibility and resilience under compression.




Figure 9 - Graph of stress versus strain for gels based on PETA-PEMP of different ratios.

Based on the mechanical analysis data, each sample’s elastic modulus was calculated and presented in Table 2. The elastic modulus was determined by calculating the tangent of the slope of the initial linear portion of the compression curve. Increasing the concentration of PEMP in the gel composition was observed to contribute to an increase in the elastic modulus. This indicates that gels with higher proportions of PEMP exhibit greater stiffness and resistance to deformation under compression.

Table 2

Values of elastic modulus for gels of PETA-PEMP compositions at different ratios of initial monomers

Ratios of initial monomers	Modulus of elasticity, Pa
3:1	7727
2:1	18633
1:1	29518
1:2	34519
1:3	11670

Study of the degradation ability of synthesised gels based on PETA-PEMP

An essential criterion for using polymers for drug delivery systems in medicine is their ability to biodegrade within the body. Biodegradation ensures that once the active substance in the medication is depleted, the polymer carrier can be naturally broken down and eliminated from the body, preventing any unnecessary accumulation. This process is crucial for sustained drug release and reducing the frequency of medication intake.

In this study, the biodegradation of the synthesised PETA-PEMP gels was investigated using a phosphate buffer solution containing pig liver esterase enzymes. Esterase enzymes catalyse the hydrolysis of ester bonds, which are common in organic compounds found in the human body. The experimental results, depicted in Figure 3.3.1, indicate that the gels began to degrade immediately in the presence

of enzymes.

When analysing the degradation of PETA-PEMP gels in a buffer solution simulating physiological fluid (pH = 7.4), no significant weight loss was observed. However, swelling of the gels was noted, suggesting a response to the environment similar to that of human bodily fluids. This underscores the potential biocompatibility of these gels as drug carriers in medical applications.




Figure 10 - Dependence of the degree of destruction of PETA-PEMP gels at a ratio of 3:1 wt.% on time in various solutions.

In areas of inflammation and oncological tumour sites, hydrogen peroxide is naturally released in small quantities. This release serves a dual role: it helps prevent infection and signals to attract immune cells, such as leukocytes, to the affected area (Shuler, Kazybayeva, 2021: 29).

This study investigated how gels based on PETA-PEMP degrade in solutions with varying concentrations of hydrogen peroxide. The experiment continued until the mass of the gels stabilised. Based on the results, a graph was generated to illustrate how the degree of degradation of the gels changes over time in these solutions (Figure 10). The graph indicates that higher concentrations of hydrogen peroxide accelerate the degradation process. The degradation primarily involved swelling of the gels before reaching a stable mass.

These findings underscore the potential of PETA-PEMP gels for applications where controlled degradation in response to hydrogen peroxide levels could be advantageous, such as in localised treatments for inflammatory conditions or in targeted drug delivery systems.

Conclusion

In this research, gels were synthesised using PETA and PEMP monomers in various ratios in the presence of DMF solvent. The synthesised gels underwent comprehensive characterisation using multiple analytical methods. Sol-gel analysis determined the yields of the sol and gel fractions, providing insights into the polymer network formation. The water absorption capacity of the gels was evaluated by assessing their degrees of swelling in different media.

Structural analysis using IR and Raman spectroscopy revealed distinctive vibrations in the spectra of gels with an excess of PEMP, indicating the presence of -SH groups. Morphological studies conducted via optical and scanning electron microscopy highlighted those gels with excess PETA exhibited a more porous structure, whereas those with excess PEMP showed a denser morphology. Mechanical testing using compression mode demonstrated that gels enriched with PETA were more elastic and resilient, whereas those with more PEMP were stronger and harder. The degradation behaviour of the synthesised gels was investigated in buffer solutions with pH=7.4, enzyme solutions, and hydrogen peroxide solutions of varying concentrations. No degradation was observed in buffer solutions, whereas enzymatic degradation with esterase and degradation in hydrogen peroxide solutions showed distinct effects. The concentration and type of H₂O₂ solution significantly influenced the rate and extent of degradation of the PETA-PEMP gels.

Overall, these findings contribute to understanding how the composition of PETA and PEMP monomers affects the properties and degradation behaviour of the synthesised gels, which is crucial for their potential applications in controlled drug delivery and biomedical devices.

REFERENCES

Cheredy K.K., Vandermeulen G. and Pr at V. (2016). PLGA based drug delivery systems: Promising carriers for wound healing activity. *Wound Rep and Reg.* — 24. — 223–236. — <https://doi.org/10.1111/wrr.12404>.

Kim M.S., Chang H. et.al. (2023). A review of biodegradable plastics: Chemistry, Applications, Properties, and Future Research Needs. *Chemical Reviews.* — 123 (16). — 9915–9939. — <https://doi.org/10.1021/acsomega.9b04422>.

Ki C., Lin T., Korc M., Lin C. (2014). Thiol-ene hydrogels as desmoplasia-mimetic matrices for modeling pancreatic cancer cell growth, invasion, and drug resistance. *Biomaterials.* — 35. — 9668–9677. — <https://doi.org/10.1016/j.biomaterials.2014.08.014>.

Kazybayeva D.S., Irmukhametova G.S., Khutoryanskiy V.V. (2022). Thiol-Ene “Click Reactions” as a Promising Approach to Polymer Materials. *Polym. Sci. Ser. B.* — 64. — 1–16. — <https://doi.org/10.1134/S1560090422010055>.

Kazybayeva D.S., Irmukhametova G.S., Khutoryanskiy V.V. (2021). Synthesis of hydrolytically and oxidation-responsive networks using thiol-ene “click” chemistry with pentaerythritol tetrakis(3-mercaptopropionate) and tri/tetra-acrylates. *Polym Adv Technol.* — 32. — 2682–2689. — <https://doi.org/10.1002/pat.5147>.

Hermenegildo B., Meira R.M., Correia D.M., et.al. (2022). Poly(lactic-co-glycolide) based biodegradable electrically and magnetically active microenvironments for tissue regeneration applications. *Eur. Polym. J.* — 171. — 111197. — <https://doi.org/10.1016/j.eurpolymj.2022.111197>.

Li P., Wang X., Zhao Y. (2019). Click chemistry as a versatile reaction for construction and modification of metal-organic frameworks. *Coord. Chem. Rev.* — 380. — 484–518. — <https://doi.org/10.1016/j.ccr.2018.11.006>.

Liu Y., Hou W., Sun H., et al. (2017). Thiol-ene click chemistry: a biocompatible way for orthogonal bioconjugation of colloidal nanoparticles. *Chem Sci.* — 8. — 6182–6187. — <https://doi.org/10.1039/c7sc01447c>.

Mukherjee C., Varghese D., Krishna J., et.al. (2023). Recent advances in biodegradable polymers – Properties, applications and future prospects. *Eur. Polym. J.* — 192. — 112068. — <https://doi.org/10.1016/j.eurpolymj.2023.112068>.

Mirjafari A. (2018). Ionic liquid syntheses via click chemistry: expeditious routes toward versatile functional materials. *Chem. Commun.* — 54. — 2944–2961. — <https://doi.org/10.1039/C8CC00372F>.

Machado T.O., Sayer C., Araujo P.H.H. (2017). Thiol-ene polymerisation: A promising technique to obtain novel biomaterials *Eur. Polym. J.* — 86. — 200–215. — <https://doi.org/10.1016/j.eurpolymj.2016.02.025>.

Zhang J., Zhan P., Tian H. (2021). Recent updates in the polysaccharides-based Nano-biocarriers for drugs delivery and its application in diseases treatment: A review. *Int. J. Biol. Macromol.* — 182. — 115–28. —

<https://doi.org/10.1016/j.ijbiomac.2021.04.009>.

Panchal S.S., Vasava D.V. (2020). Biodegradable Polymeric Materials: Synthetic Approach. ACS Omega. — 5 (9). — 4370 — 4379. — <https://doi.org/10.1021/acsomega.9b04422>.

Gregoritz M., Brandl F.P. (2015). The Diels–Alder reaction: A powerful tool for the design of drug delivery systems and biomaterials. Eur J Pharm Biopharm. — 97 (B). — 438–453. — <https://doi.org/10.1016/j.ejpb.2015.06.007>.

Samir A., Ashour F.H., Hakim A.A.A. et al. (2022). Recent advances in biodegradable polymers for sustainable applications. npj Mater Degrad. — 6. — 68. — <https://doi.org/10.1038/s41529-022-00277-7>.

Štorha A., Mun E.A., Khutoryanskiy V. V. (2013) Synthesis of thiolated and acrylated nanoparticles using thiol-ene click chemistry: Towards novel mucoadhesive materials for drug delivery. RSC Advances. — 3. — 12275–12279. — <https://doi.org/10.1039/C3RA42093K>.

Shulen R., Kazybayeva D. (2021). Synthesis and characterization of new biodegradable gels based on 2,2'-(ethylenedioxy) diethanethiol and pentaerythritol triacrylate . CUMR. — 320 (1). — 25–31. — <https://doi.org/10.31643/2022/6445.03>.

МАЗМҰНЫ

Қ. Амантайұлы, С. Азат, Н.Н. Нурғалиев, Х. Аббас, Қ. Тоштай МЫРЫШ БАЛҚЫТУ ҚОЖДАРЫНЫҢ ҚҰРАМЫНАН МЫРЫШТЫ АММОНИЙ ХЛОРИДІ АРҚЫЛЫ ШАЙМАЛАП БӨЛІП АЛУ.....	7
Е.Б. Асылбеков, С.А. Тунгатарова, G.G. Xanthoroulou, Т.С. Байжуманова, М. Жумабек МЕТАНОЛДЫ SHS ӘДІСІМЕН СИНТЕЗДЕЛГЕН КАТАЛИЗАТОРЛАРДА СУТЕГІ БАР ЖАНАРМАЙ ҚОСПАСЫНА КОНВЕРСИЯЛАУ.....	21
С.Н. Ахметова, А.С. Ауезханова, А.К. Жармагамбетова, Э.Т. Талғатов, А.И. Джумекеева АЛКАНДАРДЫҢ СҰЙЫҚ ФАЗАЛЫҚ ТОТЫҒУЫНДА ГЕТЕРОГЕНДІ ХИТОЗАНМЕН ТҰРАҚТАНДЫРЫЛҒАН ХРОМ ЖӘНЕ ТЕМІР КАТАЛИЗАТОРЛАРЫНЫҢ КАТАЛИТИКАЛЫҚ ҚАСИЕТТЕРІН ЗЕРТТЕУ...34	34
М.Д. Даулетова, А.К. Умбетова, Ю.А. Литвиненко, Г.Ш. Бурашева, Н.С. Елибаева <i>POLYGANACEAE</i> ТҰҚЫМДАС ӨСІМДІК ТҮРІНЕН БИОЛОГИЯЛЫҚ БЕЛСЕНДІ КЕШЕНДІ АЛУ ЖОЛДАРЫН ҰСЫНУ.....	46
Г.Д. Жетписбаева, Б.К. Масалимова, В.А. Садықов ТРАНСМИССИЯЛЫҚ ЭЛЕКТРОНДЫ МИКРОСКОПИЯНЫҢ КӨМЕГІМЕН ПЕРОВСКИТ ТӘРІЗДІ КҮРДЕЛІ ОКСИДТЕРДІ ЗЕРТТЕУ.....	62
Б.И. Диханбаев, А.Б. Диханбаев, М.Б. Кошумбаев, Ж.Т. Бекишева ҚАЗАҚСТАН ЭНЕРГЕТИКАЛЫҚ КЕШЕНІНІҢ ЭКОЛОГИЯЛЫҚ ПРОБЛЕМАЛАРЫ ЖӘНЕ ҚАЛДЫҚСЫЗ ТЕХНОЛОГИЯЛАРҒА КӨШЕ ОТЫРЫП, ЖЫЛУ КӨМІР ЭНЕРГЕТИКАСЫН ДЕКАРБОНИЗАЦИЯЛАУ.....	70
Э.А. Камбарова, Н.А. Бектенов, А.К. Байдуллаева, М.А. Гавриленко ЦЕОЛИТ БЕТІНДЕГІ ЭПОКСИДІ ШАЙЫРЛЫ ПЛАНДАРДАҒЫ СОРБИЦИЯЛЫҚ ЗАТТАРДЫҢ БӨЛҮІ.....	87
М.Б. Камбатыров, П.А. Абдуразова, У.Б. Назарбек КӨМІР ӨНДІРУ ҚАЛДЫҚТАРЫН АЗЫҚ ӨНДІРУ ҮШІН ПАЙДАЛАНУ: ҚҰС ТАҒАМЫНДАҒЫ ГУМАТТАРДЫҢ ӘЛЕУЕТІН ЗЕРТТЕУ.....	99
М.М. Матаев, Г.С. Патрин, К.Ж. Сейтбекова, М.А. Нурбекова, М.Е. Жайсанбаева ШПИНЕЛЬ-ПЕРОВКСИТТИ КОМПОЗИЦИЯЛЫҚ МАТЕРИАЛДЫ ӨНДІРУ ЖӘНЕ ҚҰРЛЫМЫН ЗЕРТТЕУ ӘДІСІН ӘЗІРЛЕУ.....	114
Г. Мукушева, Р. Джалмаханбетова, М. Алиева, А. Самородов, А. Тәжібай ХИНИН АЛКАЛОИДЫНЫҢ СИНТЕЗДЕЛГЕН ТУЫНДЫЛАРЫНЫҢ АНТИКОАГУЛЯЦИЯЛЫҚ ЖӘНЕ АГРЕГАЦИЯҒА ҚАРСИ БЕЛСЕНДІЛІГІН ЗЕРТТЕУ.....	126
А.О. Оразымбетова, С.А. Сакибаева, Г.Ф. Сагитова, А.Ж. Суйгенбаева ШАНҚАНАЙ КЕН ОРНЫНДАҒЫ ЦЕОЛИТТЕРДІҢ ФИЗИКА-ХИМИЯЛЫҚ ҚАСИЕТТЕРІН ЗЕРТТЕУ.....	138
Ж. Рахимберлинова, И. Кулаков, Г. Якуда, А. Ағысбай, А. Альжанов ХЛОРАНҒАН КӨМІРЛЕР МЕН ХЛОРГУМИН ҚЫШҚЫЛДАРЫНА НЕГІЗДЕЛГЕН СИНТЕЗДЕР.....	151

В.В. Романов, В.В. Меркулов, С.К. Кабиева, Р.Қ. Жаслан, Л.М. Власова
КЛИНКЕРСІЗ ТҮТҚЫР ЗАТ АЛУ МАҚСАТЫНДА ДОМНА ӨНДІРІСІНІҢ
ТЕХНОГЕНДІК ҚАЛДЫҚТАРЫН ҚАЙТА ӨНДЕУ ПРОЦЕСІН ЗЕРТТЕУ.....164

Ә.И. Тасмағамбетова, А.Д. Товасаров, Н.Б. Акынбаев
ИТБАЛЫҚ МАЙЫНЫҢ ХИМИЯЛЫҚ ҚҰРАМЫН ЗЕРТТЕУ.....177

Р. Шулен, Д. Махаева, Д. Казыбаева, Г. Ирмухаметова, Г.А. Мун
ТЕТРААКРИЛАТ ПЕНТАЭРИТРИТОЛ ЖӘНЕ ТЕТРАКИС(3-
МЕРКАПТОПРОПИОНАТ) ПЕНТАЭРИТРИТОЛ НЕГІЗІНДЕ
БИОДЕГРАДАЦИЯЛАНАТЫН ДӘРІЛІК ФОРМАЛАРДЫ АЛУ.....191

СОДЕРЖАНИЕ

Қ. Амантайұлы, С. Азат, Н. Нурғалиев, Х. Аббас, Қ. Тошта ИЗВЛЕЧЕНИЕ ЦИНКА ИЗ ЦИНКОВЫХ ШЛАКОВ ПУТЕМ ВЫЩЕЛАЧИВАНИЯ ХЛОРИДОМ АММОНИЯ.....	7
Е.Б. Асылбеков, С.А. Тунгатарова, G.G. Xanthoroulou, Т.С. Байжуманова, М. Жумабек КОНВЕРСИЯ МЕТАНОЛА В ВОДОРОДСОДЕРЖАЩУЮ ТОПЛИВНУЮ СМЕСЬ НА КАТАЛИЗАТОРАХ, СИНТЕЗИРОВАННЫХ МЕТОДОМ SHS.....	21
С.Н. Ахметова, А.С. Ауезханова, А.К. Жармагамбетова, Э.Т. Талғатов, А.И. Джумекеева ИССЛЕДОВАНИЕ КАТАЛИТИЧЕСКИХ СВОЙСТВ ГЕТЕРОГЕННЫХ ХИТОЗАН-СТАБИЛИЗИРОВАННЫХ ХРОМОВЫХ И ЖЕЛЕЗНЫХ КАТАЛИЗАТОРОВ В ЖИДКОФАЗНОМ ОКИСЛЕНИИ АЛКАНОВ.....	34
М.Д. Даулетова, А.К. Умбетова, Ю.А. Литвиненко, Г.Ш. Бурашева, Н.С. Елибаева РАЗРАБОТКА СПОСОБА ПОЛУЧЕНИЯ БИОЛОГИЧЕСКИХ АКТИВНОЙ КОМПОЗИЦИИ НА ОСНОВЕ РАСТЕНИЙ СЕМЕЙСТВА POLYGANACEAE.....	46
Г.Д. Джетписбаева, Б.К. Масалимова, В.А. Садыков ИЗУЧЕНИЕ СЛОЖНЫХ ОКСИДОВ ПЕРОВСКИТНОГО ТИПА МЕТОДОМ ТРАНСМИССИОННОЙ ЭЛЕКТРОННОЙ МИКРОСКОПИИ.....	62
Б.И. Диханбаев, А.Б. Диханбаев, М.Б. Кошумбаев, Ж.Т. Бекишева ЭКОЛОГИЧЕСКИЕ ПРОБЛЕМЫ ЭНЕРГЕТИЧЕСКОГО КОМПЛЕКСА КАЗАХСТАНА И ДЕКАРБОНИЗАЦИЯ ТЕПЛОВОЙ УГОЛЬНОЙ ЭНЕРГЕТИКИ С ПЕРЕХОДОМ НА БЕЗОТХОДНЫЕ ТЕХНОЛОГИИ.....	70
Э.А. Камбарова, Н.А. Бектенов, А.К. Байдуллаева, М.А.Гавриленко РАСПРЕДЕЛЕНИЕ СОРБИРОВАННОГО ВЕЩЕСТВА В ПЛЕНКАХ ЭПОКСИДНОЙ СМОЛЫ НА ПОВЕРХНОСТИ ЦЕОЛИТА	87
М.Б. Камбатыров, П.А. Абдуразова, У.Б. Назарбек ИСПОЛЬЗОВАНИЕ ОТХОДОВ УГЛЕДОБЫЧИ ДЛЯ ПРОИЗВОДСТВА КОРМОВ: ИЗУЧЕНИЕ ПОТЕНЦИАЛА ГУМАТОВ В ПИТАНИИ ПТИЦЫ.....	99
М.М. Матаев, Г.С. Патрин, К.Ж. Сейтбекова, М.А. Нурбекова, М.Е. Жайсанбаева РАЗРАБОТКА СПОСОБА ПОЛУЧЕНИЯ И ИССЛЕДОВАНИЕ СТРУКТУРЫ ШПИНЕЛЬНО-ПЕРОВКСИТНОГО КОМПОЗИЦИОННОГО МАТЕРИАЛА....	114
Г. Мукушева, Р. Джалмаханбетова, М. Алиева, А. Самородов, А. Тәжібай ИЗУЧЕНИЕ АНТИКОАГУЛЯЦИОННОЙ И АНТИАГРЕГАЦИОННОЙ АКТИВНОСТИ СИНТЕЗИРОВАННЫХ ПРОИЗВОДНЫХ АЛКАЛОИДА ХИНИНА.....	126
А.О. Оразымбетова, С.А. Сакибаева, Г.Ф. Сагитова, А.Ж. Суйгенбаева ИССЛЕДОВАНИЕ ФИЗИКО-ХИМИЧЕСКИХ СВОЙСТВ ЦЕОЛИТОВ ЧАНКАНАЙСКОГО МЕСТОРОЖДЕНИЯ.....	138
Ж. Рахимберлинова, И. Кулаков, Г. Якуда, А. Ағысбай, А. Альжанов СИНТЕЗЫ НА ОСНОВЕ ХЛОРИРОВАННЫХ УГЛЕЙ И ХЛОРГУМИНОВЫХ КИСЛОТ	151

В.В. Романов, В.В. Меркулов, С.К. Кабиева, Р.Қ. Жаслан, Л.М. Власова ИССЛЕДОВАНИЕ ПРОЦЕССА ПЕРЕРАБОТКИ ТЕХНОГЕННЫХ ОТХОДОВ ДОМЕННОГО ПРОИЗВОДСТВА С ЦЕЛЬЮ ПОЛУЧЕНИЯ БЕЗКЛИНКЕРНОГО ВЯЖУЩЕГО.....	164
А.И. Тасмагамбетова, А.Д. Товасаров, Н.Б. Акынбаев ИССЛЕДОВАНИЕ ХИМИЧЕСКОГО СОСТАВА ЖИРА ТЮЛЕНЯ.....	177
Р. Шулен, Д. Махаева, Д. Казыбаева, Г. Ирмухаметова, Г.А. Мун ПОЛУЧЕНИЕ БИОДЕГРАДИРУЕМЫХ ЛЕКАРСТВЕННЫХ ФОРМ НА ОСНОВЕ ТЕТРААКРИЛАТА ПЕНТАЭРИТРИТОЛА И ТЕТРАКИС(3- МЕРКАПТОПРОПИОНАТА) ПЕНТАЭРИТРИТОЛА.....	191

CONTENTS

K. Amantaiuly, S. Azat, N.N. Nurgaliyev, Q. Abbas, K. Toshtay EXTRACTION OF ZINC FROM ZINC SMELTING SLAG BY LEACHING WITH AMMONIUM CHLORIDE.....	7
Y.B. Assylbekov, S.A. Tungatarova, G.G. Xanthopoulou, T.S. Baizhumanova, M. Zhumabek CONVERSION OF METHANOL INTO HYDROGEN-CONTAINING FUEL MIXTURE ON CATALYSTS SYNTHESIZED BY SHS METHOD.....	21
S.N. Akhmetova, A.S. Auyezkhanova, A.K. Zharmagambetova, E.T. Talgatov, A.I. Jumekeyeva STUDY OF THE CATALYTIC PROPERTIES OF HETEROGENEOUS CHI- TOSAN-STABILIZED CHROMIUM AND IRON CATALYSTS IN LIQUID-PHASE OXIDATION OF ALKANES.....	34
M.D. Dauletova, A.K. Umbetova, Yu.A. Litvinenko, G.Sh. Burasheva, N.S. Yelibaeva DEVELOPMENT OF A METHOD FOR OBTAINING A BIOLOGICALLY ACTIVE COMPOSITION BASED ON PLANTS OF THE <i>POLYGANACEAE</i> FAMILY.....	46
G.D. Jetpisbayeva, B.K. Massalimova, V.A. Sadykov STUDYING COMPLEX OXIDES OF THE PEROVSKITE TYPE BY THE METHOD OF FLASHED ELECTRON MICROSCOPY.....	62
B.I. Dikhanbayev, A.B. Dikhanbayev, M.B. Koshumbayev, Zh.T. Bekisheva ENVIRONMENTAL PROBLEMS OF KAZAKHSTAN'S ENERGY COMPLEX AND DECARBONIZATION OF THERMAL COAL POWER WITH THE TRANSITION TO WASTE-FREE TECHNOLOGIES.....	70
E.A. Kambarova, N.A. Bektenov, A.K. Baidullayeva, M.A. Gavrilenko DISTRIBUTION OF SORBED SUBSTANCE IN EPOXY RESIN FILMS ON THE SURFACE OF ZEOLITE, 2024	87
M.B. Kambatyrov, P.A. Abdurazova, U.B. Nazarbek UTILIZING COAL MINING WASTE FOR FEED PRODUCTION: EXPLORING THE POTENTIAL OF HUMATES IN POULTRY NUTRITION.....	99
M.M. Mataev, G.S. Patrin, K.Zh. Seitbekova, M.A. Nurbekova, M.E. Zhaisanbaeva DEVELOPMENT OF A METHOD FOR PRODUCING AND STUDYING THE STRUCTURE OF SPINEL-PEROVSKITE COMPOSITE MATERIAL.....	114
G. Mukusheva, R. Jalmakhanbetova, M. Aliyeva, A. Samorodov, A. Tazhibay STUDY OF ANTICOAGULATION AND ANTIAGGREGATIONAL ACTIVITY OF SYNTHESIZED QUININE ALKALOID DERIVATIVES.....	126
A.O. Orazymbetova, S.A. Sakibayeva, G.F. Sagitova, A.Zh. Suigenbayeva INVESTIGATION OF THE PHYSICO-CHEMICAL PROPERTIES OF ZEOLITES OF THE CHANGKANAI DEPOSIT.....	138
Zh. Rakhimberlinova, I. Kulakov, G. Yakuda, A. Agysbay, A. Alzhanov SYNTHESES BASED ON CHLORINATED CARBONS AND CHLOROHUMIC ACIDS.....	151

V. Romanov, V. Merkulov, S. Kabiyeva, R. Zhaslan, L. Vlasova
INVESTIGATION OF THE PROCESS OF PROCESSING TECHNOGENIC WASTE
FROM BLAST FURNACE PRODUCTION IN ORDER TO OBTAIN A CLIN-
KER-FREE BINDER.....164

A.I. Tasmagambetova, A.D. Tovassarov, N.B. Akynbayev
RESEARCH ON THE CHEMICAL COMPOSITION OF SEAL OIL.....177

R. Shulen, D. Makhayeva, D. Kazybayeva, G. Irmukhametova, G. Mun
CREATING BIODEGRADABLE DOSAGE FORMS BASED ON PENTAERYTHRI-
TOL TETRAACRYLATE AND TETRAKIS(3-MERCAPTOPROPIONATE)
PENTAERYTHRITOL.....191

Publication Ethics and Publication Malpractice in the journals of the National Academy of Sciences of the Republic of Kazakhstan

For information on Ethics in publishing and Ethical guidelines for journal publication see <http://www.elsevier.com/publishingethics> and <http://www.elsevier.com/journal-authors/ethics>.

Submission of an article to the National Academy of Sciences of the Republic of Kazakhstan implies that the described work has not been published previously (except in the form of an abstract or as part of a published lecture or academic thesis or as an electronic preprint, see <http://www.elsevier.com/postingpolicy>), that it is not under consideration for publication elsewhere, that its publication is approved by all authors and tacitly or explicitly by the responsible authorities where the work was carried out, and that, if accepted, it will not be published elsewhere in the same form, in English or in any other language, including electronically without the written consent of the copyright-holder. In particular, translations into English of papers already published in another language are not accepted.

No other forms of scientific misconduct are allowed, such as plagiarism, falsification, fraudulent data, incorrect interpretation of other works, incorrect citations, etc. The National Academy of Sciences of the Republic of Kazakhstan follows the Code of Conduct of the Committee on Publication Ethics (COPE), and follows the COPE Flowcharts for Resolving Cases of Suspected Misconduct (http://publicationethics.org/files/u2/New_Code.pdf). To verify originality, your article may be checked by the Cross Check originality detection service <http://www.elsevier.com/editors/plagdetect>.

The authors are obliged to participate in peer review process and be ready to provide corrections, clarifications, retractions and apologies when needed. All authors of a paper should have significantly contributed to the research.

The reviewers should provide objective judgments and should point out relevant published works which are not yet cited. Reviewed articles should be treated confidentially. The reviewers will be chosen in such a way that there is no conflict of interests with respect to the research, the authors and/or the research funders.

The editors have complete responsibility and authority to reject or accept a paper, and they will only accept a paper when reasonably certain. They will preserve anonymity of reviewers and promote publication of corrections, clarifications, retractions and apologies when needed. The acceptance of a paper automatically implies the copyright transfer to the National Academy of Sciences of the Republic of Kazakhstan.

The Editorial Board of the National Academy of Sciences of the Republic of Kazakhstan will monitor and safeguard publishing ethics.

Правила оформления статьи для публикации в журнале смотреть на сайтах:

**www.nauka-nanrk.kz
<http://chemistry-technology.kz/index.php/en/arhiv>
ISSN 2518-1491 (Online), ISSN 2224-5286 (Print)**

Подписано в печать 15.06.2024.
Формат 60x88¹/₈. Бумага офсетная. Печать – ризограф.
13,0 п.л. Тираж 300. Заказ 2.