

ISSN 2518-1491 (Online),
ISSN 2224-5286 (Print)



«ҚАЗАҚСТАН РЕСПУБЛИКАСЫ
ҰЛТТЫҚ ҒЫЛЫМ
АКАДЕМИЯСЫ» РҚБ

«ҚАЗАҚСТАН РЕСПУБЛИКАСЫ
ҰЛТТЫҚ ҒЫЛЫМ АКАДЕМИЯСЫ» РҚБ

Х А Б А Р Л А Р Ы

ИЗВЕСТИЯ

РОО «НАЦИОНАЛЬНОЙ
АКАДЕМИИ НАУК РЕСПУБЛИКИ
КАЗАХСТАН»

N E W S

OF THE ACADEMY OF SCIENCES
OF THE REPUBLIC OF
KAZAKHSTAN

SERIES
CHEMISTRY AND TECHNOLOGY

1 (462)

JANUARY – MARCH 2025

PUBLISHED SINCE JANUARY 1947

PUBLISHED 4 TIMES A YEAR

ALMATY, NAS RK

Бас редактор:

ЖҰРЫНОВ Мұрат Жұрынулы, химия ғылымдарының докторы, профессор, ҚР ҰҒА академигі, РБҚ ҚР ҰҒА президенті, АҚ «Д.В. Сокольский атындағы Отын, катализ және электрохимия институтының» бас директоры (Алматы, Қазақстан) <https://www.scopus.com/authid/detail.uri?authorId=6602177960>, <https://www.webofscience.com/wos/author/record/2017489>

Редакция алқасы:

ӘДЕКЕНОВ Серғазы Мыңжасарұлы (бас редактордың орынбасары), химия ғылымдарының докторы, профессор, ҚР ҰҒА академигі, «Фитохимия» Халықаралық ғылыми-өндірістік холдингінің директоры (Қарағанды, Қазақстан) <https://www.scopus.com/authid/detail.uri?authorId=7006153118>, <https://www.webofscience.com/wos/author/record/48648658>

АГАБЕКОВ Владимир Енокович (бас редактордың орынбасары), химия ғылымдарының докторы, профессор, Беларусь ҰҒА академигі, Жаңа материалдар химиясы институтының құрметті директоры (Минск, Беларусь) <https://www.scopus.com/authid/detail.uri?authorId=7004624845>, <https://www.webofscience.com/wos/author/record/28920574>

СТРНАД Мирослав, профессор, Чехия ғылым академиясының Эксперименттік ботаника институтының зертхана меңгерушісі (Оломоуц, Чехия) <https://www.scopus.com/authid/detail.uri?authorId=36789185000>, <https://www.webofscience.com/wos/author/record/18379>

БҮРКІТБАЕВ Мұхамбетқали, химия ғылымдарының докторы, профессор, ҚР ҰҒА академигі, (Алматы, Қазақстан) <https://www.scopus.com/authid/detail.uri?authorId=8513885600>, <https://www.webofscience.com/wos/author/record/691218>

ХОХМАНН Джудит, Сегед университетінің Фармацевтика факультетінің Фармакогнозия кафедрасының меңгерушісі, Жаратылыстану ғылымдарының пәнаралық орталығының директоры (Сегед, Венгрия) <https://www.scopus.com/authid/detail.uri?authorId=7004457196>, <https://www.webofscience.com/wos/author/record/15630788>

РОСС Самир, PhD, Миссисипи университетінің Өсімдік өнімдерін ғылыми зерттеу ұлттық орталығы, Фармация мектебінің профессоры (Окефорд, АҚШ) <https://www.scopus.com/authid/detail.uri?authorId=7401610128>, <https://www.webofscience.com/wos/author/record/47926269>

ХУТОРЯНСКИЙ Виталий, философия докторы (PhD, фармацевт), Реддинг университетінің профессоры (Реддинг, Англия) <https://www.scopus.com/authid/detail.uri?authorId=35606915700>, <https://www.webofscience.com/wos/author/record/221621>

ТЕЛТАЕВ Бағдат Бұрханбайұлы, техника ғылымдарының докторы, профессор, ҚР ҰҒА академигі, Қазақстан Республикасы Индустрия және инфрақұрылымдық даму министрлігі (Алматы, Қазақстан) <https://www.scopus.com/authid/detail.uri?authorId=6506225641>, <https://www.webofscience.com/wos/author/record/72161>

ФАРУК Асана Дар, Хамдар аль-Маджида Шығыс медицина колледжінің профессоры, Хамдард университетінің Шығыс медицина факультеті (Карачи, Пәкістан) <https://www.scopus.com/authid/detail.uri?authorId=55884056900>, <https://www.webofscience.com/wos/author/record/1796996>

ФАЗЫЛОВ Серік Драхметұлы, химия ғылымдарының докторы, профессор, ҚР ҰҒА академигі, Органикалық синтез және көмір химиясы институты директорының ғылыми жұмыстар жөніндегі орынбасары (Қарағанды, Қазақстан) <https://www.scopus.com/authid/detail.uri?authorId=6701472056>, <https://www.webofscience.com/wos/author/record/1541357>

ЖОРОБЕКОВА Шарипа Жоробекқызы, химия ғылымдарының докторы, профессор, Қырғызстан ҰҒА академигі, ҚР ҰҒА Химия және химиялық технология институты (Бішкек, Қырғызстан) <https://www.scopus.com/authid/detail.uri?authorId=6602652060>, <https://www.webofscience.com/wos/author/record/31723468>

ХАЛИКОВ Джурабай Халикович, химия ғылымдарының докторы, профессор, Тәжікстан ҒА академигі, В.И. Никитин атындағы Химия институты (Душанбе, Тәжікстан) <https://www.scopus.com/authid/detail.uri?authorId=6603735641>, <https://www.webofscience.com/wos/author/record/9567106>

ФАРЗАЛИЕВ Вағиф Меджидоглы, химия ғылымдарының докторы, профессор, АҰҒА академигі (Баку, Әзірбайжан) <https://www.scopus.com/authid/detail.uri?authorId=6601962486>, <https://www.webofscience.com/wos/author/record/21617033>

ГАРЕЛИК Хемда, философия докторы (PhD, химия), Халықаралық таза және қолданбалы химия одағының Химия және қоршаған орта бөлімінің президенті (Лондон, Англия) <https://www.scopus.com/authid/detail.uri?authorId=56010090400>, <https://www.webofscience.com/wos/author/record/29866743>

«ҚР ҰҒА Хабарлары. Химия және технология сериясы»

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Меншіктенуші: «Қазақстан Республикасының Ұлттық ғылым академиясы» РҚБ (Алматы қ.).

Ақпарат агенттігінің мерзімді баспасөз басылымын, ақпарат агенттігін және желілік басылымды қайта есепке қою туралы ҚР Мәдениет және Ақпарат министрлігі «Ақпарат комитеті» Республикалық мемлекеттік мекемесі **28.02.2025 ж.** берген №КЗ63ВРҮ00113743 Күәлік.

Тақырыптық бағыты: *химия және химиялық технология*

Мерзімділігі: жылына 4 рет.

<http://chemistry-technology.kz/index.php/en/arihiv>

© Қазақстан Республикасының Ұлттық ғылым академиясы РҚБ, 2025

Главный редактор:

ЖУРИНОВ Мурат Журинович, доктор химических наук, профессор, академик НАН РК, президент РОО Национальной академии наук Республики Казахстан, генеральный директор АО «Институт топлива, катализа и электрохимии им. Д.В. Сокольского» (Алматы, Казахстан), <https://www.scopus.com/authid/detail.uri?authorId=6602177960>, <https://www.webofscience.com/wos/author/record/2017489>

Редакционная коллегия:

АДЕКЕНОВ Сергазы Мынжасарович (заместитель главного редактора), доктор химических наук, профессор, академик НАН РК, директор Международного научно-производственного холдинга «Фитохимия» (Караганда, Казахстан), <https://www.scopus.com/authid/detail.uri?authorId=7006153118>, <https://www.webofscience.com/wos/author/record/48648658>

АГАБЕКОВ Владимир Енокович (заместитель главного редактора), доктор химических наук, профессор, академик НАН Беларуси, почетный директор Института химии новых материалов (Минск, Беларусь), <https://www.scopus.com/authid/detail.uri?authorId=7004624845>, <https://www.webofscience.com/wos/author/record/28920574>

СТРНАД Мирослав, профессор, заведующий лабораторией института Экспериментальной ботаники Чешской академии наук (Оломоуц, Чехия), <https://www.scopus.com/authid/detail.uri?authorId=36789185000>, <https://www.webofscience.com/wos/author/record/18379>

БУРКИТБАЕВ Мухамбеткали, доктор химических наук, профессор, академик НАН РК, (Алматы, Казахстан), <https://www.scopus.com/authid/detail.uri?authorId=8513885600>, <https://www.webofscience.com/wos/author/record/691218>

ХОХМАНН Джудит, заведующий кафедрой Фармакогнозии Фармацевтического факультета Университета Сегеда, директор Междисциплинарного центра естественных наук (Сегед, Венгрия), <https://www.scopus.com/authid/detail.uri?authorId=7004457196>, <https://www.webofscience.com/wos/author/record/15630788>

РОСС Самир, PhD, профессор Школы Фармации национального центра научных исследований растительных продуктов Университета Миссисипи (Оксфорд, США), <https://www.scopus.com/authid/detail.uri?authorId=7401610128>, <https://www.webofscience.com/wos/author/record/47926269>

ХУТОРЯНСКИЙ Виталий, доктор философии (Ph.D, фармацевт), профессор Университета Рединга (Рединг, Англия), <https://www.scopus.com/authid/detail.uri?authorId=35606915700>, <https://www.webofscience.com/wos/author/record/221621>

ТЕЛЬТАЕВ Багдат Бурханбайулы, доктор технических наук, профессор, академик НАН РК, Министерство Индустрии и инфраструктурного развития Республики Казахстан (Алматы, Казахстан), <https://www.scopus.com/authid/detail.uri?authorId=6506225641>, <https://www.webofscience.com/wos/author/record/72161>

ФАРУК Ахсана Дар, профессор колледжа Восточной медицины Хамдарда аль-Маджида, факультет Восточной медицины университета Хамдарда (Карачи, Пакистан), <https://www.scopus.com/authid/detail.uri?authorId=55884056900>, <https://www.webofscience.com/wos/author/record/1796996>

ФАЗЫЛОВ Серик Драхметович, доктор химических наук, профессор, академик НАН РК, заместитель директора по научной работе Института органического синтеза и углекислотной химии (Караганда, Казахстан), <https://www.scopus.com/authid/detail.uri?authorId=6701472056>, <https://www.webofscience.com/wos/author/record/1541357>

ЖОРОБЕКОВА Шарипа Жоробековна, доктор химических наук, профессор, академик НАН Кыргызстана, Институт химии и химической технологии НАН КР (Бишкек, Кыргызстан), <https://www.scopus.com/authid/detail.uri?authorId=6602652060>, <https://www.webofscience.com/wos/author/record/31723468>

ХАЛИКОВ Джурабай Халикович, доктор химических наук, профессор, академик АН Таджикистана, Институт химии имени В.И. Никитина АН РТ (Душанбе, Таджикистан), <https://www.scopus.com/authid/detail.uri?authorId=6603735641>, <https://www.webofscience.com/wos/author/record/9567106>

ФАРЗАЛИЕВ Вагиф Меджид оглы, доктор химических наук, профессор, академик НАНА (Баку, Азербайджан), <https://www.scopus.com/authid/detail.uri?authorId=6601962486>, <https://www.webofscience.com/wos/author/record/21617033>

ГАРЕЛИК Хемда, доктор философии (Ph.D, химия), президент Отдела химии и окружающей среды Международного союза чистой и прикладной химии (Лондон, Англия), <https://www.scopus.com/authid/detail.uri?authorId=56010090400>, <https://www.webofscience.com/wos/author/record/29866743>

«Известия НАН РК. Серия химии и технологии».

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Собственник: Республиканское общественное объединение «Национальная академия наук Республики Казахстан» (г. Алматы).

Свидетельство №KZ63VPY00113743 о повторной регистрации периодического печатного издания информационного агентства, информационного агентства и сетевого издания, выданное Республиканским государственным учреждением «Комитет информации» Министерства культуры и информации Республики Казахстан 28.02.2025 г.

Тематическая направленность: *химия и химические технологии*

Периодичность: 4 раза в год.

<http://chemistry-technology.kz/index.php/en/arhiv>

© РОО Национальная академия наук Республики Казахстан, 2025

Editor in chief:

ZHURINOV Murat Zhurinovich, doctor of chemistry, professor, academician of NAS RK, President of NAS RK RPA, general director of JSC "D.V. Sokolsky Institute of fuel, catalysis and electrochemistry (Almaty, Kazakhstan) <https://www.scopus.com/authid/detail.uri?authorId=6602177960>, <https://www.webofscience.com/wos/author/record/2017489>

Editorial board:

ADEKENOV Sergazy Mynzhasarovich (deputy editor-in-chief) doctor of chemical sciences, professor, academician of NAS RK, director of the International Scientific and Production Holding «Phytochemistry» (Karaganda, Kazakhstan) <https://www.scopus.com/authid/detail.uri?authorId=7006153118>, <https://www.webofscience.com/wos/author/record/48648658>

AGABEKOV Vladimir Enokovich (deputy editor-in-chief), doctor of chemistry, professor, academician of NAS of Belarus, honorary director of the Institute of Chemistry of new materials (Minsk, Belarus) <https://www.scopus.com/authid/detail.uri?authorId=7004624845>, <https://www.webofscience.com/wos/author/record/28920574>

STRNAD Miroslav, head of the laboratory of the Institute of Experimental Botany of the Czech Academy of Sciences, professor (Olomouc, Czech Republic) <https://www.scopus.com/authid/detail.uri?authorId=36789185000>, <https://www.webofscience.com/wos/author/record/18379>

BURKITBAYEV Mukhambetkali, doctor of chemistry, professor, academician of NAS RK, (Almaty, Kazakhstan) <https://www.scopus.com/authid/detail.uri?authorId=8513885600>, <https://www.webofscience.com/wos/author/record/691218>

HOHMANN Judith, head of the department of pharmacognosy, faculty of Pharmacy, University of Szeged, director of the interdisciplinary center for Life sciences (Szeged, Hungary) <https://www.scopus.com/authid/detail.uri?authorId=7004457196>, <https://www.webofscience.com/wos/author/record/15630788>

ROSS Samir, Ph.D, professor, school of Pharmacy, National Center for scientific research of Herbal Products, University of Mississippi (Oxford, USA) <https://www.scopus.com/authid/detail.uri?authorId=7401610128>, <https://www.webofscience.com/wos/author/record/47926269>

KHUTORYANSKY Vitaly, Ph.D, pharmacist, professor at the University of Reading (Reading, England) <https://www.scopus.com/authid/detail.uri?authorId=35606915700>, <https://www.webofscience.com/wos/author/record/221621>

TELTAYEV Bagdat Burkhanbayuly, doctor of technical sciences, professor, academician of NAS RK, Ministry of Industry and infrastructure development of the Republic of Kazakhstan (Almaty, Kazakhstan) <https://www.scopus.com/authid/detail.uri?authorId=6506225641>, <https://www.webofscience.com/wos/author/record/72161>

PHARUK Asana Dar, professor at Hamdard al-Majid college of Oriental medicine, faculty of Oriental medicine, Hamdard University (Karachi, Pakistan) <https://www.scopus.com/authid/detail.uri?authorId=55884056900>, <https://www.webofscience.com/wos/author/record/1796996>

FAZYLOV Serik Drakhmetovich, doctor of chemistry, professor, academician of NAS RK, deputy director of the Institute of Organic Synthesis and Coal Chemistry (Karaganda, Kazakhstan) <https://www.scopus.com/authid/detail.uri?authorId=6701472056>, <https://www.webofscience.com/wos/author/record/1541357>

ZHOROBEKOVA Sharipa Zhorobekovna, doctor of chemistry, professor, academician of NAS of Kyrgyzstan, Institute of Chemistry and chemical technology of NAS KR (Bishkek, Kyrgyzstan) <https://www.scopus.com/authid/detail.uri?authorId=6602652060>, <https://www.webofscience.com/wos/author/record/31723468>

KHALIKOV Jurabay Khalikovich, doctor of chemistry, professor, academician of the Academy of Sciences of Tajikistan, V.I. Nikitin Institute of Chemistry AS RT (Tajikistan) <https://www.scopus.com/authid/detail.uri?authorId=6603735641>, <https://www.webofscience.com/wos/author/record/9567106>

FARZALIEV Vagif Medzhid ogly, doctor of chemistry, professor, academician of NAS of Azerbaijan (Azerbaijan) <https://www.scopus.com/authid/detail.uri?authorId=6601962486>, <https://www.webofscience.com/wos/author/record/21617033>

GARELIK Hemda, PhD in chemistry, president of the department of Chemistry and Environment of the International Union of Pure and Applied Chemistry (London, England) <https://www.scopus.com/authid/detail.uri?authorId=56010090400>, <https://www.webofscience.com/wos/author/record/29866743>

News of the National Academy of Sciences of the Republic of Kazakhstan. Series of chemistry and technology.

ISSN 2518-1491 (Online),

ISSN 2224-5286 (Print)

Owner: RPA «National Academy of Sciences of the Republic of Kazakhstan» (Almaty).

The certificate of registration of a periodical printed publication in the Committee of Information of the Ministry of Information and Social Development of the Republic of Kazakhstan No. **KZ66VPY00025419**, issued **29.07.2020**.

Thematic scope: *organic chemistry, inorganic chemistry, catalysis, electrochemistry and corrosion, pharmaceutical chemistry and technology.*

Periodicity: 4 times a year.

Editorial address: 28, Shevchenko str., of. 219, Almaty, 050010, tel. 272-13-19

<http://chemistry-technology.kz/index.php/en/arhiv>

© National Academy of Sciences of the Republic of Kazakhstan, 2025

NEWS

OF THE NATIONAL ACADEMY OF SCIENCES OF THE REPUBLIC OF KAZAKHSTAN
SERIES CHEMISTRY AND TECHNOLOGY
ISSN 2224-5286

Volume 1. Number 462 (2025), 144–156

<https://doi.org/10.32014/2025.2518-1491.273>

МРНТИ 31.15.37

**E.Yu. Nakisko¹, N.N. Gavrilova¹, A.E. Tulegen², K.B. Bulekbayeva²,
G.K. Matniyazova³, 2025.**

¹D.I. Mendeleev University of Chemical Technology of Russia, Moscow, Russian;

²Taraz University named after M.H. Dulaty, Department of Chemistry and Chemical
Technology, Taraz, Kazakhstan;

³Astana International University, Astana, Kazakhstan.

E-mail: nsgavril@yahoo.com

DETERMINATION OF COAGULATION THRESHOLDS OF MOLYBDENUM-VANADIUM BLUE SOLS

Evgeniya Yur'evna Nakisko – postgraduate student of the Russian University of Chemical Technology named after D.I. Mendeleev, Moscow, Russian, E-mail: eu.visotskaya@yandex.ru <https://orcid.org/0009-0009-9287-6600>;

Gavrilova Natalia Nickolaevna Doctor of Chemical Sciences, D.I. Mendeleev University of Chemical Technology of Russia, Moscow, Russian, E-mail gavrilova.n.n@muctr.ru <https://orcid.org/0000-0002-9733-7130>;

Tulegen Aruzhan Erbolkyzy – 4th year student, Department of Chemistry and Chemical Technology, Taraz University named after M.H. Dulaty, Taraz, Kazakhstan <https://orcid.org/0009-0004-9792-3481>;

Bulekbayeva Kamila Baltabaevna – Candidate of Technical Sciences, Department of Chemistry and Chemical Technology, Associate Professor, Taraz University named after M.H. Dulaty, Taraz, Kazakhstan, E-mail: Nurhat2000@mail.ru, <https://orcid.org/0009-0003-1747-179X>;

Matniyazova Gulsim Kadyrzhanovna – PhD, Associate Professor Astana International University, Kazakhstan, E-mail: gulsim.matniyazova@mail.ru, <https://orcid.org/0000-0002-6820-5219>.

Abstract. Molybdenum-vanadium blue sols are colloidal dispersions known for their unique optical and chemical properties, making them important in catalysis, sensors, and materials science. The article discusses the coagulation threshold of the sol and the effect of electrolytes such as potassium nitrate, potassium chloride, and calcium nitrate on sol coagulation. This work discusses the conditions for the occurrence of coagulation, and considers the experience of conducting an experiment to achieve the goal. During the experimental work, it was concluded that to determine the coagulation threshold of the sol, it is necessary to take reagents with high concentrations, both sol and electrolytes. Since it is known that Mo-V blue is aggregation stable.

Thus, in the course of work, a sol Mo-V blue ratio [Mo]:[V] = 90:10 was synthesized using ascorbic acid as a reducing agent. The low content of ash and electrolyte, especially in the case of stable systems, such as molybdenum-vanadium blue, had to initiate reduced coagulation.

To achieve significant effects, high temperatures or changes in environmental conditions (pH, temperature) are necessary. For sol Mo-V, the constants of fast coagulation and half-time of coagulation were determined for KNO_3 : $k_b = 5 \cdot 10^{-4} \text{ m}^3/\text{particle} \cdot \text{s}$ and $\Theta = 1563 \text{ s}$, for KCl : $k_b = 4 \cdot 10^{-4} \text{ m}^3/\text{particle} \cdot \text{s}$ and $\Theta = 1000 \text{ s}$.

Keywords: Sol, coagulation, electrolytes, polyoxometalates, aggregation stability

**Е.Ю. Накисько¹, Н.Н. Гаврилова¹, А.Е. Тулеген², К.Б. Булекбаева²,
Г.Қ. Матниязова³, 2025.**

¹Д.И. Менделеев атындағы Ресейдің химиялық технология университеті,
Мәскеу, Ресей;

²М.Х. Дулати атындағы Тараз университеті, «Химия және химиялық технология»
кафедрасы, Тараз, Қазақстан;

³Астана халықаралық университеті, Астана, Қазақстан.
E-mail: nsgavril@yahoo.com

МОЛИБДЕН-ВНАДИЙ КӨК ҚОСЫЛЫСЫНЫҢ ҚОЙЫЛУ ШЕКТЕРІН АНЫҚТАУ

Накисько Евгения Юрьевна – аспирант, Д.И. Менделеев атындағы Ресейдің химиялық технология университеті, Мәскеу, Ресей, E-mail: eu.visotskaya@yandex.ru <https://orcid.org/0009-0009-9287-6600>

Гаврилова Наталья Николаевна – химия ғылымдарының докторы, Д.И. Менделеев атындағы Ресейдің химиялық технология университеті, Мәскеу, Ресей, E-mail: gavrilova.n.n@muctr.ru <https://orcid.org/0000-0002-9733-7130>;

Тулеген Аружан Ерболқызы – М.Х. Дулати атындағы Тараз университетінің «Химия және химиялық технология» кафедрасының 4-курс студенті, Тараз, Қазақстан, <https://orcid.org/0009-0004-9792-3481>;

Булекбаева Камила Балтабаевна – т.ғ.к., қауымдастырылған профессор, М.Х. Дулати атындағы Тараз университетінің «Химия және химиялық технология» кафедрасы, Тараз, Қазақстан, E-mail: Nurhat2000@mail.ru, <https://orcid.org/0009-0003-1747-179X>;

Матниязова Гүлсім Қадыржанқызы – PhD, қауымдастырылған профессор, Астана халықаралық университеті, Астана, Қазақстан, E-mail: gulsim.matniyazova@mail.ru, <https://orcid.org/0000-0002-6820-5219>.

Аннотация. Молибден-ванадий көгілдір түсті ерітінділер – олардың бірегей оптикалық және химиялық қасиеттерімен танымал коллоидтық дисперсиялар, оларды катализде, сенсорикада және материалтануда маңызды етеді. Мақалада золь коагуляциясының шегі және калий нитраты, калий хлориді және кальций нитраты сияқты электролиттердің золь коагуляциясына әсері қарастырылды. Бұл жұмыста коагуляцияның пайда болу жағдайлары қарастырылады, сонымен қатар мақсатқа жету үшін эксперименттер жүргізу тәжірибесі жасалды. Тәжірибелік жұмыс барысында зольдің коагуляция шегін анықтау үшін зольдің де, электролиттердің де концентрациясы жоғары реагенттерді алу керек деген Мо-V көктің агрегативті тұрақты екені белгілі болды.

Сондықтан, жұмыс барысында тотықсыздандырғыш ретінде аскорбин қышқылын қолданып, $[\text{Mo}]:[\text{V}] = 90:10$ қатынасы бар Мо-V көк золь синтезделді. Төмен күл мен электролит мөлшері, әсіресе молибден-ванадий көк сияқты тұрақты жүйелер жағдайында коагуляцияның төмендеуіне әкеледі.

Осындай маңызды әсерлерге қол жеткізу үшін жоғары температура немесе қоршаған орта жағдайларының өзгеруі (рН, температура) қажет. Мо-V золь үшін жылдам коагуляция константалары және коагуляцияның жартылай шығарылу кезеңі KNO_3 үшін анықталды: $k_b = 5 \cdot 10^{-4} \text{ м}^3/\text{бөлшек} \cdot \text{с}$ және $\Theta = 1563 \text{ с}$, KCl үшін: $k_b = 4 \cdot 10^{-4} \text{ м}^3/\text{бөлшек} \cdot \text{с}$ және $\Theta = 1000 \text{ с}$.

Түйін сөздер: Золь, коагуляция, электролиттер, полиоксометалаттар, агрегациялық тұрақтылық

**Е.Ю. Накисько¹, Н.Н. Гаврилова¹, А.Е. Тулеген², К.Б. Булекбаева²,
Г.К. Матниязова³, 2025.**

¹Российского химико-технологического университета имени Д.И. Менделеева, Москва, Россия;

²Таразский университет имени М.Х. Дулати, Кафедра химии и химической технологии, Тараз, Казахстан;

³Международный университет «Астана», Астана, Казахстан.
E-mail: rustem_ergali@mail.ru

ОПРЕДЕЛЕНИЕ ПОРОГОВ КОАГУЛЯЦИИ ЗОЛЕЙ МОЛИБДЕН- ВАНАДИЕВЫХ СИНЕЙ

Накисько Евгения Юрьевна – аспирантка, Российского химико-технологического университета имени Д.И. Менделеева, Москва, Россия, E-mail: eu.visotskaya@yandex.ru <https://orcid.org/0009-0009-9287-6600>;

Гаврилова Наталья Николаевна – доктор химических наук, Российский химико-технологический университет имени Д.И. Менделеева, Москва, Россия, E-mail: gavrilova.n.n@muctr.ru <https://orcid.org/0000-0002-9733-7130>;

Тулеген Аружан Ерболовна – студент 4 курса, факультет Химии и химической технологии, Таразского университета имени М.Х. Дулати, Тараз, Казахстан, <https://orcid.org/0009-0004-9792-3481>;

Булекбаева Камила Балтабаевна – кандидат технических наук, ассоциированный профессор, кафедра Химии и химической технологии, Таразского университета имени М.Х. Дулати, Тараз, Казахстан, E-mail: Nurhat2000@mail.ru, <https://orcid.org/0009-0003-1747-179X>;

Матниязова Гүльсим Кадыржановна – PhD, ассоциированный профессор, Международный университет Астана, Казахстан, E-mail: gulsim.matniyazova@mail.ru, <https://orcid.org/0000-0002-6820-5219>.

Аннотация. Золи молибденово-ванадиевого синего представляют собой коллоидные дисперсии, известные своими уникальными оптическими и химическими свойствами, что делает их важными в катализе, сенсорике и материаловедении. В статье рассматривается порог коагуляции золя и влияние электролитов, таких как нитрат калия, хлорид калия и нитрат кальция, на коагуляцию золя. В данной работе обсуждаются условия возникновения коагуляции, а также рассматривается опыт проведения эксперимента для достижения цели. В ходе экспериментальной работы был сделан вывод, что для определения порога коагуляции золя необходимо брать реагенты с высокими концентрациями, как золя, так и электролитов. Так как известно, что Мо-V синий агрегативно устойчив.

Таким образом, в ходе работы был синтезирован золь Мо-V синий с

соотношением $[Mo]:[V] = 90:10$ с использованием аскорбиновой кислоты в качестве восстановителя. Низкое содержание золя и электролита, особенно в случае стабильных систем, таких как молибден-ванадиевая синь, должно было инициировать пониженную коагуляцию.

Для достижения значительных эффектов необходимы высокие температуры или изменения условий окружающей среды (pH, температура). Для золя Mo-V были определены константы быстрой коагуляции и полупериод коагуляции для KNO_3 : $k_b = 5 \cdot 10^{-4} \text{ м}^3/\text{частица} \cdot \text{с}$ и $\Theta = 1563 \text{ с}$, для KCl: $k_b = 4 \cdot 10^{-4} \text{ м}^3/\text{частица} \cdot \text{с}$ и $\Theta = 1000 \text{ с}$.

Ключевые слова: золь, коагуляция, электролиты, полиоксометгалаты, агрегативная устойчивость.

Introduction. Colloidal systems, such as molybdenum-vanadium blue salts, exhibit unique optical and physical properties that largely depend on their stability and aggregation behavior. The critical concentration of coagulation is the most important parameter determining the stability of these colloids, since it marks the threshold at which the Van der Waals attraction overcomes the stabilizing forces, which leads to irreversible aggregation (Berouaken, et al, 2020).

In this study, we examine the coagulation behavior of molybdenum-vanadium blue salts by systematically changing the salt concentration and tracking changes in the average hydrodynamic diameter over time. The initial slope of the kinetic curves is proportional to the coagulation rate, which is small at sufficiently low salt concentrations and increases with increasing salt concentration until it reaches its maximum in the fast coagulation mode (Chudnovskii, 2002).

Stabilization of colloidal systems can be achieved through various mechanisms such as charge stabilization or steric stabilization. For blue molybdenum-vanadium salts, stability is likely mediated by a combination of electrostatic and steric forces, which can be adjusted by the presence of certain ions or surfactants (Fei, et al, 2014). The critical concentration of coagulation is influenced by several factors, including the concentration and distribution of colloidal components, the salt content, and the dielectric properties of the medium. However, the stability of these sols is very sensitive to changes in ionic strength, pH, and other environmental factors. Understanding the coagulation threshold — the minimum concentration of electrolyte required for rapid aggregation of colloidal particles — is important for monitoring their stability and optimizing their use (Navyashree, et al, 2018)

Blue molybdenum-vanadium sols are colloidal dispersions formed by reducing the ions of molybdate and vanadate. These sols exhibit unique optical and catalytic properties, which makes them interesting for materials science and chemistry. However, their stability is crucial for practical applications, as coagulation or aggregation can lead to loss of functionality. Understanding the coagulation thresholds under different conditions provides insight into the factors affecting sol stability and allows precise control of their behavior.

Preparation of sols. Blue molybdenum-vanadium salts were synthesized by reducing

a solution of potassium nitrite and calcium nitrate. Analytical KNO_3 and KCl were used as electrolytes to study coagulation thresholds. Before conducting an experiment on the effect of electrolytes on Mo-V blue, sol was synthesized and salt solutions with a volume of 100 ml, a concentration of 0.3 mol/l KNO_3 , 0.2 mol/l $\text{Ca}(\text{NO}_3)_2$ were prepared and electrolyte solutions with a volume of 50 ml, a concentration of 2 mol/l of KNO_3 and KCl . To do this, the mass of salt was determined by the formula:

$$m = n \cdot M$$

g – where m is the mass of the substance,

M – is the molar mass of the substance,

n – is the amount of the substance. From the equation it is necessary to find the amount of substance n according to the formula:

$$n = C \cdot V$$

where C – is the concentration of the solution,

V – is the volume of the solution.

The pH of the sol was determined before the experiment. Water was prepared with the same pH solution as the sol for dilution. To determine the pH of solutions, the device must be calibrated with a buffer solution with pH = 4.01 and 6.86. Before each pH meter measurement, the device was rinsed with distilled water so that the device would get rid of salt residue from previous measurements. Next, first release the electrode into a buffer solution with a pH of 4.01, then into a buffer solution with a pH = 6.86. After calibrating the device, the pH of the molybdenum-vanadium blue sol medium can be measured. Next, hydrochloric acid 2 M is needed to prepare acidified water.

To do this, immerse the electrode in distilled water, turn on the agitator, and gradually add hydrochloric acid to prepare the acidified water, then dilute the sol to the desired concentrations. The sol concentration is selected experimentally in such a way that when the absorption spectra are obtained, there is no shift of the maximum for Mo-V to blue (738 nm) (Jiwen, et al. 2015).

Materials and Methods. Based on data from previous studies, it is known that the MoV Salt has insufficient charge. Based on this, it was necessary to select suitable electrolytes for the experiment. K^+ , Na^+ , and Ca^{2+} were selected from the proposed series of cations. Thus, as electrolytes It was assumed that sol with a dispersed phase concentration of 0.035% undergoes coagulation at an electrolyte concentration of less than 0.3 mol/l. For the initial study of the coagulation threshold, the following electrolytes were selected: KNO_3 with a concentration of 0.3 mol/l and $\text{Ca}(\text{NO}_3)_2$ with a concentration of 0.2.

The volume of sol with a concentration of 0.035 % content is 10 ml. The proportions of acidified water and electrolyte used in the experiment are shown in Table 1.

Table 1. Compositions of sol samples for determining coagulation thresholds

№	1	2	3	4	5	6	7	8	9	10
Volume of water (acidified), ml	10,0	9,0	8,5	8,0	7,5	7,0	6,5	6,0	5,5	5,0
Volume of electrolytes, ml	0	1,0	1,5	2,0	2,5	3,0	3,5	4	4,5	5,0

10 test tubes are filled with 10 ml of dilute sol with a concentration of sol and water in the volume indicated in the table. The electrolyte is injected into each tube 2 minutes before measuring the absorption spectrum. This experiment did not yield results, so it was decided to investigate the kinetics of coagulation and change the concentrations of electrolytes and sol. Thus, KCl and KNO₃ were chosen as electrolytes, since Ca²⁺ cations are prone to precipitating with molybdates and vanadates. The parameters for determining the kinetic dependence are presented in Table 2.

Table 2. Concentrations of coagulation reagents

Parameter	Meaning
C _{mass.%} Sol Mo-V blue	0,17
C (KNO ₃), mol/l	0,8
C (KCl), mol/l	0,8

In this experiment, optical density was measured using a spectrophotometer over time with minimal confidence (502 nm). Based on the data obtained, the velocity constants were calculated using the Smolukhovsky equation (Liu, et al. 2015).

Table 3. Compositions of sol samples for determining coagulation thresholds for this experiment

Tube Number №	1	2	3	4	5	6	7	8	9	10
Volume of water (acidification), ml	9	8,8	8,5	8,0	7,5	7,0	6,5	6,0	5,5	5,0
The volume of the el-ta, ml	0	0,2	0,5	1,0	1,5	2,0	2,5	3,0	3,5	4,0

For the experiment, the samples were prepared as follows: 0.5 ml of concentrated sol and water were added to 10 test tubes in the volume indicated in Table 3. The total volume of the solution in each tube was 9.5 ml. The concentrations and compositions of the electrolytes were matched in accordance with the experimental provisions.

In this experimental work, an electrolyte and acidified water were introduced into samples with molybdenum vanadium blues at a constant concentration. After mixing all the reagents, it is necessary to wait 10 minutes for KCl, 15 minutes for KNO₃. Immediately after the expiration of the time, the optical density was measured at a minimum of absorption for molybdenum-vanadium blues.

Results and Discussion. When using electrolytes of Ca(NO₃)₂ with a concentration of 0.2 M and KNO₃ with a concentration of 0.3 M, the data presented in Figures 1-4 were obtained.




Figure 1. Effect of $\text{Ca}(\text{NO}_3)_2$ electrolyte concentration on the absorption spectra of MoV blue




Figure 2. Dependence of the change in optical density (502 nm) on the concentration of electrolyte $\text{Ca}(\text{NO}_3)_2$




Figure 3. The influence of the concentration of electrolyte KNO_3 on the absorption spectrum of Mo-V blue




Figure 4. Dependence of the change in optical density in the region of the absorption minimum (502 nm) on the concentration of electrolyte KNO_3

According to the obtained results, it is possible to notice that the coagulation of the sol does not occur at low concentrations of electrolytes. Coagulation does not occur in the first case (Figure 1,2) because calcium nitrate does not affect the coagulation of the Mo-V sol, since a chemical reaction can occur during interaction and a precipitate of molybdate or calcium vanadate is formed. In the second case (Figure 3,4), it is possible to notice that some signs of coagulation are present in the form of changes in optical density, but since the difference in values is small, we will not consider these values. The reason for this is the low concentration of sol and electrolyte, as well as the stability of molybdenum-vanadium blue dispersions (Rafique, et al. 2020).

When choosing the concentrations of sol and electrolyte, the concentrations of C sol (wt.%) = 0.035% and C (KNO_3) = 0.3 M were initially selected. For the second experiment, the concentration of C sol (wt.%) = 0.17% and the concentration of electrolytes 2 M of potassium nitrate and potassium chloride were taken. Further, by studying the kinetic dependence, the constant and half-coagulation time of the sol with KNO_3 electrolyte were determined:




Figure 5. Kinetic dependence of the change in the absorption minimum of Mo-V blue (502 nm) with KNO_3




Figure 6. Linearization of the kinetic dependence Mo-V sinei with KNO_3

According to the graph, the constant of rapid coagulation and the time of half coagulation were determined: $k_b = 5 \cdot 10^{-4} \text{ m}^3/\text{particle} \cdot \text{s}$ and $\Theta = 1563 \text{ s}$.

Then, after determining the time frame of the coagulation process, an experiment was conducted to determine the coagulation threshold. For this, absorption spectra of Mo-V blue with addition of different concentrations of KNO_3 were obtained (Figure 5-8).




Figure 7. Changes in Mo-V blue absorption spectra when adding KNO_3

Coagulation threshold for sol Mo-V blue with electrolyte KNO_3 was $S_k \text{KNO}_3 = 0.53 \text{ mol/l}$.

Next, the same experiment was conducted for KCl electrolyte, where the conditions of the experiment were identical. As can be seen from the data of coagulation kinetics (Figures 9, 10), the half-time of coagulation decreases.




Figure 8. Dependence of optical density on Mo-V blue in the region of minimum absorption (502 nm) of fire concentration electrolyte (KNO₃)




Figure 9. Kinetic dependence of the change in the absorption minimum of Mo-V blue (502 nm) with KCl




Figure 10. Linearization of the kinetic dependence for Mo-V blue with KCl




Figure 11. Changes in the absorption spectra of sols Mo-V blue with addition of KCl




Figure 12. Dependence of the optical density of Mo-V blue in the region of the absorption minimum on the electrolyte concentration (KCl)

As a result of the linearization of the kinetic dependence, the following were obtained: the fast coagulation constant and the half-coagulation time for Mo-V blue using KCl as an electrolyte: $k_b = 4 \cdot 10^{-4} \text{ m}^3/\text{particle} \cdot \text{s}$ and $\Theta = 1000 \text{ s}$.

Then, after determining the time frame of the coagulation process, an experiment was conducted to determine the coagulation threshold. For this, absorption spectra of Mo-V blue with addition of different concentrations of KCl were obtained (Figures 11, 12).

The coagulation threshold value for the studied electrolyte was 0.38 mol/l (Miras et al. 2012, Rand, et al. 2011, Toth, et al. 2019, Velmurugan, et al. 2019, Tan, et al. 2020).

Conclusion. Thus, in the course of work, a sol Mo-V blue ratio [Mo]:[V] = 90:10 was synthesized using ascorbic acid as a reducing agent. The low content of ash and electrolyte, especially in the case of stable systems, such as molybdenum-vanadium blue, had to initiate reduced coagulation. Chemical interaction of electrolytes with components of the sol (for example, the formation of precipitates) completely prevents coagulation (Камбалина, и др., 2014).

To achieve significant effects, high temperatures or changes in environmental conditions (pH, temperature) are necessary. For sol Mo-V, the constants of fast coagulation and half-time of coagulation were determined for KNO_3 : $k_b = 5 \cdot 10^{-4} \text{ m}^3/\text{particle} \cdot \text{s}$ and $\Theta = 1563 \text{ s}$, for KCl : $k_b = 4 \cdot 10^{-4} \text{ m}^3/\text{particle} \cdot \text{s}$ and $\Theta = 1000 \text{ s}$. The coagulation thresholds for the Mo-V blue electrolytes with KNO_3 $S_k = 0.52 \text{ mol/l}$ and KCl $S_k = 0.38 \text{ mol/l}$ were also obtained. During the work, it was determined that the threshold of coagulation of the sol with the studied electrolytes is reached at a sol concentration of 0.17 mass% and at a concentration of electrolytes of at least 0.4 mol/l (Офицеров, и др., 2011, Савченко, и др., 2013).

Литература

Berouaken M., Talbi L., Yaddadene C., Maoudj M., Menari H., Alkama R., Gabouze N. (2020). Room Temperature Ammonia Gas Sensor Based on V_2O_5 Nanoplatelets Quartz Crystal Microbalance. *Mater. Sci. Process.*, 126, 949 <https://www.mdpi.com/2079-4991/13/1/146> (in English)

Chudnovski F.A. (2002). Metal-insulator phase transition in disordered VO_2 . *Chem.*, 98, 137–145 <https://doklady.belnauka.by/jour/article/view/124/125> (in English)

Fei H., Lin Y., Wei M. (2014). Facile Synthesis of V_6O_{13} Micro-Flowers for Li-Ion and Na-Ion Battery Cathodes with Good Cycling Performance. *Colloid Interface Sci.*, 425, 1–4 <https://scite.ai/reports/facile-synthesis-of-v6o13-micro-flowers-Y9kzgd> (in English)

G.R. Navyashree, K. Hareesh, D.V. Sunitha, H. Nagabhushana, G. Nagaraju (2018). Photocatalytic degradation performance of Nd^{3+} doped V_2O_5 nanostructures. *Mater. Res. Express* 5 (9) <https://doi.org/10.1088/2053-1591/aad373>. (in English)

Jiwen Liu, Erik Luijten. (2005). Colloidal stabilization via nanoparticle halo formation. *Physical Review E*, 72 (6) <https://doi.org/10.1103/PhysRevE.72.061401>(in English)

Liu X., Conte M., Weng W., Knight D.W. (2015). Molybdenum blue nano-rings: An effective catalyst for the partial oxidation of cyclohexane. *Catalysis Science and Technology*, V.5. № 1, 217-227 <https://www.mdpi.com/1420-3049/26/15/4438> (in English)

M. Rafique, M. Hamza, M.B. Tahir, S. Muhammad, A.G. Al-Sehemi (2020). Facile hydrothermal synthesis of highly efficient and visible light-driven Ni-doped V_2O_5 photocatalyst for degradation. *Mater. Sci. Electron.*, 31 (15), 12913–12925 <https://doi.org/10.1007/s10854-020-03844-3> (in English)

Miras H.N., Richmond C.J., Long D., Cronin L. (2012). Solution-Phase Monitoring of the Structural Evolution of a Molybdenum Blue Nanoring. *Journal of American Chemical Society*, V. 134, 3816-3824 <https://pubmed.ncbi.nlm.nih.gov/22257105/> (in English)

Rand D., Ortiz V., Liu Y. et al. (2011). Nanomaterials for X-ray Imaging: Gold Nanoparticle-Enhancement of X-ray Scatter Imaging of Hepatocellular Carcinoma *Nano Letters*. Vol. 11, № 7, 2678-2683 <https://pubs.acs.org/doi/abs/10.1021/nl200858y>

Toth L.T., A. Stathakopoulos, R.A. Ruzicka and M.A. Kollala. (2019). Absolute and relative composition of the Holocene reef framework and modern reefs in the Florida Keys. *Geological Survey*, 9, 29-43 <https://esajournals.onlinelibrary.wiley.com/doi/epdf/10.1002/ecy.2781>(in English)

Velmurugan R., Premkumar J., Pitchai R., Ulaganathan M., Subramanian B. (2019). Robust, Flexible, and Binder Free Highly Crystalline V_2O_5 Thin Film Electrodes and Their Superior Supercapacitor Performances. *Chem. Eng.* 7, 13115-13126 <https://www.scinapse.io/papers/2961245485> (in English)

D. Tan, et al. (2020). Effective photocatalytic degradation of methyl orange using $\text{V}_2\text{O}_5@ \text{ZnO}$ nanocomposite under UV and visible irradiations. *Electrochem. Sci.* 15 12232–12243, <https://doi.org/10.20964/2020.12.75>. (in English)

Камбалина М.Г., Скворцова Л.Н., Мазурова И.С., Гусева Н.В., Бакибаев А.А. (2014). Исследование форм нахождения кремния в природных водах с высоким содержанием растворенных органических веществ. *Известия Томского политехнического университета* - № 3. – С.64-70 <file:///C:/Users/User/Downloads/%D0%92%D0%A0.pdf> (in Russian)

Офицеров Е.Н., Рябов Г.К., Убаскина Ю.А., Климовский А.Б., Фетюхина Е.Г. (2011). Кремний

и гуминовые кислоты: моделирование взаимодействий в почве. Известия Самарского Научного Центра Российской Академии Наук. – 2011. – Т. 13. - № 4. – С. 550–557 file:///C:/Users/User/Downloads/%D0%92%D0%A0.pdf.pdf (in Russian)

Савченко И.А., Корнеева И.Н., Плаксин Г.В., Лукша Е.А., Гончаров Д.С. (2013). Изменение свойств гуминовых веществ под воздействием УФ-света. Фундаментальные исследования. №10. Ч. 12. С. 2705–2709 file:///C:/Users/User/Downloads/%D0%92%D0%A0.pdf.pdf (in Russian)

References

Berouaken M., Talbi L., Yaddadene C., Maoudj M., Menari H., Alkama R., Gabouze N. (2020). Room Temperature Ammonia Gas Sensor Based on V_2O_5 Nanoplatelets Quartz Crystal Microbalance. *Mater. Sci. Process.*, 126, 949 <https://www.mdpi.com/2079-4991/13/1/146> (in English)

Chudnovski F.A. (2002). Metal-insulator phase transition in disordered VO_2 . *Chem.*, 98, 137–145 <https://doklady.belnauka.by/jour/article/view/124/125> (in English)

Fei H., Lin Y., Wei M. (2014). Facile Synthesis of V_6O_{13} Micro-Flowers for Li-Ion and Na-Ion Battery Cathodes with Good Cycling Performance. *Colloid Interface Sci.*, 425, 1–4 <https://scite.ai/reports/facile-synthesis-of-v6o13-micro-flowers-Y9kzgd> (in English)

G.R. Navayashree, K. Hareesh, D.V. Sunitha, H. Nagabhushana, G. Nagaraju (2018). Photocatalytic degradation performance of Nd^{3+} doped V_2O_5 nanostructures. *Mater. Res. Express* 5 (9) <https://doi.org/10.1088/2053-1591/aad373>. (in English)

Jiwen Liu, Erik Luijten. (2005). Colloidal stabilization via nanoparticle halo formation. *Physical Review E*, 72 (6) <https://doi.org/10.1103/PhysRevE.72.061401>(in English)

Liu X., Conte M., Weng W., Knight D.W. (2015). Molybdenum blue nano-rings: An effective catalyst for the partial oxidation of cyclohexane. *Catalysis Science and Technology*, V.5. № 1, 217-227 <https://www.mdpi.com/1420-3049/26/15/4438> (in English)

M. Rafique, M. Hamza, M.B. Tahir, S. Muhammad, A.G. Al-Sehemi (2020). Facile hydrothermal synthesis of highly efficient and visible light-driven Ni-doped V_2O_5 photocatalyst for degradation. *Mater. Sci. Electron.*, 31 (15), 12913–12925 <https://doi.org/10.1007/s10854-020-03844-3> (in English)

Miras H.N., Richmond C.J., Long D., Cronin L. (2012). Solution-Phase Monitoring of the Structural Evolution of a Molybdenum Blue Nanoring. *Journal of American Chemical Society*, V. 134, 3816-3824 <https://pubmed.ncbi.nlm.nih.gov/22257105/> (in English)

Rand D., Ortiz V., Liu Y. et al. (2011). Nanomaterials for X-ray Imaging: Gold Nanoparticle-Enhancement of X-ray Scatter Imaging of Hepatocellular Carcinoma *Nano Letters*. Vol. 11, № 7, 2678-2683 <https://pubs.acs.org/doi/abs/10.1021/nl200858y>

Toth L.T., A. Stathakopoulos, R.A. Ruzicka and M.A. Kollala. (2019). Absolute and relative composition of the Holocene reef framework and modern reefs in the Florida Keys. *Geological Survey*, 9, 29-43 <https://esajournals.onlinelibrary.wiley.com/doi/epdf/10.1002/ecy.2781>(in English)

Velmurugan R., Premkumar J., Pitchai R., Ulaganathan M., Subramanian B. (2019). Robust, Flexible, and Binder Free Highly Crystalline V_2O_5 Thin Film Electrodes and Their Superior Supercapacitor Performances. *Chem. Eng. 7*, 13115-13126 <https://www.scinapse.io/papers/2961245485> (in English)

D. Tan, et al. (2020). Effective photocatalytic degradation of methyl orange using $V_2O_5@ZnO$ nanocomposite under UV and visible irradiations. *Electrochem. Sci.* 15 12232–12243, <https://doi.org/10.20964/2020.12.75>. (in English)

Kambalina M.G., Skvortsova L.N., Mazurova I.S., Guseva N.V., Bakibaev A.A. (2014). [Study of silicon occurrence forms in natural waters with high content of dissolved organic matter]. *Bulletin of Tomsk Polytechnic University - No. 3*. - P.64-70 file:///C:/Users/User/Downloads/%D0%92%D0%A0.pdf.pdf (in Russian)

Ofitserov E.N., Ryabov G.K., Ubas'kina Yu.A., Klimovsky A.B., Fetyukhina E.G. (2011). [Silicon and humic acids: modeling of interactions in soil]. *Bulletin of the Samara Scientific Center of the Russian Academy of Sciences*. – 2011. – V. 13. - No. 4. – P. 550–557 file:///C:/Users/User/Downloads/%D0%92%D0%A0.pdf.pdf(in Russian)

Savchenko I.A., Korneeva I.N., Plaksin G.V., Luksha E.A., Goncharov D.S. (2013). [Changes in the properties of humic substances under the influence of UV light]. *Fundamental research*. No. 10. Part 12. P. 2705–2709 file:///C:/Users/User/Downloads/%D0%92%D0%A0.pdf.pdf (in Russian)

CONTENTS

A.A. Anarbayev, B.N. Kabyzbekova, J.E. Khusanov, G. M. Ormanova INVESTIGATION OF THE PROCESS OF OBTAINING A COMPLEX PHOSPHOHUMATE MINERAL FERTILIZER.....	5
G.Zh. Baisalova, A.A. Zhanybekova, A.B. Shukirbekova, B.B. Torsykbaeva, Sh.K. Utzhanova QUANTITATIVE DETERMINATION OF FLAVONOIDS IN ULMUS PUMILA LEAVES BY SPECTROPHOTOMETRIC METHOD.....	21
N. Bektenov, G. Koszhanova QUANTUM-CHEMICAL MODEL CALCULATION REVIEW OF VERMICULITE AND ITS BASED MODIFIED SORBENT.....	33
G.M. Zhusipnazarova, R. Reshmy, A.S. Dardenbayeva, Zh.B. Mukazhanova, G.B. Aubakirova PRODUCTION AND STUDY OF PROPERTIES OF BIOLOGICAL COATINGS BASED ON CELLULOSE OBTAINED FROM BARLEY AND FLAX STEMS.....	43
M. Ibrayeva, E. Sagindykova, Zh. Mukazhanova ISOLATION OF IRIDOIDS FROM <i>VERBASCUM MARSCHALLIANUM</i>	57
L.K. Kazhygeldiyeva, B.Kh. Mussabayeva, A.N. Sabitova, L.K. Orazzhanova, A.S. Seitkan DETERMINATION OF THE CHEMICAL COMPOSITION AND ANTIOXIDANT ACTIVITY OF FRUIT EXTRACTS FROM <i>HIPPOPHAE RHAMNOIDES</i> L. AND <i>CRATAEGUS SANGUINEA</i> L.	68
M.B. Kambatyrov, P.A. Abdurazova, U.B. Nazarbek, Y.B. Raiymbekov FTIR SPECTROSCOPIC STUDY OF HUMIC ACIDS PRECIPITATION.....	79
N.B. Kassenova, R. Sh. Erkassov, N.N. Nurmukhanbetova, S.K. Makhanova, G.K. Bekishova THE INVESTIGATION OF SPIN-CROSSOVER IN TETRANUCLEAR IRON (II) COMPLEXES BY MAGNETIC MEASUREMENTS.....	94
B.K. Massalimova, A.S. Dardenbayeva, Zh. Mukazhanova, K.A. Shorayeva, N.V. Ostafeychuk DEVELOPMENT AND STUDY OF CATALYSTS FOR DEHYDROGENATION OF SATURATED HYDROCARBONS TO OLEFINS.....	104

D.N. Makhayeva, Sh. Zhetesbayeva, G.S. Irmukhametova, Z.A. Kenessova PREPARATION AND CHARACTERIZATION OF POLYMER FILMS BASED ON IODINE COMPLEXED WITH POLY(2-ETHYL-2-OXAZOLINE).....	121
N. Merkhately, S.B. Abeuova, S.K. Zhokizhanova, A. Sviderskiy, S.A. Kairoldin INCLUSION OF AZULENE INTO THE BACKBONE OF CONJUGATED OLIGOMERS: IMPROVEMENT OF PROTON SENSITIVITY AND ELECTRONIC ABSORPTION.....	133
E. Yu. Nakisko, N. N. Gavrilova, A.E. Tulegen, K.B. Bulekbayeva, G.K. Matniyazova DETERMINATION OF COAGULATION THRESHOLDS OF MOLYBDENUM-VANADIUM BLUE SOLS.....	144
E.T. Talgatov, A.A. Naizabaev, A.M. Tynyshbay, A.S. Auezkhanova, A.Z. Abilmagzhanov INVESTIGATION OF COMPLEXATION OF RUTHENIUM (III) IONS WITH POLYMERS.....	157
A.A. Tolepbergen, U. Amzeyeva, Ye. Shybyray, A.Baiseitova, J. Jenis PHYTOCHEMICAL PROFILE OF UNDERGROUND PART OF CICHORIUM INTUBYS L.	170
T.S. Khosnutdinova, A.O. Sapieva, N.A. Sultanova, Sh.A. Madieva DEVELOPMENT OF A METHOD FOR OBTAINING A FLAVONOID COMPLEX FROM THE AERIAL PART OF <i>FERULA SONGARICA</i> PALL. EX SPRENG. WITH ANTIOXIDANT ACTIVITY.....	183
D.Y. Shoganbek, S.A. Tungatarova, D.Yu. Murzin, T.S. Baizhumanova, M. Zhumabek DRY REFORMING OF METHANE ON Co-La-Al AND Co-Ce-Al CATALYSTS PREPARED BY THE SCS METHOD.....	195

МАЗМҰНЫ

А.А. Анарбаев, Б.Н. Кабылбекова, Ж.Е. Хусанов, Г.М. Орманова КҮРДЕЛІ ФОСФОГУМАТТЫ МИНЕРАЛДЫ ТЫҢАЙТҚЫШ АЛУ ПРОЦЕССИН ЗЕРТТЕУ.....	5
Г.Ж. Байсалова, А.А. Жаныбекова, А.Б. Шукирбекова, Б.Б. Торсыкбаева, Ш.К. Утжанова <i>ULMUS PUMILA</i> ЖАПЫРАҚТАРЫНДАҒЫ ФЛАВОНОИДТАР МӨЛШЕРІН СПЕКТРОФОТОМЕТРЛІК ӘДІСПЕН АНЫҚТАУ.....	21
Н. Бектенов, Г. Қосжанова ВЕРМИКУЛИТ ЖӘНЕ ОНЫҢ НЕГІЗІНДЕ МОДИФИКАЦИЯЛАНҒАН СОРБЕНТТІҢ КВАНТТЫ-ХИМИЯЛЫҚ МОДЕЛІН ЕСЕПТЕУГЕ ШОЛУ.....	33
Г.М. Жусипназарова, Р. Решми, А.С. Дарменбаева, Ж.Б. Мукажанова, Г.Б. Аубакирова. АРПА МЕН ЗЫҒЫР САБАҒЫНАН АЛЫНҒАН ЦЕЛЛЮЛОЗА НЕГІЗІНДЕГІ БИОЛОГИЯЛЫҚ ЖАБЫНДАРДЫҢ ДАЙЫНДАЛУЫ ЖӘНЕ ҚАСИЕТТЕРІН ЗЕРТТЕУ.....	43
М. Ибраева, Э. Сагиндыкова, Ж. Мукажанова <i>VERBASCUM MARSCHALLIANUM</i> -НАН ИРИДОИДТАРДЫ БӨЛУ.....	57
Л.К. Қажыгелдиева, Б.Х. Мұсабаева, А.Н. Сабитова, Л.К. Оразжанова, А.С. Сейтқан. <i>HIPPURHAE RHAMNOIDES</i> L. ЖӘНЕ <i>CRATAEGUS SANGUINEA</i> L. ӨСІМДІК ЖЕМІСТЕРІНІҢ ЭКСТРАКТТАРЫНЫҢ ХИМИЯЛЫҚ ҚҰРАМЫН ЖӘНЕ АНТИОКСИДАНТТЫҚ БЕЛСЕНДІЛІГІН АНЫҚТАУ.....	68
М.Б. Камбатыров, П.А. Абдуразова, У.Б. Назарбек, Е.Б. Райымбеков ГУМИН ҚЫШҚЫЛДАРЫН ТҰНДЫРУ ҮРДІСІН ИҚ-СПЕКТРОСКОПИЯЛЫҚ ЗЕРТТЕУ.....	79
Н.Б. Касенова, Р.Ш. Еркасов, Н.Н. Нурмуханбетова, С.К. Маханова, Г.К. Бекишова МАГНИТТІК ӨЛШЕУЛЕР ӘДІСІМЕН ТЕМІРДІҢ (II) ТӨРТЯДРОЛЫ КЕШЕНДЕРІНДЕ СПИН-КРОССОВЕРДІ ЗЕРТТЕУ.....	94

Б.К. Масалимова, А.С. Дарменбаева, Ж.Б. Мукажанова, К.А. Шораева, Н.В. Остафейчук КӨМІРСУТЕКТЕРДІ ОЛЕФИНДЕРГЕ ДЕГИДРЛЕУ ҮШІН КАТАЛИЗАТОРЛАРДЫ ҚҰРУ ЖӘНЕ ЗЕРТТЕУ.....	104
Д.Н. Махаева, Ш. Жетесбаева, Ғ.С. Ирмухаметова, З.А. Кенесова ЙОДТЫҢ ПОЛИ(2-ЭТИЛ-2-ОКСАЗОЛИНМЕН) КЕШЕНІ НЕГІЗІНДЕ ПОЛИМЕРЛІ ҮЛДІРЛЕРДІ АЛУ ЖӘНЕ СИПАТТАУ.....	121
Н. Мерхатұлы, С.Б. Абеуова, С.К. Жокижанова, А. Свидерский, С.А. Қайролдин ҚОСАРЛАНҒАН ОЛИГОМЕРЛЕР НЕГІЗІНЕ АЗУЛЕНДІ ЕНГІЗУ: ПРОТОНҒА СЕЗІМТАЛДЫҚ ПЕН ЭЛЕКТРОНДЫҚ СІңІРУДІ ЖАҚСARTУ.....	133
Е. Ю. Накисько, Н. Н. Гаврилова, А.Е. Тулеген, К.Б. Булекбаева, Г.Қ. Матниязова МОЛИБДЕН-ВАНАДИЙ КӨК ҚОСЫЛЫСЫНЫҢ ҚОЙЫЛУ ШЕКТЕРІН АНЫҚТАУ.....	144
Э.Т. Талғатов, А.А. Найзабаев, А.М. Тынышбай, А.С. Ауезханова, А.З. Абильмагжанов РУТЕНИЙ (III) ИОНДАРЫМЕН ПОЛИМЕРЛЕРДІҢ КЕШЕН ТҮЗУІН ЗЕРТТЕУ.....	157
А.А. Төлепберген, Ұ. Әмзеева, Е. Шыбырай, А. Байсеитова, Ж. Жеңіс <i>SICHORIUM INTYBUS</i> L. ӨСІМДІГІНІҢ ЖЕР АСТЫ БӨЛІГІНІҢ ФИТОХИМИЯЛЫҚ ПРОФИЛІ.....	170
Т.С. Хоснутдинова, А.О. Сәпиева, Н.А. Сұлтанова, Ш.А. Мадиева АНТИОКСИДАНТТЫҚ БЕЛСЕНДІЛІККЕ ИЕ <i>FERULA SONGARICA</i> PALL. EX SPRENG. ЖЕР ҮСТІ БӨЛІГІНЕН ФЛАВОНОИДТЫ КЕШЕНДІ АЛУ ӘДІСІН ӘЗІРЛЕУ.....	183
Д.Е. Шоғанбек, С.А. Тунгатарова, Д.Ю. Мурзин, Т.С. Байжуманова, М. Жұмабек ЖТС ӘДІСІМЕН ДАЙЫНДАЛҒАН Co-La-Al ЖӘНЕ Co-Ce-Al КАТАЛИЗАТОРЛАРЫНДА МЕТАНДЫ ҚҰРҒАҚ РИФОРМАЛАУ.....	194

СОДЕРЖАНИЕ

А.А. Анарбаев, Б.Н. Кабылбекова, Ж.Е. Хусанов, Г.М. Орманова ИССЛЕДОВАНИЕ ПРОЦЕССА ПОЛУЧЕНИЯ КОМПЛЕКСНОГО ФОСФОГУМАТНОГО МИНЕРАЛЬНОГО УДОБРЕНИЯ.....	5
Г.Ж. Байсалова, А.А. Жаныбекова, А.Б. Шукирбекова, Б.Б. Торсыкбаева, Ш.К. Утжанова КОЛИЧЕСТВЕННОЕ ОПРЕДЕЛЕНИЕ ФЛАВОНОИДОВ В ЛИСТЯХ ULMUS PUMILA СПЕКТРОФОТОМЕТРИЧЕСКИМ МЕТОДОМ.....	21
Н. Бектенов, Г. Косжанова ОБЗОР КВАНТОВО-ХИМИЧЕСКОЙ МОДЕЛИ РАСЧЕТА ВЕРМИКУЛИТА И МОДИФИЦИРОВАННОГО СОРБЕНТА НА ЕГО ОСНОВЕ.....	33
Г.М. Жусипназарова, Р. Решми, А.С. Дарменбаева, Ж.Б. Мукажанова, Г.Б. Аубакирова СИНТЕЗ И ИЗУЧЕНИЕ СВОЙСТВ БИОЛОГИЧЕСКИХ ПОКРЫТИЙ НА ОСНОВЕ ЦЕЛЛЮЛОЗЫ, ПОЛУЧЕННОЙ ИЗ СТЕБЕЛЕЙ ЯЧМЕНЯ И ЛЬНА.....	43
М. Ибраева, Э. Сагиндыкова, Ж. Мукажанова ВЫДЕЛЕНИЕ ИРИДОИДОВ ИЗ VERBASCUM MARSCHALLIANUM.....	57
Л.К. Кажыгелдиева, Б.Х. Мусабаева, А.Н. Сабитова, Л.К. Оразжанова, А.С. Сейткан ОПРЕДЕЛЕНИЕ ХИМИЧЕСКОГО СОСТАВА И АНТИОКСИДАНТНОЙ АКТИВНОСТИ ЭКСТРАКТОВ ПЛОДОВ РАСТЕНИЙ HIPPOPHAE RHAMNOIDES L. И CRATAEGUS SANGUINEA L	68
М.Б. Камбатыров, П.А. Абдуразова, У.Б. Назарбек, Е.Б. Райымбеков ИК-СПЕКТРОСКОПИЧЕСКОЕ ИССЛЕДОВАНИЕ ОСАЖДЕНИЯ ГУМИНОВЫХ КИСЛОТ.....	79
Н.Б. Касенова, Р.Ш. Еркасов, Н.Н. Нурмуханбетова, С.К. Маханова, Г.К. Бекишова ИССЛЕДОВАНИЕ СПИН-КРОССОВЕРА В ТЕТРАЯДЕРНЫХ КОМПЛЕКСАХ ЖЕЛЕЗА (II) МЕТОДОМ МАГНИТНЫХ ИЗМЕРЕНИЙ.....	94

Б.К. Масалимова, А.С. Дарменбаева, Ж.Б. Мукажанова, К.А. Шораева, Н.В. Остафейчук РАЗРАБОТКА И ИЗУЧЕНИЕ КАТАЛИЗАТОРОВ ДЛЯ ДЕГИДРИРОВАНИЯ УГЛЕВОДОРОДОВ ДО ОЛЕФИНОВ.....	104
Д.Н. Махаева, Ш. Жетесбаева, Г.С. Ирмухаметова, З.А. Кенесова ПОЛУЧЕНИЕ И ХАРАКТЕРИСТИКА ПОЛИМЕРНЫХ ПЛЕНОК НА ОСНОВЕ КОМПЛЕКСА ЙОДА С ПОЛИ (2-ЭТИЛ-2-ОКСАЗОЛИНОМ).....	121
Н. Мерхатулы, С.Б. Абеуова, С.К. Жокижанова, А. Свидерский, С.А. Кайролдин ВВЕДЕНИЕ АЗУЛЕНА В ОСНОВУ СОПРЯЖЕННЫХ ОЛИГОМЕРОВ: УЛУЧШЕНИЕ ПРОТОННОЙ ЧУВСТВИТЕЛЬНОСТИ И ЭЛЕКТРОННОГО ПОГЛОЩЕНИЯ.....	133
Е. Ю. Накисько, Н. Н. Гаврилова, А.Е. Тулеген, К.Б. Булекбаева, Г.К. Матниязова ОПРЕДЕЛЕНИЕ ПОРОГОВ КОАГУЛЯЦИИ ЗОЛЕЙ МОЛИБДЕН-ВАНАДИЕВЫХ СИНЕЙ.....	144
Э.Т. Талгатов, А.А. Найзабаев, А.М. Тынышбай, А.С. Ауезханова, А.З. Абильмагжанов ИССЛЕДОВАНИЕ КОМПЛЕКСООБРАЗОВАНИЯ ИОНОВ РУТЕНИЯ (III) С ПОЛИМЕРАМИ.....	157
А.А. Толепберген, У. Амзеева, Е. Шыбырай, А. Байсеитова, Ж. Женис ФИТОХИМИЧЕСКИЙ ПРОФИЛЬ ПОДЗЕМНОЙ ЧАСТИ CICHORIUM INTYBUS L.	170
Т.С. Хоснутдинова, А.О. Сапиева, Н.А. Султанова, Ш.А. Мадиева РАЗРАБОТКА СПОСОБА ПОЛУЧЕНИЯ ФЛАВОНОИДНОГО КОМПЛЕКСА ИЗ НАДЗЕМНОЙ МАССЫ FERULA SONGARICA PALL. EX SPRENG., ОБЛАДАЮЩЕГО АНТИОКСИДАНТНОЙ АКТИВНОСТЬЮ.....	183
Д.Е. Шоганбек, С.А. Тунгатарова, Д.Ю. Мурзин, Т.С. Байжуманова, М. Жумабек СУХОЙ РИФОРМИНГ МЕТАНА НА КАТАЛИЗАТОРАХ CO-LA-AL И CO-SE-AL ПРИГОТОВЛЕННЫХ МЕТОДОМ СВС.....	194

Publication Ethics and Publication Malpractice in the journals of the National Academy of Sciences of the Republic of Kazakhstan

For information on Ethics in publishing and Ethical guidelines for journal publication see <http://www.elsevier.com/publishingethics> and <http://www.elsevier.com/journal-authors/ethics>.

Submission of an article to the National Academy of Sciences of the Republic of Kazakhstan implies that the described work has not been published previously (except in the form of an abstract or as part of a published lecture or academic thesis or as an electronic preprint, see <http://www.elsevier.com/postingpolicy>), that it is not under consideration for publication elsewhere, that its publication is approved by all authors and tacitly or explicitly by the responsible authorities where the work was carried out, and that, if accepted, it will not be published elsewhere in the same form, in English or in any other language, including electronically without the written consent of the copyright-holder. In particular, translations into English of papers already published in another language are not accepted.

No other forms of scientific misconduct are allowed, such as plagiarism, falsification, fraudulent data, incorrect interpretation of other works, incorrect citations, etc. The National Academy of Sciences of the Republic of Kazakhstan follows the Code of Conduct of the Committee on Publication Ethics (COPE), and follows the COPE Flowcharts for Resolving Cases of Suspected Misconduct (http://publicationethics.org/files/u2/New_Code.pdf). To verify originality, your article may be checked by the Cross Check originality detection service <http://www.elsevier.com/editors/plagdetect>.

The authors are obliged to participate in peer review process and be ready to provide corrections, clarifications, retractions and apologies when needed. All authors of a paper should have significantly contributed to the research.

The reviewers should provide objective judgments and should point out relevant published works which are not yet cited. Reviewed articles should be treated confidentially. The reviewers will be chosen in such a way that there is no conflict of interests with respect to the research, the authors and/or the research funders.

The editors have complete responsibility and authority to reject or accept a paper, and they will only accept a paper when reasonably certain. They will preserve anonymity of reviewers and promote publication of corrections, clarifications, retractions and apologies when needed. The acceptance of a paper automatically implies the copyright transfer to the National Academy of Sciences of the Republic of Kazakhstan.

The Editorial Board of the National Academy of Sciences of the Republic of Kazakhstan will monitor and safeguard publishing ethics.

Правила оформления статьи для публикации в журнале смотреть на сайтах:

www.nauka-nanrk.kz

<http://chemistry-technology.kz/index.php/en/arhiv>

ISSN 2518-1491 (Online), ISSN 2224-5286 (Print)

Директор отдела издания научных журналов НАН РК *А. Ботанқызы*

Редакторы: *Д.С. Аленов, Ж.Ш. Әден*

Верстка на компьютере *Г.Д. Жадырановой*

Подписано в печать 20.06.2025.

Формат 60x88¹/₈. Бумага офсетная. Печать – ризограф.

13,5 п.л. Заказ 2.